

Australian/New Zealand Standard™

Methods of test for pulp and paper

Method 209: Laboratory processing of
pulp—PFI mill method



AS/NZS 1301.209:2017

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 20 March 2017 and by the New Zealand Standards Approval Board on 5 April 2017.

This Standard was published on 9 May 2017.

The following are represented on Committee PK-019:

Appita
Monash University
New Zealand Paper Forum
Scion

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com or Standards New Zealand web site at www.standards.govt.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of Standards Australia or the New Zealand Standards Executive at the address shown on the back cover.

This Standard was issued in draft form for comment as DR AS.NZS 1301.209:2016.

Australian/New Zealand Standard™

Methods of test for pulp and paper

**Method 209: Laboratory processing of
pulp—PFI mill method**

Originally in Australia as AS 1301.P209ts—1975.
Previous and first joint edition AS/NZS 1301.209s:2003.
Completely revised and redesignated as AS/NZS 1301.209:2017.

COPYRIGHT

© Standards Australia Limited

© The Crown in right of New Zealand, administered by the New Zealand Standards Executive

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, PO Box 1473, Wellington 6140.

ISBN 978 1 76035 755 9

PREFACE

This Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper, to supersede AS/NZS 1301.209s:2003, *Methods of test for pulp and paper Method 209s: Laboratory processing of pulp—PFI mill method*.

This Standard is part of the AS/NZS 1301 series, *Methods of test for pulp and paper*.

The objective of this Standard is to set out a procedure for the beating of pulp using a PFI mill. Information on care and maintenance of the mill is also provided.

This Standard is an adoption with national modifications and has been reproduced from ISO 5264-2:2011, *Pulps—Laboratory beating—Part 2: PFI mill method*, and has been varied as indicated to take account of Australian/New Zealand conditions. The modifications are specified in Appendix ZZ (normative). Informative Appendix ZA has been added to provide additional information on the conditioning of the surfaces of the beating elements.

A similar Standard that is also used in place of this Standard is TAPPI T248, *Laboratory beating of pulp (PFI mill method)*.

As this Standard is reproduced from an International Standard, the following applies:

- (A) In the source text ‘this part of ISO 5264’ should read ‘this Australian/New Zealand Standard’.
- (B) A full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific standards.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annex or appendix to which they apply. A ‘normative’ annex or appendix is an integral part of a Standard, whereas an ‘informative’ annex or appendix is for information and guidance only.

CONTENTS

1	Scope.....	1
2	Normative references.....	1
3	Principle	1
4	Apparatus and auxiliary materials.....	1
5	Sampling	1
6	Preparation of sample.....	1
7	Procedure.....	2
8	Test report.....	4
	Annex A (normative) PFI mill	5
	Annex B (normative) Control and maintenance of the PFI mill	8
	Annex C (informative) Checking the stability of the PFI mill	10
	Bibliography	11

Currently in preview, click buy full version

INTRODUCTION

In view of the widespread use of the following beaters:

- Valley beater,
- PFI mill,

it has been decided to provide guidance on the use of these beaters in order to achieve consistency of results with each instrument. Although both beaters show similar trends in the effect on pulp properties, there is no correlation between the actual results obtained with the different types of beaters.

ISO 5264-1 specifies a method of laboratory beating using a Valley beater.

Beating is a preliminary step in the preparation of laboratory sheets for testing the physical properties of pulps. In the PFI mill, each beating is performed separately, i.e. a new test portion of unbeaten pulp is taken for each beating.

NOTE A complete test of physical properties normally comprises unbeaten pulp and several beatings of the same pulp, where the beating is carried out for different numbers of roll revolutions. The number of roll revolutions depends on the type of pulp and the beating load. After beating, the drainability is measured according to ISO 5267-1 or ISO 5267-2, and laboratory sheets are prepared according to ISO 5269-1^[1], ISO 5269-2^[2] or ISO 5269-3^[3]. Physical testing of the laboratory sheets is performed according to ISO 5270^[4].

AUSTRALIAN/NEW ZEALAND STANDARD

Methods of test for pulp and paper

Method 209

Laboratory processing of pulp—PFI mill method

1 Scope

This part of ISO 5264 specifies a method for the laboratory beating of pulp using a PFI mill. The description is limited to the sampling, preparation and beating of the pulp and the beating equipment.

NOTE Beating is a preliminary step in testing the physical properties of pulp.

In principle, this method is applicable to all kinds of chemical and semi-chemical pulps. In practice, the method might not give satisfactory results with certain pulps having extremely long fibres.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*

ISO 4119, *Pulps — Determination of stock concentration*

ISO 5263-1, *Pulps — Laboratory wet disintegration — Part 1: Disintegration of chemical pulps*

ISO 5267-1, *Pulps — Determination of drainage ability — Part 1: Schopper-Riegler method*

ISO 5267-2, *Pulps — Determination of drainage ability — Part 2: "Canadian Standard" freeness method*

ISO 7213, *Pulps — Sampling for testing*

ISO 14487, *Pulps — Standard water for physical testing*

3 Principle

A measured amount of pulp at a specified stock concentration is beaten between a roll with bars and a smooth beater housing, both rotating in the same direction, but at different peripheral speeds.

4 Apparatus and auxiliary materials

Use ordinary laboratory equipment and the following.

4.1 PFI mill, as specified in Annex A.

See Annexes B and C.