

Australian/New Zealand Standard™

Methods of test for pulp and paper

Part 210s: Alkali solubility of pulp



AS/NZS 1301.210s:2002

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 17 May 2002 and on behalf of the Council of Standards New Zealand on 9 May 2002. It was published on 19 June 2002.

The following are represented on Committee PK-019:

Appita Inc.
AusInfo
CSIRO Forestry and Forest Products
Forest Research (New Zealand)
National Association of Forest Industries
New Zealand Pulp and Paper Industry Association
Printing Industries Association of Australia
Pulp and Paper Manufacturers Federation of Australia

Additional interests participating in the preparation of this Standard are:
Paper manufacturers
Pulp manufacturers
Research interests
Manufacturers of paper testing instruments
Suppliers of paper testing instruments

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Australia web site at www.standards.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia International or Standards New Zealand at the address shown on the back cover.

Australian/New Zealand Standard™

Methods of test for pulp and paper

Part 210s: Alkali solubility of pulp

Originated as AS P1.P210m—1962.
Previous edition AS P1.P210m—1969.
Revised and redesignated as AS/NZS 1301.210s:2002.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

ISBN 0 7337 4549 0

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper as a revision of AS Pl.P210m—1969, which was withdrawn in July 1996.

The objective of this Standard is to provide those involved with the analysis of pulps a standardized method of determining the cold alkali solubility of pulp.

This Standard is identical with and has been reproduced from ISO 692:1982, *Pulps — Determination of alkali solubility*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text 'this International Standard' should read 'this Australian/New Zealand Standard'.
- (c) A full point should be substituted for a comma when referring to a decimal number.

References to International Standards should be replaced by references to equivalent Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian/New Zealand Standard</i>
ISO	AS/NZS
638 Pulps — Determination of dry matter content	—

AUSTRALIAN/NEW ZEALAND STANDARD

Methods of test for pulp and paper

Method 210s:

Alkali solubility of pulp

0 Introduction

The object of both this International Standard and ISO 699, *Pulps — Determination of alkali resistance*, is to permit the study of the behaviour of pulps in the presence of alkali solutions, but their fields of application are different: while this International Standard describes the volumetric determination of the alkali-soluble constituents of the pulp and is applied preferably to the control of bleached pulps, ISO 699 describes the gravimetric determination of the alkali-insoluble constituents of the pulp and applies to all categories of pulps.

1 Scope and field of application

This International Standard specifies a method for the determination of the solubility of pulp in cold sodium hydroxide solutions of various and fixed concentrations. The sodium hydroxide concentrations most frequently used are 18 and 10 % (*m/m*).

The method is mainly intended for the investigation of bleached pulps, but may, however, also be used with unbleached pulps, for example in the different stages of manufacture of bleached pulp.

2 Reference

ISO 638, *Pulps — Determination of dry matter content*.

3 Definitions

3.1 S-value Alkali solubility; the soluble fraction expressed as a percentage by mass of the oven-dry pulp.

3.2 S_{18} , S_{10} or S_c : S-values in which the indices 18, 10 or *c* refer to the chosen concentration, in grams of sodium hydroxide per 100 g of solution.

4 Principle

Treatment of the pulp with sodium hydroxide solution and oxidation of the dissolved organic matter with potassium dichromate. Titration of the excess potassium dichromate and calculation of the amount of cellulose equivalent to the potassium dichromate consumed.

5 Reagents

Use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

5.1 Sodium hydroxide, solution of known concentration, containing less than 1 g of sodium carbonate per litre (see the note), for example:

— 5,39 ± 0,03 mol/l solution, containing 18,0 ± 0,1 g of sodium hydroxide per 100 g of solution ($\rho_{20} = 1,197\ 2$ g/ml), equivalent to 215,5 ± 1,0 g of sodium hydroxide per litre;

— 2,77 ± 0,03 mol/l solution, containing 10,0 ± 0,1 g of sodium hydroxide per 100 g of solution ($\rho_{20} = 1,108\ 9$ g/ml), equivalent to 110,9 ± 1,0 g of sodium hydroxide per litre.

NOTE — The sodium hydroxide solution may be conveniently prepared as follows:

Dissolve a quantity of solid sodium hydroxide in an equal mass of water and allow the suspended sodium carbonate to settle. Decant the supernatant liquid and dilute with carbon dioxide-free water to the appropriate concentration. Check by titration with standard acid solution.

5.2 Sulphuric acid, concentrated, not less than 94 % (*V/V*) ($\rho_{20} = 1,84$ g/ml).

NOTE — If the concentration of the sulphuric acid is less than 94 % (*V/V*), the temperature will not reach the 125 to 130 °C required during the oxidation.