

Australian/New Zealand Standard

Methods of test for pulp and paper

Method 452rp: Determination of weight factors by the comparison method



AS/NZS 1301.452rp:2006

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 8 December 2005 and on behalf of the Council of Standards New Zealand on 21 December 2005.

This Standard was published on 6 January 2006.

The following are represented on Committee PK-019:

Australian Plantation Products and Paper Industry Council (A3P)
Appita
CSIRO Forestry and Forest Products
Ensis Papro, SCION (New Zealand)
National Association of Forest Industries

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web page at www.standards.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 05396.

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

RECONFIRMATION
OF
AS/NZS 1301.452rp:2006
Methods of test for pulp and paper
Method 452rp: Determination of weight factors by the comparison method

RECONFIRMATION NOTICE

Technical Committee PK-019 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 10 May 2017.

Approved for reconfirmation in New Zealand on behalf of the Standards Council of New Zealand on 10 August 2017.

The following are represented on Technical Committee PK-019:

Appita
Monash University
New Zealand Paper Forum
Scion

NOTES

Currently in preview, click buy full vers.

Australian/New Zealand StandardTM

Methods of test for pulp and paper

Method 452rp: Determination of weight factors by the comparison method

Originated in Australia as AS 1301.452rp—1992.
Originated in New Zealand as NZS 1301.452rp:1992.
Jointly revised and designated as AS/NZS 1301.452rp:2006.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper to supersede AS 1301.452rp—1992. This Standard is identical with and reproduced from ISO 9184-7:1994, *Paper, board and pulps—Fibre furnish analysis, Part 7: Determination of weight factor*.

The objective of this Standard is to specify two methods for determining the weight factor of fibres used in the fibre furnish analysis of paper, board and pulp. In this Standard the weight factor is obtained either by a comparison method or by calculating from the fibre coarseness.

This Standard is applicable to all kinds of fibres of pulps from unmixed wood species. In this context, it means pulps which do not contain more than 5% of other fibres with an essentially different weight factor (see ISO 9184-1:1990, annex A).

The term ‘informative’ has been used in this Standard to define the application of the annex to which it applies. An ‘informative’ annex is only for information and guidance.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text ‘this part of ISO 9184’ should read ‘this Australian/New Zealand Standard’.
- (c) A full point should be substituted for a comma when referring to a decimal marker.

The references to International Standards should be replaced by references to the following Australian/New Zealand Standards.

<i>Reference to International Standard</i>		<i>Australian/New Zealand Standard</i>	
ISO		AS	
9184	Paper, board and pulps—Fibre furnish analysis	1301	Methods of test for pulp and paper
9184-1	Part 1: General method	1301.451rp	Part 451rp: Fibre furnish analysis
9184-2	Part 2: Staining guide	—	
9184-6	Part 6: Determination of fibre coarseness	—	

AUSTRALIAN/NEW ZEALAND STANDARD

Methods of test for pulp and paper**Method 452rp:****Determination of weight factors by the comparison method****1 Scope**

This part of ISO 9184 specifies two methods for determining the weight factor of fibres used in the fibre furnish analysis of paper, board and pulp. In this part of ISO 9184, the weight factor is obtained either by a comparison method or by calculating from the fibre coarseness.

This part of ISO 9184 is applicable to all kinds of fibres of pulps from unmixed wood species. In this context, it means pulps which do not contain more than 5 % of other fibres with an essentially different weight factor (see ISO 9184-1:1990, annex A).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 9184. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 9184 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO

maintain registers of currently valid International Standards.

ISO 9184-1:1990, *Paper, board and pulps — Fibre furnish analysis — Part 1: General method.*

ISO 9184-2:1990, *Paper, board and pulps — Fibre furnish analysis — Part 2: Staining guide.*

ISO 9184-6:1994, *Paper, board and pulps — Fibre furnish analysis — Part 6: Determination of fibre coarseness.*

3 Definition

For the purposes of this part of ISO 9184, the following definition applies.

3.1 weight factor: A specific dimensionless quantity for each kind of fibre. It is the ratio of the mass per unit length of a particular kind of fibre to that of a reference fibre with a mass per unit length of 0,180 mg/m.

NOTE 1 Originally rag (staple cotton) fibre was selected as the standard fibre with which all other fibres were compared. The weight factor or rag was taken as 1,00 and its average fibre coarseness was found to be 0,180 mg/m.¹⁾

1) The references cited in annex A may be useful in this respect.