

Australian/New Zealand Standard™

**Methods of test for pulp and paper—
Determination of colour by diffuse
reflectance**

**Method 530: Indoor daylight conditions
(C/2°)**



AS/NZS 1301.530:2016

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 6 December 2016 and by the New Zealand Standards Approval Board on 9 December 2016.
This Standard was published on 23 December 2016.

The following are represented on Committee PK-019:

Appita
Australian Forest Products Association
Monash University
New Zealand Paper Forum
Scion

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com or Standards New Zealand web site at www.standards.govt.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of Standards Australia or the New Zealand Standards Executive at the address shown on the back cover.

Australian/New Zealand Standard™

**Methods of test for pulp and paper—
Determination of colour by diffuse
reflectance**

**Method 530: Indoor daylight conditions
(C/2°)**

First published as AS/NZS 1301.530:2016.

COPYRIGHT

© ISO 2016 – All rights reserved

© Standards Australia Limited

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968.

Published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 978 1 76035 649 1

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper.

The objective of this Standard is to provide a method for determining the colour of paper and board by diffuse reflectance under indoor daylight conditions ($C/2^\circ$).

This Standard is identical with, and has been reproduced from ISO 5631-1:2015, *Paper and board—Determination of colour by diffuse reflectance—Part 1: Indoor daylight conditions ($C/2^\circ$)*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number appears on the cover and title page while the International Standard number appears only on the cover.
- (b) In the source text ‘this part of ISO 5631’ should read ‘this Australian/New Zealand Standard’.
- (c) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian/New Zealand Standard</i>	
ISO		AS/NZS	
186	Paper and board—Sampling to determine average quality	1301	Methods of test for pulp and paper
2469	Paper, board and pulps—Measurement of diffuse radiance factor (diffuse reflectance factor)	Method 414s:	Sampling to determine average quality
		Method 510:	Measurement of diffuse radiance factor (diffuse reflectance factor)

The reference ISO 187 has not been adopted as an Australian/New Zealand Standard.

In Australia and New Zealand the following Standards are generally used:

AS/NZS	
1301	Methods of test for pulp and paper
1301.414s:2006	Method 414s: Conditioning of paper for testing
1301.415s:2008	Method 415s: Standard atmosphere for testing paper and board and procedure for monitoring the atmosphere

Only normative references that have been adopted as Australian or Australian/New Zealand Standard have been listed.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annex to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

CONTENTS

1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	3
5	Apparatus	2
	5.1 Reflectometer.....	3
6	Sampling and conditioning	4
7	Preparation of test pieces	4
8	Procedure	4
9	Calculation	4
	9.1 CIE tristimulus values.....	4
	9.2 CIELAB coordinates.....	5
	9.3 Dispersion of the results.....	5
10	Expression of results	6
11	Precision	6
12	Test report	6
Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values		7
Bibliography		13

INTRODUCTION

The colour of an object can be uniquely characterized by means of a triplet of colour coordinates such as the CIE tristimulus values or the CIELAB 1976 L^* , a^* , b^* coordinates for a specified CIE illuminant and CIE standard observer.

Apart from the optical properties of the sample, the values of such coordinates depend upon the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 5631 should therefore be read in conjunction with ISO 2469.

This part of ISO 5631 describes the measurement and description of colour in terms of the CIE illuminant C and the CIE 1931 (2°) standard observer. The other parts of this International Standard describe measurements and calculations carried out in an analogous manner using either the CIE standard illuminant D65 and the CIE 1964 (10°) standard observer or the CIE illuminant D50 and the CIE 1931 (2°) standard observer.

The choice of illuminant conditions is important when determining the colour coordinates of white papers containing a fluorescent whitening agent. In ISO 5631-2, the UV content of the illumination is much higher, approximating UV levels encountered in outdoor viewing conditions.

ISO 5631-3 describes the measurement and description of colour in terms of the CIE illuminant D50 and the CIE 1931 (2°) standard observer. This method is especially applicable to graphic arts situations since these illuminant/observer conditions are used within the graphic arts industry.

AUSTRALIAN/NEW ZEALAND STANDARD

Methods of test for pulp and paper—Determination of colour by diffuse reflectance

Method 530:

Indoor daylight conditions (C/2°)

1 Scope

This part of ISO 5631 specifies a method for measuring the colour of paper and board by the diffuse reflectance method with the elimination of specular gloss.

This part of ISO 5631 is not applicable to coloured papers or boards which incorporate fluorescent dyes or pigments. It may be used to determine the colour of papers or boards which contain fluorescent whitening agents provided the UV content of the illumination on the test piece has been adjusted to conform to that in the CIE illuminant C, using a fluorescent reference standard that fulfils the requirements for international fluorescent reference standards of level 3 (CR3) as prescribed by ISO 2469 with an assigned ISO brightness value (C/2°) provided by an authorized laboratory, as described in ISO 2470-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ASTM E308, *Standard Practice for Computing the Colors of Objects by Using the CIE System*

CIE Publication 15:2004, *Colorimetry*, 3rd ed

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1**radiance factor** β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone, with its apex at the surface element, to that of the perfect reflecting diffuser under the same conditions of illumination

Note 1 to entry: For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_R , and the luminescent radiance factor, β_L , so that $\beta = \beta_R + \beta_L$.

For non-fluorescent materials, the reflected radiance factor, β_R , is numerically equal to the reflectance factor, R .