

Australian/New Zealand Standard

Occupational protective gloves

**Part 10.3: Protective gloves against
chemicals and micro-organisms—
Determination of resistance to
permeation by chemicals**

AS/NZS 2161.10.3:2005

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee SF-023, Occupational Protective Gloves. It was approved on behalf of the Council of Standards Australia on 9 March 2005 and on behalf of the Council of Standards New Zealand on 18 March 2005.

This Standard was published on 27 April 2005.

The following are represented on Committee SF-023:

Association of Accredited Certification Bodies
Australasian Fire Authorities Council
Australian Chamber of Commerce and Industry
Department of Consumer & Employment Protection, Worksafe Division (WA)
Griffith University
Telstra Corporation Limited
University of New South Wales
United Firefighters Union of Australia
University of Otago, New Zealand
University of Western Sydney

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.standards.com.au or Standards New Zealand website at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

RECONFIRMATION
OF
AS/NZS 2161.10.3:2005
Occupational protective gloves
Part 10.3: Protective gloves against chemicals and micro-organisms—
Determination of resistance to permeation by chemicals

RECONFIRMATION NOTICE

Technical Committee SF-023 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 16 June 2016.

Approved for reconfirmation in New Zealand on behalf of the Standards Council of New Zealand on 5 July 2016.

The following are represented on Technical Committee SF-023:

Australian Chamber of Commerce and Industry
Certification Interests (Australia)
Griffith University
National Safety Council of Australia
Safety Institute of Australia
University of Otago New Zealand
Worksafe New Zealand

NOTES

Currently in preview, click buy full vers.

Australian/New Zealand StandardTM

Occupational protective gloves

**Part 10.3: Protective gloves against
chemicals and micro-organisms—
Determination of resistance to
permeation by chemicals**

Originally as AS/NZS 2161.10.3:2002.
Second edition 2005.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 5420, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

ISBN 0 7337 6580 7

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee SF-023, Occupational Protective Gloves, to supersede AS/NZS 2161.10.3:2002.

The objective of this Standard is to provide users and manufacturers with a method for testing gloves to determine resistance to permeation by non-gaseous chemicals under conditions of continuous contact. The objective of this revision is to adopt the current edition of EN 374-3.

This Standard is identical with and has been reproduced from the European (CEN) Standard EN 374-3:2003, *Protective gloves against chemicals and micro-organisms, Part 3: Determination of resistance to permeation by chemicals*.

The Committee considered that the issue of recording uncertainty in measurement is not addressed in this Standard. Users are encouraged to refer to 'Guide to the Expression of Uncertainty in Measurement' issued by BIPM, IEC, IFCC, ISO, IUPAC, IUPAPA and OIML.

Guidance for the selection, care and use of occupational protective gloves is not covered by this Standard but is provided in AS/NZS 2161.1, *Occupational protective gloves, Part 1: Selection, use and maintenance*.

The Committee noted that there was no advice on the effect of different solvents on chemical permeation result or advice on mixtures of chemical and commonly-occurring pesticides may affect results. Such advice is intended to be included in the next version of AS/NZS 2161.1.

As this Standard is reproduced from a European Standard, the following applies:

- Its number appears on the cover and title page while the European Standard number appears only on the cover.
- In the source text 'this European Standard' should read 'this Australian/New Zealand Standard'.
- A full point substitutes for a comma when referring to a decimal marker.

References to international Standards should be replaced by equivalent Australian, New Zealand or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard or other publication</i>	<i>Joint Australian/New Zealand Standard</i>
EN 374 Protective gloves against chemicals and micro-organisms	AS/NZS 2161 Occupational protective gloves
374-1 Part 1: Terminology and performance requirements	2161.10.1 Part 10.1: Protective gloves against chemicals and micro-organisms—Terminology and performance requirements
ISO 4648 Rubber, vulcanised or thermoplastic—Determination of dimensions of test pieces and products for test purposes	—

This Standard is Part 10.3 of the following series:

AS/NZS

2161 Occupational protective gloves

2161.10.1 Part 10.1: Protective gloves against chemicals and micro-organisms—Terminology and performance requirements

2161.10.2 Part 10.2: Protective gloves against chemicals and micro-organisms—Determination of resistance to penetration

2161.10.3 Part 10.3 Protective gloves against chemicals and micro-organisms—Determination of resistance to permeation by chemicals

The term ‘informative’ has been used in this Standard to define the application of the annex to which it applies. An ‘informative’ annex is only for information and guidance.

CONTENTS

1	Scope.....	1
2	Normative references	1
3	Terms and definitions	1
4	Test principle	2
5	Collecting media	2
	5.1 General	2
	5.2 Gaseous collecting medium.....	2
	5.3 Liquid collecting medium	2
	5.4 Other collecting medium.....	2
6	Apparatus	2
	6.1 Permeation cell	2
	6.2 Temperature controlled room, cabinet or water bath	3
	6.3 Gas supply, e.g. dry air, nitrogen or helium (in case of a gaseous collecting medium)	3
	6.4 Liquid pump and stirrer (in case of a liquid collecting medium)	3
	6.5 Equipment for the quantitative determination of the test chemical or its components in the collecting medium	3
	6.6 Time measuring device.....	3
7	Test specimens.....	4
8	Procedure	4
	8.1 Calibration	4
	8.2 Preparation of test specimens and apparatus	4
	8.3 Test conditions.....	4
	8.4 Assessment of breakthrough time	4
	8.5 Test procedure for determination of the permeation rate	4
	8.6 Expression of results	6
9	Test report	6
	ANNEX ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives.....	8

AUSTRALIAN/NEW ZEALAND STANDARD

Occupational protective gloves

Part 10.3:

Protective gloves against chemicals and micro-organisms—Determination of resistance to permeation by chemicals

Introduction

A simple flow-through, two-compartment permeation cell, of standard dimensions, is used to measure quantitatively the permeation of chemicals through protective glove materials. Breakthrough time is measured and used as a measure of protection.

1 Scope

This European Standard specifies the determination of the resistance of protective glove materials to permeation by potentially hazardous non-gaseous chemicals under the condition of continuous contact.

It is emphasised that the test does not represent conditions likely to be found in practice, and the use of test data should be restricted to comparing materials chiefly on a relative basis in broad categories of breakthrough times.

2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate place in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references, the latest edition of the publication referred to applies (including amendments).

EN 374-1, *Protective gloves against chemicals and micro-organisms — Part 1: Terminology and performance requirements*.

ISO 4648, *Rubber, vulcanised or thermoplastic — Determination of dimensions of test pieces and products for test purposes*.

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions in EN 374-1 apply with the following terms and definitions:

3.1

collecting medium

a medium in which the test chemical is freely soluble to saturation mass or volume fraction greater than 0,5 %

3.2

delay time

time between actual arrival of the test chemical on the collecting side of the specimen and the time when the analytical instrumentation responds to it

3.3

permeation rate

the mass of test chemical permeating the glove per unit area per unit time (in $\mu\text{g cm}^{-2} \text{min}^{-1}$)

3.4

closed loop

breakthrough detection system in which the collecting medium is re-circulated through the sampling compartments of the test cell. Closed loop systems are not used with gaseous collection media