

Australian/New Zealand Standard™

Methods of testing portland, blended and masonry cements

Method 18: Determination of water retention of masonry cement

AS/NZS 2350.18:2006

1 SCOPE

This Standard sets out the method for determining the water retention of a masonry cement prepared and tested as a standard mortar.

NOTES:

- 1 The testing procedure herein may involve the use of materials or equipment that require safety measures to be observed.
- 2 This Standard does not purport to address all of the safety concerns, if any, associated with its use.
- 3 The user of this Standard should establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS/NZS

- 2350 Methods of testing of portland, blended and masonry cements
2350.1 Method 1: Sampling
2350.3 Method 3: Normal consistency

ASTM

- C230 Standard Specification for Flow Table for Use in Tests of Hydraulic Cement
C778 Standard Specification for Standard Sand

3 PRINCIPLE

A standard mortar is prepared by mechanically mixing 1 part masonry cement to 3 parts standard sand, by volume, with sufficient water to achieve a standard consistency as measured by the flow table. The standard fresh mortar is subjected to a vacuum and its ability to retain water is calculated from its change in consistency as measured by the flow table.

4 APPARATUS AND RELATED CONDITIONS

4.1 Laboratory

The air within the laboratory in which the specimens are made and tested shall be maintained at a temperature of $23 \pm 2^\circ\text{C}$ and a relative humidity of not less than 50%.

4.2 Balance

The balance shall have a capacity appropriate to the mass required and shall be capable of weighing to the nearest 1 g.