

Australian/New Zealand Standard™

Paints for steel structures

**Part 11: Chlorinated rubber—High-build
and gloss**



AS/NZS 3750.11:2009

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee CH-003, Paints and Related Materials. It was approved on behalf of the Council of Standards Australia on 16 March 2009 and on behalf of the Council of Standards New Zealand on 27 March 2009.
This Standard was published on 20 April 2009.

The following are represented on Committee CH-003:

AUSTROADS

Australasian Corrosion Association
Australian Paint Approval Scheme
Australian Paint Manufacturers' Federation
Australian Pipeline Industry Association
Business New Zealand
Engineers Australia
Institution of Professional Engineers New Zealand
Master Painters Australia
Master Painters New Zealand Association
National Association of Testing Authorities Australia
Water Corporation Western Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.standards.com.au or Standards New Zealand website at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 06351.

Australian/New Zealand Standard™

Paints for steel structures

**Part 11: Chlorinated rubber—High-build
and gloss**

Originally in Australia as AS 2672—1983.
Previous edition AS/NZS 3750.11:1996.
Second edition 2009.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

ISBN 0 7337 9124 7

PREFACE

This Standard was prepared by the Joint Australia/New Zealand Standards Committee CH-003, Paints and Related Materials to supersede AS/NZS 3750.11:1996. It is part of a series of product Standards for paints referred to in AS/NZS 2312, *Guide to the protection of structural steel against atmospheric corrosion by the use of protective coatings*.

The objective of this Standard is to revise the 1996 edition by taking account of revisions to Standards such as AS/NZS 2312 and the AS/NZS 1580 series of test methods.

The following Standards in this series have been published:

AS

- 2364 Paints for steel structures—High build epoxy (two-pack)
- 2672 Paints for steel structures—Chlorinated rubber, high build
- 2673 Paints for steel structures—alkyd/micaceous iron oxide
- 2674 Paints for steel structures—Epoxy primer (two-pack)
- 3750 Paints for steel structures
- 3750.1 Part 1: Epoxy mastic (two-pack)—For rusted steel
- 3750.2 Part 2: Ultra high-build paint
- 3884 Etch primers (single pack and two-pack) for preparing metal surfaces
- 3885 Paints for steel structures—Galvanized and zinc primed—Latex
- 3887 Paints for steel structures—Coal tar epoxy (two-pack)

AS/NZS

- Paints for steel structures
- 3750.3 Part 3: Heat-resisting—Exterior
- 3750.4 Part 4: Bitumen paint
- 3750.5 Part 5: Acrylic full gloss (two-pack)
- 3750.6 Part 6: Full gloss polyurethane (two-pack)
- 3750.7 Part 7: Aluminium paint
- 3750.8 Part 8: Vinyl paints—Primer, high-build and gloss
- 3750.9 Part 9: Organic zinc-rich primer
- 3750.10 Part 10: Full gloss epoxy (two-pack)
- 3750.11 Part 11: Chlorinated rubber—High-build and glass (this Standard)
- 3750.12 Part 12: Alkyd/micaceous iron oxide
- 3750.13 Part 13: Epoxy primer (two-pack)
- 3750.14 Part 14: High-build epoxy (two-pack)
- 3750.15 Part 15: Inorganic zinc silicate paint
- 3750.16 Part 16: Waterborne primer and paint for galvanized, zinc/aluminium alloy-coated and zinc-primed steel
- 3750.17 Part 17: Etch primers (single pack and two-pack)
- 3750.18 Part 18: Moisture cure urethane (single-pack) systems
- 3750.19 Part 19: Metal primer—General purpose
- 3750.20 Part 20: Anticorrosive metal primer—Solvent-borne—Lead and chromate free
- 3750.21 Part 21: Undercoat—Solvent-borne
- 3750.22 Part 22: Full gloss enamel—Solvent-borne
- 3750.23 Part 23: Semi-gloss enamel—Solvent-borne

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 REFERENCED DOCUMENTS	4
1.3 DEFINITIONS	4
1.4 SAFETY PRECAUTIONS	5
SECTION 2 MATERIAL REQUIREMENTS	
2.1 GENERAL	6
2.2 COMPOSITION	6
2.3 CONDITIONS OF TEST	6
2.4 LIQUID PAINT	6
2.5 APPLICATION PROPERTIES	7
2.6 APPLIED FILM	7
SECTION 3 PACKAGING AND LABELLING	
3.1 PACKAGING	10
3.2 LABELLING	10
APPENDICES	
A PURCHASING GUIDELINES	11
B GUIDANCE ON THE USE AND APPLICATION OF CHLORINATED RUBBER PAINT	12
C REFERENCED DOCUMENTS	14
D PREPARATION OF TEST PANELS	16
E ASSESSMENT OF RESISTANCE OF CHLORINATED RUBBER PAINT TO DISTILLED WATER	17

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

**Australian/New Zealand Standard
Paints for steel structures****Part 11: Chlorinated rubber—High-build and gloss**

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard specifies requirements for a high-build, chlorinated rubber based, intermediate or topcoat paint and a chlorinated rubber gloss finish paint for the protection of structural steel against exterior atmospheric corrosion in an industrial or marine environment. The high-build paints are suitable for application only by conventional air or airless spraying, while the gloss paint is suitable for application by brush or spray. Paints specified in this Standard are described in AS/NZS 2312 as Paint References C14 and C25.

Chlorinated rubber paints have very good resistance to most acids and alkali solutions but their high solvent/binder ratio have OHS and environmental implications that limit their suitability.

These paints are intended for use in paint systems for the protection of iron and steel against corrosion involving wet and damp areas, high humidity, marine and industrial fallout.

NOTES:

- 1 These paints may be used as detailed for systems CLR2, CLR3 and HDG600P4 in AS/NZS 2312.
- 2 Appendix A contains recommendations and advice on information that should be provided by the purchaser at the time of enquiry or order.
- 3 Additional information on the use and application of chlorinated rubber paints is contained in Appendix B.
- 4 These paints are available in a range of colours.
- 5 The high-build paint is available pigmented with micaceous iron oxide (MIO).

1.2 REFERENCED DOCUMENTS

A list of the documents referred to in this Standard is contained in Appendix C.

1.3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS/NZS 2310 and the following apply.

1.3.1 Chlorinated rubber resin

A material consisting of natural or synthetic rubber reacted with chlorine to give a product having a nominal chlorine content of 65% by mass.

1.3.2 Type 1

A high-build conventionally pigmented chlorinated rubber paint.