

Australian/New Zealand Standard™

**Heat-treated steel tapping screws—
Mechanical properties**



AS/NZS 4412:2015

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee ME-029, Fasteners. It was approved on behalf of the Council of Standards Australia on 24 July 2015 and on behalf of the Council of Standards New Zealand on 24 July 2015.

This Standard was published on 26 August 2015.

The following are represented on Committee ME-029:

Association of Accredited Certification Bodies
Association of Wall and Ceiling Industries of Australia and New Zealand
Australasian Corrosion Association
Australian Chamber of Commerce and Industry
Australian Engineered Fasteners and Anchors Council
Australian Industry Group
Australian Steel Institute
Australian Technical Infrastructure Committee
Austroads
Bureau of Steel Manufacturers of Australia
CSIRO
Employers and Manufacturers Association
Galvanizers Association of Australia
Materials Australia
National Association of Steel-Framed Housing
National Association of Testing Authorities Australia
New Zealand Heavy Engineering Research Association
Society of Automotive Engineers—Australasia
Steel Construction New Zealand
Swinburne University of Technology

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the online catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR AS/NZS 4412:2015.

Australian/New Zealand Standard™

**Heat-treated steel tapping screws—
Mechanical properties**

Originally as AS/NZS 4412:1996.
Second edition 2015.

COPYRIGHT

© Standards Australia Limited/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, Private Bag 2439, Wellington 6140.

ISBN 978 1 76035 218 9

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee ME-029, Fasteners, to supersede AS/NZS 4412:1996.

The objective of this Standard is to ensure that tapping screws will form mating threads in materials into which they are normally driven without deforming their own thread and without breaking during assembly or service.

This Standard is identical with, and has been reproduced from, ISO 2702:2011, *Heat-treated steel tapping screws—Mechanical properties*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text ‘this International Standard’ should read ‘this Australian/New Zealand Standard’.
- (b) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian Standard</i>
ISO 898 Mechanical properties of fasteners	AS 4291 Mechanical properties of fasteners made of carbon steel and alloy steel
ISO 898-7 Part 7: Torsional test and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm	AS 4291.7 Part 7: Torsional test and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm

Only normative references that have been adopted as Australian or Australian/New Zealand Standards have been listed.

AUSTRALIAN/NEW ZEALAND STANDARD

Heat-treated steel tapping screws—Mechanical properties**1 Scope**

This International Standard specifies the characteristics of heat-treated steel tapping screws, with tapping screw thread from ST2,2 to ST9,5 inclusive according to ISO 1478, together with the corresponding test methods.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 898-7:1992, *Mechanical properties of fasteners — Part 7: Torsional tensile and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

3 Materials

Tapping screws shall be made from cold heading, case hardening quality steel.

4 Requirements**4.1 Metallurgical requirements****4.1.1 Surface hardness**

The minimum surface hardness after heat treatment shall be 450 HV 0,3 (see ISO 6507-1).

4.1.2 Case depth

The case depth shall conform to the values given in Table 1.

Table 1 — Case depth

Dimensions in millimetres

Thread	Case depth	
	min.	max.
ST2,2, ST2,6	0,04	0,10
ST2,9, ST3,3, ST3,5	0,05	0,18
ST3,9, ST4,2, ST4,8, ST5,5	0,10	0,23
ST6,3, ST8, ST9,5	0,15	0,28