

AS/NZS IEC 60840:2020
IEC 60840:2020

STANDARDS®
NEW ZEALAND
PAEREWĀ AOTEAROA



STANDARDS
Australia



Australian/New Zealand Standard™

Power cables with extruded insulation and their accessories for rated voltages above 30 kV ($U_m = 36$ kV) up to 150 kV ($U_m = 170$ kV) — Test methods and requirements



currently in review, click to buy full version

AS/NZS IEC 60840:2020

This Joint Australian/New Zealand Standard™ was prepared by Joint Technical Committee EL-003, Electric Wires And Cables. It was approved on behalf of the Council of Standards Australia on 9 September 2020 and by the New Zealand Standards Approval Board on 2 September 2020.

This Standard was published on 23 October 2020.

The following are represented on Committee EL-003:

- Australian Cablemakers Association
- Australian Industry Group
- Aviation and Marine Engineers Association
- Electrical Compliance Testing Association of Australia
- Electrical Regulatory Authorities Council, Australia
- Engineers Australia
- Institute of Electrical Inspectors, Australia
- Master Electricians, New Zealand
- National Electrical and Communications Association, Australia
- Queensland University of Technology
- WorkSafe New Zealand

This Standard was issued in draft form for comment as DR AS/NZS IEC 60840:2020.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

www.standards.govt.nz

ISBN 978 1 76113 009 0

Australian/New Zealand Standard™

Power cables with extruded insulation and their accessories for rated voltages above 30 kV ($U_n = 36$ kV) up to 150 kV ($U_n = 170$ kV) — Test methods and requirements

First published as AS/NZS 60840:2006.
Jointly revised and redesignated as AS/NZS IEC 60840:2020.



© IEC 2020 — All rights reserved
© Standards Australia Limited/the Crown in right of New Zealand, administered by the New Zealand Standards Executive 2020

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of either the IEC or the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth) or the Copyright Act 1994 (New Zealand). If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please see the contact details on the back cover or the contact us page of the website for further information.

Preface

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee EL-003, Electric Wires and Cables, to supersede AS/NZS 60840—2006, *Power cables with extruded insulation and their accessories for rated voltages above 30 kV ($U_m = 36$ kV) up to 150 kV ($U_m = 170$ kV) — Test methods and requirements*.

The objective of this document is to specify test methods and requirements for power cable systems, cables alone and accessories alone, for fixed installations and for rated voltages above 30 kV ($U_m = 36$ kV) up to and including 150 kV ($U_m = 170$ kV).

The requirements apply to single-core cables and to individually screened three-core cables and to their accessories for usual conditions of installation and operation, but not to special cables and their accessories, such as submarine cables and their accessories, for which modifications to the standard tests or the setup of special test conditions can be necessary.

This document does not cover transition joints between cables with extruded insulation and paper insulated cables.

This document is identical with, and has been reproduced from, IEC 60840:2020, *Power cables with extruded insulation and their accessories for rated voltages above 30 kV ($U_m = 36$ kV) up to 150 kV ($U_m = 170$ kV) — Test methods and requirements*.

As this document has been reproduced from an International Standard, a full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

NOTES

Currently in preview, click buy full version

CONTENTS

FOREWORD	8
INTRODUCTION	10
1 Scope	11
2 Normative references	11
3 Terms and definitions	13
3.1 Definitions of dimensional values (thicknesses, cross-sections, etc.)	13
3.2 Definitions concerning tests	13
3.3 Other definitions	14
4 Voltage designations, materials and rounding of numbers	15
4.1 Rated voltages	15
4.2 Cable insulating compounds	15
4.3 Cable metal screens/sheaths	15
4.4 Cable oversheathing compounds	16
4.5 Rounding of numbers	16
5 Precautions against water penetration in cables	16
6 Cable characteristics	17
7 Accessories characteristics	18
7.1 Gas immersed cable terminations	18
7.2 Composite insulators for outdoor cable terminations	18
7.3 Accessory characteristics to be declared	18
8 Test conditions	19
8.1 Ambient temperature	19
8.2 High voltage tests	19
8.3 Waveform of lightning impulse test voltages	19
8.4 Relationship of test voltage to rated voltages	19
8.5 Determination of the cable conductor temperature	19
9 Routine tests on cables and accessories	19
9.1 General	19
9.2 Partial discharge test	20
9.3 Voltage test	20
9.4 Electrical test on oversheath of the cable	21
10 Sample tests on cables	21
10.1 General	21
10.2 Frequency of tests	21
10.3 Repetition of tests	21
10.4 Conductor examination	21
10.5 Measurement of electrical resistance of conductor and metal screen	22
10.6 Measurement of thickness of cable insulation and oversheath	22
10.6.1 General	22
10.6.2 Requirements for the insulation	22
10.6.3 Requirements for the cable oversheath	23
10.7 Measurement of thickness of metal sheath	23
10.7.1 General	23
10.7.2 Lead or lead alloy sheath	23
10.7.3 Copper or aluminium sheath	24

10.7.4	Metal tape for CD design	24
10.8	Measurement of diameters	24
10.9	Hot set test for XLPE, EPR and HEPR insulations	24
10.9.1	Procedure	24
10.9.2	Requirements	24
10.10	Measurement of capacitance	25
10.11	Measurement of density of HDPE insulation	25
10.11.1	Procedure	25
10.11.2	Requirements	25
10.12	Lightning impulse voltage test	25
10.13	Water penetration test	25
10.14	Additional tests on components of cables with a longitudinally applied metal tape or foil, bonded to the oversheath	25
11	Sample tests on accessories	26
11.1	Tests on components of accessory	26
11.2	Tests on complete accessory	26
12	Type tests on cable systems	26
12.1	General	26
12.2	Range of type approval	27
12.3	Summary of type tests	28
12.4	Electrical type tests on cable systems	28
12.4.1	Test voltage values	28
12.4.2	Tests and sequence of tests	29
12.4.3	Bending test	29
12.4.4	Partial discharge tests	30
12.4.5	Tan δ measurement	30
12.4.6	Heating cycle voltage test	30
12.4.7	Lightning impulse voltage test followed by a power frequency voltage test	31
12.4.8	Examination	31
12.4.9	Resistivity of semi-conducting screens	32
12.5	Non-electrical type tests on cable components and on complete cable	32
12.5.1	General	32
12.5.2	Check on cable construction	33
12.5.3	Tests for determining the mechanical properties of insulation before and after ageing	33
12.5.4	Tests for determining the mechanical properties of oversheaths before and after ageing	33
12.5.5	Ageing tests on pieces of complete cable to check compatibility of materials	34
12.5.6	Loss of mass test on PVC oversheaths of type ST ₂	34
12.5.7	Pressure test at high temperature on oversheaths	34
12.5.8	Test on PVC oversheaths (ST ₁ , ST ₂) and LSHF oversheaths (ST ₁₂) at low temperature	35
12.5.9	Heat shock test for PVC oversheaths (ST ₁ and ST ₂)	35
12.5.10	Ozone resistance test for EPR and HEPR insulations	35
12.5.11	Hot set test for EPR, HEPR and XLPE insulations	35
12.5.12	Measurement of density of HDPE insulation	35

12.5.13	Measurement of carbon black content of black PE oversheaths (ST ₃ and ST ₇)	36
12.5.14	Test under fire conditions	36
12.5.15	Water penetration test	37
12.5.16	Tests on components of cables with a longitudinally applied metal tape or foil, bonded to the oversheath	37
12.5.17	Shrinkage test for PE, HDPE and XLPE insulations	37
12.5.18	Shrinkage test for PE oversheaths (ST ₃ , ST ₇) and LSHF oversheaths (ST ₁₂)	37
12.5.19	Determination of hardness of HEPR insulation	38
12.5.20	Determination of the elastic modulus of HEPR insulation	38
13	Prequalification test of the cable system	38
13.1	General and range of prequalification test approval	38
13.2	Prequalification test on complete system	39
13.2.1	Summary of prequalification tests	39
13.2.2	Test voltage values	39
13.2.3	Test arrangement	39
13.2.4	Heating cycle voltage test	40
13.2.5	Lightning impulse voltage test	41
13.2.6	Examination	41
13.3	Tests for the extension of the prequalification of a cable system	41
13.3.1	Summary of the extension of prequalification test	41
13.3.2	Electrical part of the extension of prequalification tests on complete cable system	41
14	Type tests on cables	43
14.1	General	43
14.2	Range of type approval	44
14.3	Summary of type tests	44
14.4	Electrical type tests on completed cables	45
15	Type tests on accessories	45
15.1	General	45
15.2	Range of type approval	45
15.3	Summary of type tests	46
15.4	Electrical type tests on accessories	47
15.4.1	Test voltage values	47
15.4.2	Tests and sequence of tests	47
16	Electrical tests after installation	47
16.1	General	47
16.2	DC voltage test of the oversheath	47
16.3	AC voltage test of the insulation	47
Annex A (informative)	Determination of the cable conductor temperature	55
A.1	Purpose	55
A.2	Calibration of the temperature of the main test loop	55
A.2.1	General	55
A.2.2	Installation of cable and temperature sensors	55
A.2.3	Calibration method	57
A.3	Heating for the test	57
A.3.1	Method 1 – Test using a reference cable	57

A.3.2	Method 2 – Test using conductor temperature calculations and measurement of the surface temperature.....	58
Annex B	(normative) Rounding of numbers.....	59
Annex C	(informative) List of type, prequalification and extension of prequalification tests for cable systems, cables and accessories.....	60
Annex D	(normative) Method of measuring resistivity of semi-conducting screens.....	62
Annex E	(normative) Water penetration test.....	65
E.1	Test piece.....	65
E.2	Test.....	65
E.3	Requirements.....	66
Annex F	(normative) Test for water penetration in the conductor.....	67
F.1	Test piece.....	67
F.2	Test.....	67
F.3	Requirements.....	67
Annex G	(normative) Tests on components of cables with a longitudinally applied metal tape or foil, bonded to the oversheath.....	69
G.1	Visual examination.....	69
G.2	Adhesion and peel strength.....	69
G.2.1	General.....	69
G.2.2	Test: Adhesion strength.....	69
G.2.3	Test: Peel strength of overlapped metal foil.....	70
G.2.4	Requirements.....	71
Annex H	(normative) Additional tests for accessories.....	73
H.1	General.....	73
H.2	Range of approval.....	74
H.2.1	Range of approval for joints without screen or metal sheath interruption.....	74
H.2.2	Range of approval for joints with screen or metal sheath interruption.....	74
H.2.3	Range of approval for accessories for cable screen interruption and/or earth connection.....	74
H.2.4	Range of approval for terminations with sectionalizing insulation.....	75
H.3	Tests of joints with or without screen or metal sheath interruption and accessories for cable screen interruption and/or earth connection.....	75
H.3.1	Water immersion.....	75
H.3.2	Electrical tests.....	75
H.4	Tests of terminations with sheath sectionalizing insulation.....	77
H.4.1	DC voltage withstand test between screen and earth.....	77
H.4.2	Lightning impulse voltage withstand test between screen and earth.....	77
H.5	Examination.....	77
H.6	Tests for composite insulators for outdoor terminations.....	78
H.6.1	General.....	78
H.6.2	Internal pressure test.....	78
H.6.3	Cantilever load test.....	78
Annex I	(normative) Determination of hardness of HEPR insulations.....	79
I.1	Test piece.....	79
I.2	Test procedure.....	79
I.2.1	General.....	79
I.2.2	Surfaces of large radius of curvature.....	79
I.2.3	Surfaces of small radius of curvature.....	79
I.2.4	Conditioning and test temperature.....	79

1.2.5	Number of measurements.....	80
Annex J (informative)	Guidance on examination of cable and accessories	81
Annex K (normative)	Methods of determining the weighted value of the cable for measurement of halogen content	82
K.1	Calculating the weighted value of the cable when the halogen content of individual materials is tested	82
K.2	Preparation of the test sample for measurement of halogen content on a sample representative of the cable construction.....	82
Bibliography	83
Figure 1	– Example of the test arrangement for the prequalification test	40
Figure 2	– Example of extension of prequalification test arrangement for the prequalification of a system with another joint, designed for rigid as well as flexible installation	42
Figure A.1	– Typical test set-up for the reference loop and the main test loop.....	56
Figure A.2	– Example of an arrangement of the temperature sensors on the conductor of the reference loop.....	57
Figure D.1	– Preparation of samples for measurement of resistivity of conductor and insulation screens.....	64
Figure E.1	– Schematic diagram of apparatus for water penetration test.....	66
Figure F.1	– Schematic diagram of apparatus for water penetration test in the conductor.....	68
Figure G.1	– Adhesion of metal tape or foil	70
Figure G.2	– Example of overlapped metal foil.....	71
Figure G.3	– Peel strength of overlapped metal foil.....	71
Figure G.4	– Typical strength versus grip spacing curve (1).....	72
Figure G.5	– Typical strength versus grip spacing curve (2).....	72
Figure I.1	– Test on surfaces of large radius of curvature.....	80
Figure I.2	– Test on surfaces of small radius of curvature	80
Table 1	– Insulating compound for cables	48
Table 2	– Oversheathing compounds for cables.....	48
Table 3	– Tan δ requirements for insulating compounds for cables.....	48
Table 4	– Test voltages	49
Table 5	– Non-electrical type tests for insulating and oversheathing compounds for cables.....	49
Table 6	– Test requirements for mechanical characteristics of insulating compounds for cables (before and after ageing)	50
Table 7	– Test requirements for mechanical characteristics of oversheathing compounds for cables (before and after ageing)	51
Table 8	– Test requirements for particular characteristics of insulating compounds for cables.....	52
Table 9	– Test requirements for particular characteristics of PVC and LSHF oversheathing for cables.....	53
Table 10	– Maximum mechanical load for composite insulators for outdoor terminations.....	54
Table C.1	– Type tests on cable systems, on cables and on accessories	60

Table C.2 – Prequalification tests on cable systems with a calculated nominal conductor electric stress above 8,0 kV/mm or a calculated nominal insulation electric stress above 4,0 kV/mm.....	61
Table C.3 – Extension of prequalification tests on cable systems with a calculated nominal conductor electric stress above 8,0 kV/mm or a calculated nominal insulation electric stress above 4,0 kV/mm	61
Table G.1 – Minimum acceptable adhesion or peel strength forces	72
Table H.1 – Test sequence	73
Table H.2 – Lightning impulse voltage withstand test between screen and earth of joints with or without screen or metal sheath interruption and accessories for cable screen interruption and/or earth connection	76
Table H.3 – Lightning impulse voltage withstand test between screen and screen of joints with screen or metal sheath interruption and accessories for cable screen interruption and/or earth connection.....	77
Table H.4 – Lightning impulse voltage withstand tests between screen and earth of terminations with sheath sectionalizing insulation	77

INTERNATIONAL ELECTROTECHNICAL COMMISSION

POWER CABLES WITH EXTRUDED INSULATION AND THEIR ACCESSORIES FOR RATED VOLTAGES ABOVE 30 kV ($U_m = 36$ kV) UP TO 150 kV ($U_m = 170$ kV) – TEST METHODS AND REQUIREMENTS

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60840 has been prepared by IEC technical committee 20: Electric cables.

This fifth edition cancels and replaces the fourth edition, published in 2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- Gas immersed cable terminations for use at rated voltages above 52 kV are required to be designed, type and routine tested in accordance with IEC 62271-209 in addition to the routine and type tests specified in this document.
- Requirements are introduced for composite outdoor termination insulators.
- The test cylinder diameters specified for the bending test (type and prequalification tests) have been modified in line with IEC TR 61901:2016.
- A low smoke halogen free oversheath material, designated ST₁₂ is introduced.

- Additional tests under fire conditions are introduced: vertical flame spread, smoke density, acidity and conductivity, which shall be applied according to the fire performance declared for the cable.
- A test for water penetration in the conductor is added.
- In addition to tests on the outer protection of joints, type tests on the screen sectionalizing insulation of all accessories have been introduced.

NOTE For a more detailed history of events leading up to this fifth edition, see the Introduction.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
20/1909/FDIS	20/1910/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

The first edition of IEC 60840, published in 1988, dealt only with cables. Accessories were added to the second edition, published in February 1999, which separately covered test methods and test requirements for

- a) cables alone,
- b) cables together with accessories (a cable system).

Some countries then suggested that a better discrimination be made between systems, cables and accessories, particularly for the lower voltages of the scope, for example 45 kV. This was taken into account in the third edition (2004) and has been retained subsequently, giving the type approval requirements and the range of approvals for:

- a) cable systems,
- b) cables alone,
- c) accessories alone.

Manufacturers and users may choose the most appropriate option for type approval.

The fourth edition (2011) introduced the prequalification test procedure, as a cable system inclusive of accessories, for cables with high electrical stresses at the conductor screen and/or insulation screen.

Other significant changes in the fourth edition were:

- a) The clause numbering of this document and IEC 62067 was coordinated to achieve as much commonality as possible.
- b) In the case of the sample test, the lightning impulse voltage test is no longer followed by a power frequency voltage test.

In this fifth edition the principle changes are as follows:

- a) New definitions have been added for three different cable screen designs following IEC TR 61901:2016.
- b) Gas immersed cable terminations for use at rated voltages above 52 kV are required to be designed, type and routine tested in accordance with IEC 62271-209 in addition to the routine and type tests specified in this document.
- c) Requirements are introduced for composite outdoor termination insulators.
- d) The test cylinder diameters specified for the bending test (type and prequalification tests) have been modified in line with IEC TR 61901:2016.
- e) A low smoke halogen free oversheath material, designated ST₁₂ is introduced.
- f) Additional tests under fire conditions are introduced: vertical flame spread, smoke density, acidity and conductivity, which are applied according to the fire performance declared for the cable.
- g) A test for water penetration in the conductor is added.
- h) In addition to tests on the outer protection of joints, type tests on the screen sectionalizing insulation of all accessories have been introduced.
- i) A list of relevant CIGRE references is given in the bibliography.

POWER CABLES WITH EXTRUDED INSULATION AND THEIR ACCESSORIES FOR RATED VOLTAGES ABOVE 30 kV ($U_m = 36$ kV) UP TO 150 kV ($U_m = 170$ kV) – TEST METHODS AND REQUIREMENTS

1 Scope

This document specifies test methods and requirements for power cable systems, cables alone and accessories alone, for fixed installations and for rated voltages above 30 kV ($U_m = 36$ kV) up to and including 150 kV ($U_m = 170$ kV).

The requirements apply to single-core cables and to individually screened three-core cables and to their accessories for usual conditions of installation and operation, but not to special cables, such as submarine cables and their accessories, for which modifications to the standard tests or the setup of special test conditions can be necessary.

This document does not cover transition joints between cables with extruded insulation and paper insulated cables.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60060-1:2010, *High-voltage test techniques – Part 1: General definitions and test requirements*

IEC 60228, *Conductors of insulated cables*

IEC 60229:2007, *Electric cables – Tests on extruded oversheaths with a special protective function*

IEC 60230, *Impulse tests on cables and their accessories*

IEC 60287-1-1:2006, *Electric cables – Calculation of the current rating – Part 1-1: Current rating equations (100 % load factor) and calculation of losses – General*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-24, *Tests on electric and optical fibre cables under fire conditions – Part 3-24: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category C*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60811-201, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness*