

ANSI/AWWA

C203-20

(Revision of ANSI/AWWA C203-15)

AWWA Standard

Coal-Tar Protective Coatings and Linings for Steel Water Pipe

Effective date: April 1, 2021.

First edition approved by Board of Directors April 25, 1940.

15th edition approved October 26, 2020.

Approved by American National Standards Institute October 8, 2020.



American Water Works
Association




AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags and labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900, or emailing info@ansi.org.



ISBN-13, print: 978-1-64717-051-7

ISBN-13, electronic: 978-1-61300-576-7

DOI: <http://dx.doi.org/10.12999/AWWA.C203.20>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Copyright © 2021 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe Manufacturer's Technical Advisory Committee (SWPMTAC) Task Group for ANSI/AWWA C203, which updated this standard, had the following personnel at the time:

Chris Smith, *Chair*

Jim Harvey, *Vice Chair*

J. Harvey, Mobile Pipe Lining and Coating, Adelanto, Calif.

B.D. Keil, Northwest Pipe Company, Draper, Utah

D. Libby, Chase Corporation, Westwood, Mass.

L. McKinney, Womble Company Inc., Houston, Tex.

C. Smith, Lone Star Specialty Products, Lone Star, Tex.

J. Buratto, LifeLast, Inc., Pflugerville, Tex.

The Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*

Bob J. Card, *Vice Chair*

John L. Luka, *Secretary*

General Interest Members

S.A. Arnaout, (*alternate*), Stantec, Dallas, Tex.

J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.

R.J. Card, Lockwood, Andrews & Newnam Inc., Houston, Tex.

R.L. Coffey, HDR Engineering Inc., Omaha, Neb.

M. Garcia, (*liaison non-voting*), Standards Council Liaison, AECOM, Denver, Colo.

R.L. Gibson, Freese and Nichols Inc., Fort Worth, Tex.

M.D. Gossert, (*alternate*), HDR Engineering, Inc., Denver, Colo.

M.B. Horsley, (*alternate*), Horsley Engineering LLC, Overland Park, Kans.

R. Josa, AECOM, McKinney, Tex.

C.M. Kirby, (*alternate*), Lockwood, Andrews & Newnam Inc., Houston, Tex.

K.A. Kufaas, Norske Corrosion & Inspection Services Ltd., Surrey, B.C., Canada

J.L. Mattson, Corrosion Control Technologies, Sandy, Utah

A. Murdock, Jacobs Engineering, Salt Lake City, Utah

R. Ortega, Lockwood, Andrews & Newman, Houston, Tex.

E.S. Ralph, (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
A.E. Romer, (*alternate*), AECOM, Orange, Calif.
J.R. Snow, Stantec, Denver, Colo.
A.M. Stanton, Black & Veatch, Los Angeles, Calif.
W.R. Whidden, Woolpert, Winter Park, Fla.

Producer Members

H.H. Bardakjian, Consultant, Glendale, Calif.
D. Dechant, Dechant Infrastructure Services, Aurora, Colo.
D.W. Dunker, Thompson Pipe Group, Grand Prairie, Tex.
W.B. Geyer, Steel Plate Fabricators Association, Lake Zurich, Ill.
B.D. Keil, Northwest Pipe Company, Draper, Utah
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.
R.D. Mielke, (*alternate*), Northwest Pipe Company, Raleigh, N.C.
G.F. Ruchti, (*alternate*), Consultant, Punta Gorda, Fla.
B.P. Simpson, (*alternate*), American Cast Iron Pipe Company, Birmingham, Ala.
C.C. Sundberg, Victaulic, Issaquah, Wash.
R. Wu, (*alternate*), Thompson Pipe Group, Grand Prairie, Tex.

User Members

L. Adams, US Bureau of Reclamation, Denver, Colo.
G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.
B. Cheng, Metro Vancouver, Burnaby, B.C., Canada
B. Fountain, San Diego County Water Authority, San Diego, Calif.
J. Garcia, (*alternate*), Metropolitan Water District of Southern California, Los Angeles, Calif.
S. Hattan, Tarrant Regional Water District, Fort Worth, Tex.
M. Lobik, Springfield Water & Sewer Commission, Springfield, Mass.
T. Peng, Metropolitan Water District of Southern California, Los Angeles, Calif.
M. Turney, (*alternate*), Denver Water, Denver, Colo.
V. Scudlarcu, Los Angeles Department of Water and Power, Los Angeles, Calif.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.3	Materials for Hot Coal-Tar Enamel Systems 5
I	Introduction..... vii	4.4	Application of Hot Coal-Tar Enamel Systems..... 10
I.A	Background..... vii	4.5	Application to Special Connectors and Appurtenances, Internal and External..... 20
I.B	History..... vii	4.6	Materials for Hot Coal-Tar Tape Systems..... 21
I.C	Acceptance vii	4.7	Additional Exterior Protection..... 24
II	Special Issues viii	4.8	Field Procedures 26
II.A	Advisory Information on Product Application viii	5 Verification	
III	Use of This Standard ix	5.1	Materials Inspection and Rejection 26
III.A	Purchaser Options and Alternatives ix	5.2	Electrical Inspection 27
III.B	Modification to Standard x	5.3	Thickness Testing..... 30
IV	Major Revisions..... x	5.4	Test Procedures..... 30
V	Comments x	6 Delivery	
Standard		6.1	Marking 43
1 General		6.2	Packaging and Shipping 43
1.1	Scope..... 1	6.3	Affidavit of Compliance 44
1.2	Purpose 2		
1.3	Application..... 2	Tables	
2 References	2	1	Physical Properties of Coal-Tar Enamel..... 6
3 Definitions	4	2	Physical Properties of Base Glass and Outerwraps 8
4 Requirements		3	Physical Properties of Innerwrap 9
4.1	Equipment 4	4	Physical Properties of Tape 23
4.2	Materials and Workmanship..... 4		

This page intentionally blank.

Currently in preview, click buy full version

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C203.*

I. Introduction.

I.A. *Background.* Hot-applied coal-tar enamel has been used for corrosion protection of steel water pipe, both as an interior lining and as an exterior coating, since the mid-1930s. Internally, the coal-tar enamel is used without reinforcement or shielding. The hot enamel is spun into the pipe and provides a smooth internal lining having low hydraulic frictional resistance. When used as an external coating, the coal-tar enamel, when specified, is reinforced with glass fiber inner and outer wrap. These wraps have replaced the original fibrous material, such as asbestos felt, which was a standard wrap for many years until health concerns regarding asbestos surfaced. The glass fiber inner and outer wraps are now being specified as routine reinforcements for coal-tar enamel coatings.

I.B. *History.* The first AWWA standards for coal-tar enamel were approved Apr. 25, 1940, and were designated 7A.5, for steel water pipe in sizes 30 in. (750 mm) and larger, and 7A.6, for steel water pipe of size up to, but not including, 30 in. (750 mm). Revisions of these documents were approved on Oct. 3, 1949; June 21, 1950; May 1, 1951; and July 14, 1955.

In 1951, the designations of 7A.5 and 7A.6 were changed to AWWA C203 and AWWA C204, respectively.

On Mar. 27, 1957, a revision was approved that combined the two standards into one document designated as AWWA C203. Subsequent revisions were approved by the AWWA Board of Directors on Jan. 23, 1962; May 22, 1966; Jan. 29, 1973; June 25, 1978; Jan. 26, 1980; June 23, 1991; Feb. 1, 1998; Jan. 20, 2002, and June 7, 2015. This edition was approved on October 26, 2020.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[†] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. Specific policies of the state or local agency.
2. Two standards developed under the direction of NSF[‡]: NSF/ANSI[§]/CAN[¶] 60, Drinking Water Treatment Chemicals—Health Effects; and NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects.
3. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*, and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI/CAN 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures” to NSF/ANSI/CAN 61 does not stipulate a maximum allowable level (MAL) or contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C203 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by all parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues.

A. *Advisory Information on Product Application.* This standard defines coal-tar protective coatings and linings in terms of performance to establish the quality desired

[†] Persons outside the United States should contact the appropriate authority having jurisdiction.

[‡] NSF International, P.O. Box 130140, 789 North Dixboro Road, Ann Arbor, MI 48105.

[§] Both publications available from The National Academies Press, 500 Fifth Street NW, Keck 360, Washington, DC 20001.

[¶] Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.

for long-term prevention of corrosion. The standard covers the external coating and internal lining of steel water pipelines for underground or underwater installation. If an extended period of aboveground storage of coated pipe is anticipated, consideration should be given to the ability of the coating to resist ultraviolet degradation and other atmospheric and environmental conditions.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following information should be provided by the purchaser:

1. Standard used—that is, ANSI/AWWA C203, Coal-Tar Protective Coatings and Linings for Steel Water Pipe, of latest revision.
2. Any exceptions to the standard that may be required.
3. Operating temperature.
4. Location of coating application with reference to environmental considerations.
5. Diameter, length, and location of pipeline, including maps and drawings necessary to show all details of the pipeline.
6. Application and use of materials provided in this standard should conform to warnings and instructions provided by the manufacturers and conform to existing federal and local governmental regulations.
7. Requirements for outdoor storage (Sec. 1.1.1).
8. Details of federal, state, and local requirements (Sec. 4.2).
9. For applications other than potable water, whether compliance with NSF/ANSI/CAN 61 Drinking Water System Components—Health Effects, is required (Sec. 4.2.3).
10. If materials only are being purchased according to the requirements of Sec. 4.2 of this standard, the purchaser shall specify quantities for the following items: (1) primer by type (Sec. 4.3.2); (2) coal-tar enamel by type (Sec. 4.3.3.1 and Table 1); (3) outerwrap (Sec. 4.3.4); and (4) glass fiber inner mat (Sec. 4.3.5). The purchaser could also specify if an affidavit of compliance is required (Sec. 6.3).
11. Type of liquid adhesive (Sec. 4.3.2).
12. Type of coal-tar enamel (Sec. 4.3.3).
13. Type of outerwrap (Sec. 4.3.4).
14. Length of pipeline requiring internal protection (Sec. 4.4.1.1).

15. Length of pipeline requiring: (1) normal exterior protection (Sec. 4.4.1.2) together with any preference regarding finish coat of whitewash, water-emulsion latex paint, or kraft paper; and (2) each type of additional exterior protection required for unusual underground or underwater conditions (Sec. 4.7).

16. Requirements for coating system thickness (Sec. 4.4.1.3 and 4.7).

17. Holdback of lining and coating at ends of pipe sections (Sec. 4.4.9)

18. Lining and coating of pipe ends (Sec. 4.4.10).

19. If materials only are being purchased according to the requirements of Sec. 4.6 of this standard, then, in addition to items 20 and 21, the purchaser should specify the following: (1) quantity of liquid adhesive (Sec. 4.6.5.1); (2) quantity of tape (Sec. 4.6.5.2); and (3) affidavit of compliance, if required (Sec. 6.3).

20. Additional materials or procedures (Sec. 4.6.2).

21. Thickness of tape (Table 4).

22. Adhesion tests (Sec. 4.6.8).

23. Additional exterior protection that may be required. Typically, the exterior coating includes a glass fiber innerwrap and outerwrap (Sec. 4.3.4.1).

24. Samples of materials, if required (Sec. 5.1.4).

25. Inspection, testing, and rejection (Sec. 5.1.4.1).

26. Testing frequency of coating thickness measurement (Sec. 5.3.1).

27. Affidavit of compliance, if required (Sec. 6.3).

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. Section 2, References, was updated.

2. The definition for applicator was added and the definition for constructor was deleted in Section 3, Definitions, and the terms were switched out throughout the standard in order to clarify responsibilities.

3. The description for outerwraps was slightly revised in Sec. 4.3.4.1.

4. The title of Sec. 4.6 was changed.

Sec. 6.3 was modified to include affidavits from both the coal-tar manufacturer and the applicator.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C203-20
(Revision of ANSI/AWWA C203-15)

AWWA Standard

Coal-Tar Protective Coatings and Linings for Steel Water Pipe

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard provides the minimum requirements for coal-tar protective coatings and linings used in the water supply industry for buried steel water pipelines.

AWWA steel pipe coating and lining standards are written for and based on the service temperature of potable water. For operating temperatures higher than the normal temperature of potable water, consult the manufacturer for recommendations concerning temperature limitations for coal-tar protective coatings and linings.

1.1.1 *Storage conditions.* Because aboveground and environmental conditions vary, the purchaser should consult the manufacturer as to type of coating that is recommended for the specific anticipated storage conditions, including the necessity for ultraviolet-light protection.

1.1.2 *Safety and environmental considerations.* The components of the coal-tar system may contain skin irritants and may be flammable. Precautions should be taken to protect against these hazards and to comply with the manufacturer's recommendations concerning the use and handling of the components.