



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C217-16
(Revision of ANSI/AWWA C217-09)

AWWA Standard

Microcrystalline Wax and Petrolatum Tape Coating Systems for Steel Water Pipe and Fittings

Effective date: Aug. 1, 2016.

First edition approved by AWWA Board of Directors June 21, 1990.

This edition approved Jan. 16, 2016.

Approved by American National Standards Institute Jan. 8, 2016.




AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the Official Notice section of *Journal – American Water Works Association*. The action becomes effective on the first day of the month following the month of *Journal – American Water Works Association* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic revision, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional material, on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval mark on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org



ISBN-13, print: 978-1-62576-174-3

eISBN-13, electronic: 978-1-61300-385-5

DOI: <http://dx.doi.org/10.12999/AWWA.C217.16>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2016 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe-Manufacturer's Technical Advisory Committee (SWPMTAC) Task Group on updating ANSI/AWWA C217 had the following personnel at the time:

Frank C. Rampton, *Chair*

John A. Wise, *Vice-Chair*

General Interest Members

D. D'Ambrosio, Polyguard Products, Ennis, Texas	(AWWA)
D. Libby, Chase Corporation, Westwood, Mass.	(AWWA)
R. Norsworthy, Polyguard Products, Ennis, Texas	(AWWA)
F.C. Rampton, Trenton Corporation, Ann Arbor, Mich.	(AWWA)
J.A. Wise, Canus International Sales Inc., Surrey, B.C., Canada	(AWWA)

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bamberg, *Chair*

Dennis Decharie, *Vice-Chair*

John L. Luka, *Secretary*

General Interest Members

W.R. Brunzell, Brunzell Associates Ltd. Skokie, Ill.	(AWWA)
R.J. Card, Lockwood, Andrews & Newnam Inc., Sugar Hill, Ga.	(AWWA)
R.L. Coffey, HDR Engineering Inc., Omaha, Neb.	(AWWA)
S.N. Foellmi, Black & Veatch Corporation, Irvine, Calif.	(AWWA)
R.L. Gibson, Freese and Nichols Inc., Fort Worth, Texas	(AWWA)
M.D. Gossett,* HDR, Denver, Colo.	(AWWA)
M.B. Horsley, Horsley Engineering LLC, Overland Park, Kan.	(AWWA)
R.A. Kutars, Norske Corrosion & Inspection Services Ltd., Surrey, B.C., Canada	(AWWA)
J.L. Mattson, Corrosion Control Technologies, Sandy, Utah	(AWWA)
J. Mullock, CH2M, Salt Lake City, Utah	(AWWA)
P. Ortega,* Lockwood, Andrews & Newnam, Houston, Texas	(AWWA)
E.S. Ralph,† Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)

* Alternate

† Liaison, nonvoting

A.E. Romer, AECOM, Orange, Calif.	(AWWA)
J.R. Snow, MWH Americas Inc., Denver, Colo.	(AWWA)
W.R. Whidden, Woolpert, Winter Park, Fla.	(AWWA)

Producer Members

D.W. Angell,* Standards Council Liaison, American Flow Control, Birmingham, Ala.	(AWWA)
S.A. Arnaout, Hanson Pressure Pipe Inc., Dallas, Texas	(AWWA)
H.H. Bardakjian, Consultant, Glendale, Calif.	(AWWA)
D. Dechant, Dechant Infrastructure Services, Aurora, Colo.	(AWWA)
V. DeGrande,* Ameron International, Chandler, Ariz.	(AWWA)
W.B. Geyer, Steel Plate Fabricators Association, Lake Zurich, Ill.	(AWWA)
B.D. Keil, Northwest Pipe Company, Draper, Utah	(AWWA)
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.	(AWWA)
R.D. Mielke,† Northwest Pipe Company, Raleigh, N.C.	(AWWA)
J. Olmos, Ameron International, Rancho Cucamonga, Calif.	(AWWA)
G.F. Ruchti,† Consultant, Punta Gorda, Fla.	(AWWA)
B.P. Simpson,† American Cast Iron Pipe Company, Birmingham, Ala.	(AWWA)
C.C. Sundberg, Victaulic, Issaquah, Wash.	(AWWA)
D. Walker, Avid Protective Products LTD/Tnemec Company, Oakville, Ont., Canada	(AWWA)
J.A. Wise, Canus International Sales Inc., Surrey, B.C., Canada	(AWWA)

User Members

G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.	(AWWA)
J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.	(AWWA)
B. Cheng, Metro Vancouver, Burnaby, B.C., Canada	(AWWA)
M.E. Conner, San Diego County Water Authority, San Diego, Calif.	(AWWA)
R.V. Frisz, US Bureau of Reclamation, Denver, Colo.	(USBR)
S. Hattan, Tarrant Regional Water District, Fort Worth, Texas	(AWWA)
T.J. Jordan,† Metropolitan Water District of Southern California, La Verne, Calif.	(AWWA)
P.K. Karna, Pacena Water, Tacoma, Wash.	(AWWA)
M. McReynolds, Metropolitan Water District of Southern California, La Mirada, Calif.	(AWWA)
M. Tunney,† Denver Water Department, Denver, Colo.	(AWWA)
D.A. Wigner, Los Angeles Department of Water and Power, Los Angeles, Calif.	(AWWA)

* Alternate

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.3	Coating System 4
I	Introduction..... vii	4.4	Coating Applications..... 5
I.A	Background..... vii	4.5	Field Procedures..... 7
I.B	History..... vii	5	Verification
II	Special Issues..... vii	5.1	Coating Materials Prequalification 8
II.A	Advisory Information on Product Application vii	5.2	Requirements of Coating System..... 8
III	Use of This Standard vii	5.3	Quality Assurance and Records..... 10
III.A	Purchaser Options and Alternatives vii	5.4	Inspection and Testing by the Purchaser..... 10
III.B	Modification to Standard viii	5.5	Quality-Control Requirements of Applied Coating System 11
IV	Major Revisions..... viii	5.6	Rejection 11
V	Comments ix	6	Delivery
Standard		6.1	Marking..... 11
1	General	6.2	Packaging and Shipping 12
1.1	Scope 1	6.3	Affidavit of Compliance 12
1.2	Purpose 2		Tables
1.3	Application..... 2	1	Properties of Primer and Coating 4
2	References 2	2	Prequalification Requirements of Primer 5
3	Definitions 3	3	Prequalification Requirements of Tape..... 6
4	Requirements	4	Quality-Control Properties of Primer 6
4.1	Equipment 3		
4.2	Materials and Workmanship 4		

This page intentionally blank.

Currently in preview, click buy full version

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C217.

I. Introduction.

I.A. *Background.* This standard was developed to provide information on cold-applied petrolatum tape coatings and petroleum wax tape coatings for external use on special sections, connections, and fittings for buried or submerged steel water pipelines. The latest edition of the standard (2016) was updated to provide a more accurate description of the tape made with microcrystalline wax and petrolatum.

I.B. *History.* Development of this standard was authorized by the American Water Works Association (AWWA) Standards Council on Nov. 3, 1985. The first edition was approved by the AWWA Board of Directors on June 21, 1990. Subsequent revisions to ANSI/AWWA C217 were prepared by the AWWA Standards Committee and approved on June 17, 1995; Jan. 24, 1999; Jan. 18, 2004; and Jan. 25, 2009. This edition was approved on Jan. 16, 2016.

II. Special Issues.

II.A. *Advisory Information on Product Application.* This standard defines the performance of cold-applied petrolatum tape and petroleum wax tape coatings establishing the quality desired for long-term protection and prevention of corrosion. It applies to the exterior coating of steel water pipelines for underground and underwater installation under normal conditions. It is based on previous experience but is not designed for unqualified use under all conditions. The advisability of its use for any installation must be reviewed by the purchaser. If an extended period of aboveground storage of coated pipe is anticipated, the material's ability to resist degradation by ultraviolet light and other atmospheric and environmental conditions should be considered.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following items should be provided by the purchaser.

1. Standard used that is, ANSI/AWWA C217, Microcrystalline Wax and Petrolatum Tape Coating Systems for Steel Water Pipe and Fittings, of latest revision.
2. Any exceptions to the standard that may be required.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

3. Expected aboveground exposure time (foreword, Section II.A).
4. Description and dimensions of each type of special section for each type of exterior protection.
 - a. Normal or average conditions.
 - b. Unusual conditions (Sec. 1.1.1).
5. Physical properties of primer and coating (Table 1).
6. Coating-system thickness (Sec. 4.3.3.4).
7. Surface preparation (Sec. 4.4.1).
8. Tape coating repair (Sec. 4.4.4).
9. Inspection (Sec. 5.4).
10. Testing (Sec. 5.2).
11. Packaging and shipping (Sec. 6.2).
12. Affidavit of compliance, if required (Sec. 6.3).

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. The title and scope of the standard were changed to add an additional wax type and expand the intended usage to include steel fittings.
2. The definition for petrolatum was revised and a new definition for microcrystalline wax was added in place of petroleum wax (Section 3).
3. Section 4 was modified to be consistent with the formatting and section numbers of other AWWA coating standards.
4. Table 1 was modified and new Tables 2, 3, and 4 were added to include information and requirements consistent with changes made to other AWWA coating standards.
5. The minimum breaking strength in Table 3 was modified to more accurately reflect the industry-accepted minimum.
6. Minimum thickness of primer listed in Table 4 was modified to require complete coverage to more accurately reflect industry practice.
7. Sec. 4.3 was modified to include the option of using a wax-based filler material in the coating system.
8. Portions of Sec. 4.5, Field Procedures, language were deleted and the reader is referred to AWWA C604 to be consistent with changes in other AWWA coating standards.

9. Section 5, Verification, was modified to be consistent with the new language and format being used in other AWWA coating standards.

10. New requirements and sections for dielectric strength (Sec. 5.2.2.4), cathodic disbondment testing (Table 3 and Sec. 5.2.2.5), breaking strength (Sec. 5.2.2.6), and elongation (Sec. 5.2.2.7) were added for consistency with other AWWA coating standards.

11. A new Sec. 5.3, Quality Assurance and Records, was added.

12. A new Sec. 5.4, Inspection and Testing by the Purchaser, was added.

13. Under new Sec. 5.5, Quality Control Requirements of Applied Coating System, new requirements for coating appearance (Sec. 5.5.1) and primer thickness (Sec. 5.5.2) were added.

14. The Electrical Continuity Inspection section was updated (Sec. 5.3).

15. Previous Sec. 5.3, Notice of Nonconformance, was renamed Rejection (new Sec. 5.6) and revised.

16. Section 6, Delivery, was modified to be consistent with other AWWA coating standards.

17. A new Sec. 6.2.1.4 was added under Packaging and Shipping to include wax-based filler.

18. The information in Sec. 6.2.2, Shipping, Handling, and Storage, was updated.

19. Sec. 6.3, Affidavit of Compliance, was modified to include an affidavit for workmanship.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or e-mail at standards@awwa.org.

This page intentionally blank.

Currently in preview, click buy full version



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C217-16
(Revision of ANSI/AWWA C217-09)

AWWA Standard

Microcrystalline Wax and Petrolatum Tape Coating Systems for Steel Water Pipe and Fittings

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard establishes minimum requirements for microcrystalline wax and petrolatum tape coating systems for steel water pipe and fittings.

This standard describes exterior coatings that consist of cold-applied microcrystalline wax or petrolatum primers and tapes and their applications to special sections, connections, and fittings to be used with buried, submerged, and above-ground steel water pipelines. The primers and tapes are not intended for use with steel joints or sections of steel pipe where coatings of cement mortar or concrete are applied directly onto the bare steel pipe. These coatings may be field- or shop-applied according to the provisions of this standard.

1.1.1 *Conditions not described in this standard.* This standard does not describe the additional materials and procedures that may be required for difficult conditions, such as those encountered in building some submarine lines, casing pipe, river crossings, and lines that are in rocky areas or in severe soil stress. Consult the manufacturer for the additional materials and procedures that may be required for these conditions. These materials may not be described in this standard.