

M23

PVC Pipe— Design and Installation

Third Edition



American Water Works
Association

Currently in preview, click buy full version

PVC Pipe—Design and Installation

Third Edition

Erratum incorporated October 2022



**American Water Works
Association**

Manual of Water Supply Practices—M23, Third Edition

PVC Pipe—Design and Installation

Copyright © 2020 American Water Works Association

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Disclaimer

The authors, contributors, editors, and publisher do not assume responsibility for the validity of the content or any consequences of its use. In no event will AWWA be liable for direct, indirect, special, incidental, or consequential damages arising out of the use of information presented in this book. In particular, AWWA will not be responsible for any costs, including, but not limited to, those incurred as a result of lost revenue. In no event shall AWWA's liability exceed the amount paid for the purchase of this book.

If you find errors in this manual, please email books@awwa.org. Possible errata will be posted at www.awwa.org/resources-tools/resource.development.groups/manuals-program.aspx.

Senior Managing Editor/Project Manager: Melissa Valentine
Technical Editor: Suzanne Snyder
Cover Design/Technical Illustrations: Michael Labruyere
Manager, Publishing Operations: Gillian Wink
Compositor: Innodata
Senior Specialist - Manuals: Willadee Hitchcock
Manuals Coordinator 2: Janet Greifinger

Library of Congress Cataloging-in-Publication Data

Names: Walker, Robert (Hydraulic engineer), author. | American Water Works Association, editor.

Title: M23 PVC pipe : design and installation / by Robert Walker.

Other titles: PVC pipe | PVC pipe--design and installation

Description: Third edition. | Denver, CO : American Water Works Association, [2020] | Revised edition of: PVC pipe--design and installation. | Includes bibliographical references and index. |

Summary: "This manual provides the user with both general and technical information to aid in design, procurement, installation, and maintenance of PVC pipe and fittings. This manual presents a discussion of recommended practices"-- Provided by publisher.

Identifiers: LCCN 2020000645 | ISBN 978-1-6257-6360-0 (paperback)

Subjects: LCSH: Water-pipes--Design and construction. | Pipe, Plastic. | Polyvinyl chloride.

Classification: LCC TD491 .W28 2020 | DDC 696/.1--dc23


LC record available at <http://idn.loc.gov/2020000645>

Printed in the United States of America

ISBN 978-1-6257-6360-0

Electronic ISBN-13 978-1-61300-530-9

DOI <https://doi.org/10.12999/AWWA.M23ed3>



**American Water Works
Association**

American Water Works Association
6666 West Quincy Avenue
Denver, CO 80235-3098
awwa.org

Contents

List of Figures	v
List of Tables	vii
Preface	ix
Acknowledgments	xi
Chapter 1	General Properties of Polyvinyl Chloride Pipe
	Material Properties of PVC Pipe Compounds, 1
	Corrosion, Permeation, and Chemical Resistance, 4
	Environmental Effects, 6
	References, 9
Chapter 2	Testing and Inspection11
	Testing and Inspection, 11
	References, 15
Chapter 3	Hydraulics17
	Flow Formulas, 17
	References, 24
Chapter 4	External Load Design for Trench Installation25
	Flexible Pipe Design, 25
	Trench Terminology, 26
	Soil Classes, 27
	Soil Compaction, 27
	Basic and Engineered Installations, 28
	Pipe Deflection, 29
	Load on Pipe, 30
	Pipe Stiffness, 33
	Example, 40
	References, 42
Chapter 5	Design for Internal Pressure43
	Internal Hydrostatic Pressure, 43
	Internal Surge Pressure, 48
	Injection-Molded PVC Fittings, 57
	Fabricated PVC Fittings, 57
	Air Removal and Vacuum Prevention, 57
	References, 58
Chapter 6	Receiving, Storage, and Handling61
	Receiving, 61
	Storage, 63
	Reference, 64
Chapter 7	Installation in Trenches and Embankments65
	Alignment and Grade, 66
	Installation in Trenches, 66
	Basic and Engineered Installations, 67

	Soil Classes and Treatment, 69	
	Pipe Bedding, 72	
	Pipe Joints, 73	
	Pipe Cutting and Bending, 75	
	Haunch Zone and Initial Backfill, 75	
	Soil Compaction, 76	
	References, 78	
Chapter 8	Testing and Maintenance.....	79
	Initial Testing, 79	
	Timing of the Testing, 80	
	Initial Cleaning of the Pipeline, 80	
	Test Preparation, 80	
	Hydrostatic Testing, 81	
	Test Pressure, 81	
	Duration of Tests, 82	
	Test Allowance, 82	
	Test Acceptance, 84	
	Disinfecting Water Mains, 84	
	System Maintenance, 84	
	References, 85	
Chapter 9	Service Connections.....	87
	Pipe Tapping Overview, 87	
	Direct Tapping, 91	
	Saddle Tapping, 97	
	Sleeve Tapping, 102	
	References, 106	
Chapter 10	Trenchless Installation of PVC Pipe.....	107
	PVC Properties for Trenchless Construction, 107	
	Trenchless Installation Joints Available with PVC, 108	
	Trenchless Construction and Trenchless Rehabilitation, 110	
	Reference, 121	
Chapter 11	Design for Thrust Restraint.....	123
	Forces at Horizontal Bends, 124	
	Forces at Other Fittings, 124	
	Thrust Blocks, 125	
	Restrained Joints, 129	
	References, 141	
Chapter 12	Other Design Considerations.....	143
	Axial Deflection and Bending, 143	
	Expansion and Contraction, 150	
	Methods for Locating Buried PVC Pipelines, 153	
	References, 153	
Appendix A	Requirements for Establishing the Hydrostatic Design Basis (HDB) of PVC Compounds for Pipe or Fittings.....	155
Appendix B	Hydraulic Tables.....	167
	Index, 217	
	List of AWWA Manuals, 223	

Figures

- 1-1 Class 12454 requirements, 4
- 1-2 Approximate relationship for 12454 PVC for PVC pipe strength properties versus temperature, 6

- 3-1 Moody diagram—friction factor, 19
- 3-2 Moody diagram—relative roughness, where ϵ is in ft, 20
- 3-3 Friction loss characteristics of water flow through PVC pipe, 22
- 3-4 Resistance of valves and fitting to flow of fluids, 23

- 4-1 Flexible pipe deflection, 26
- 4-2 Trench construction and terminology, 27
- 4-3 Distribution of AASHTO HS20 or HS25 live load through granular fill, for $H \leq 45$ in. (3.75 ft), 32
- 4-4 AASHTO HS20 live load, soil load (120 pcf), and total load graph, 34
- 4-5 AASHTO HS25 live load, soil load (120 pcf), and total load graph, 35
- 4-6 Cooper E80 live load, soil load (120 pcf), and total load graph, 35

- 5-1 Stress regression curve for PVC pressure pipe, 43
- 5-2 Stress regression lines, 46
- 5-3 Strength and life lines of PVC 12454, 46
- 5-4 Diagram showing internal pressure, design stress, and pipe wall thickness, 47
- 5-5 Recurring (cyclic) design graph for PVC pressure pipe, 53
- 5-6 Recurring (cyclic) design graph example, 56

- 6-1 Chock block, 63

- 7-1 Trench construction and terminology, 66
- 7-2 Standard trench types for PVC and PVCO pipe, 68
- 7-3 Basic installation for PVC and PVCO pipe, 69
- 7-4 Engineered installation for PVC and PVCO pipe, 70
- 7-5 Diagram showing lower boundary of initial backfill, 76

- 9-1 Corporation stop, 88
- 9-2 Brass tapping saddle, 88
- 9-3 Tapping sleeve, 88
- 9-4 Smooth coupon, 89
- 9-5 Coupon with striations, 89
- 9-6 Coupon showing “crown” at outer surface, 90
- 9-7 Coupon showing “punch-through” at inner wall, 90
- 9-8 Cordless drill and brace and bit, 92
- 9-9 Slotted core cutter with threads for direct tapping, 92

- 9-10 Improper tapping bits, 93
- 9-11 Tap spacing for 12-in. pipe or smaller, 94
- 9-12 Feed lightly, just enough to keep the cutter engaged, 95
- 9-13 Incorrect and correct mounting of tapping machine, 95
- 9-14 Improper saddle sizing, 98
- 9-15 Proper saddle sizing, 98
- 9-16 Brass tapping saddles, 99
- 9-17 Tapping machines with feed nut and yoke, 100
- 9-18 Hand-held drill and threading boring bar without ratchet feed, 100
- 9-19 Improper cutters, 100
- 9-20 Tapping sleeve, 103

- 10-1 Butt fused pipe, 109
- 10-2 Spline and grooves restraint, 109
- 10-3 Pins and groove restraint, 109
- 10-4 Grip ring and casing, 110
- 10-5 Typical HDD alignment shown schematically for design considerations, 111
- 10-6 Illustration of minimum bend radius, 111
- 10-7 Example of short pipe sections being used to reduce coefficient of friction, 113
- 10-8 Typical roller placement, 113
- 10-9 Insertion schematic for rollers, 114
- 10-10 Field application of roller-supported insertion, 114
- 10-11 Schematic for an aerial insertion with rollers, 115
- 10-12 Proper use of aerial slings, with rollers to reduce friction, for an HDD insertion, 115
- 10-13 Schematic of slipline insertion pulled from grade, 118
- 10-14 Annular space in sliplining, 119

- 11-1 Free body diagram of forces at a pipeline bend, 124
- 11-2 Thrust forces generated at other pipeline fittings, 125
- 11-3 Typical thrust block for horizontal bend, 126
- 11-4 Thrust block placement to resist thrust forces, 128
- 11-5 Gravity thrust block for a vertical down bend, 129
- 11-6 The Unified Soil Classification System, 130
- 11-7 Bearing and frictional resistance acting on a restrained horizontal bend, 134
- 11-8 Restraint design for a dead end, 136
- 11-9 Restraint design for a reducer, 136
- 11-10 Restraint design for a tee, 137
- 11-11 Restraint design for a vertical down bend, 138
- 11-12 Restraint design for a vertical up bend, 139

- 12-1 PVC pipe longitudinal bending diagram, 145
- 12-2 PVC pipe joint offset, 148
- 12-3 Length variation of unrestrained PVC pipe as a result of temperature change, 152

Tables

- 1-1 Cell class requirements for rigid poly(vinyl chloride) compounds, 3
- 4-1 Soil classes for pipe installation, 28
- 4-2 AASHTO HS20, HS25, and Cooper E80 live loads (psi), 34
- 4-3 PVC and PVCO pipe stiffness, 36
- 4-4 E' values, psi, 38
- 4-5 Values for the soil support combining factor, S_c , 38
- 4-6 E'_n based on standard penetration test (SPT) values, psi, 39
- 5-1 Thermal de-rating factors for PVC and PVCO pressure pipes and fittings, 44
- 5-2 Pressure classes and required minimum burst-test pressures for PVC pipe (ANSI/AWWA C900), 49
- 5-3 PVC pipe pressure surge for each 1-ft/s (0.3-m/s) instantaneous flow velocity change, 51
- 5-4 Safe maximum occasional surge pressures and allowable sudden changes in water velocity for ANSI/AWWA PVC pipe operating at working pressures (WP) expressed as percent of nominal pressure class (PC), 52
- 7-1 Soil classes for pipe installation, 70
- 8-1 Makeup water test allowances per 1,000 ft (305 m) of PVC pipe, gph, 83
- 9-1 Guidance for outlet sizes, 88
- 9-2 Guidance for direct tapping, 91
- 9-3 Guidance for saddle tapping, 97
- 9-4 Guidance for sleeve tapping, 102
- 10-1 Important material properties for trenchless installation, 108
- 10-2 Recommended straight (no bending) pull and push force values, along with the safety factor, used to calculate them, for 8-in. DR 18 PVC pipe, 110
- 10-3 Pre-installation, recommended support spacing for restrained-joint PVC pipe (ejector), 112
- 10-4 Recommended grouting pressure limits, 120
- 10-5 Temperature corrections for modulus of elasticity, tensile load, and pressure, 120
- 11-1 Estimated bearing strength of undisturbed soil, 126
- 11-2 Pipe to soil interface properties used to calculate R_s and F_s , 131
- 11-3 In-situ values of fine-grained soils that are used to calculate R_s , 132
- 12-1 Longitudinal bending relationships for Figure 12-1, 146
- 12-2 Allowable longitudinal bending for fusion-joined PVC pressure pipe, 147

- 12-3 Longitudinal bending stress and strain in PVC pipe at 73.4°F (23°C), 149
- 12-4 PVC coefficient of thermal expansion in relation to other pipe materials, 151
- 12-5 Length variation per 10°F (5.6°C) ΔT for PVC pipe, 151

- A-1 Minimum data requirements for initial ratings, 156
- A-2 Minimum test duration and data distribution requirements for initial levels, 156
- A-3 Substitution resin property requirements, 158
- A-4 Compound ingredient variation limits, 159
- A-5 Generic compound ingredient requirements and range limits, 161
- A-6 Calcium stearate property requirements, 162
- A-7 Paraffinic hydrocarbon wax property requirements, 162
- A-8 Polyethylene wax property requirements, 163
- A-9 Titanium dioxide property requirements, 164
- A-10 Uncoated calcium carbonate property requirements, 164
- A-11 Stearate-coated calcium carbonate property requirements, 165
- A-12 Required test procedures and references for the evaluation of calcium carbonate properties, 165

- B-1 Flow friction loss, AWWA C900 CIOD PVC pipe, 166
- B-2 Flow friction loss, AWWA C900 (and ASTM D2241) IPS OD PVC pipe, 192
- B-3 Flow friction loss, AWWA C909 (and CSA B137.3.1) CIOD PVCO pipe, 206

Preface



This is the third edition of AWWA M23, *PVC Pipe—Design and Installation*. This manual provides the user with both general and technical information to aid in design, procurement, installation, and maintenance of PVC pipe and fittings.

This manual presents a discussion of recommended practices. It is not intended to be a technical commentary on AWWA standards that apply to PVC pipe, fittings, and related appurtenances.

This page intentionally blank.

Acknowledgments

The following key individuals and members of the PVC Pipe Design Manual Subcommittee were instrumental in updating this edition of the M23 manual.

Robert Walker, (Task Group Chairman) Underground Solutions, Southlake, Tex.
Linda Bowles, Bureau of Reclamation, Denver, Colo.
Amster Howard, Consultant, Lakewood, Colo.
Tim McCandless, Staff Engineer Liaison, AWWA, Denver, Colo.
Jay Parvez, Uni-Bell PVC Pipe Association, Dallas, Tex.
Larry Schmidt, Diamond Plastics Corporation, Grand Island, Neb.
Suzanne Scott, North American Pipe Corporation, Woodbridge, Ont. Canada
Dennis Shumard, EBAA Iron, Katy, Tex.
Bill Whidden, Woolpert, Orlando, Fla.

This manual was developed by the AWWA Standards Committee on PVC Pressure Pipe and Fittings. The membership of the committee at the time it approved this manual was as follows:

W. R. Whidden, (Committee Chair) Woolpert, Orlando, Fla.
S. D. Adams, Gwinnett County Dept. of Water Resources, Lawrenceville, Ga.
J. R. Barbier, Denver Water, Denver, Colo.
R. R. Bishop, Diamond Plastics Corporation, Grand Island, Neb.
L. M. Bowles, (Chapter Chair) Bureau of Reclamation, Denver, Colo.
J. P. Castronovo, Blue Ridge, Ga.
A. Chastain-Howley, (Standards Council Liaison) Atonix Digital, Frisco, Tex.
A. J. Ciechanowski, NSF International, Ann Arbor, Mich.
S. J. Cook, Black & Veatch, Virginia Beach, Va.
S. E. Cooper, Uni-Bell PVC Pipe Association, Louisville, Ky.
S. Ferry, PSILab Inc., Longmont, Colo.
G. Garcia, JM Eagle, Los Angeles, Calif.
L. J. Gill, (Chapter Chair) Ipex Management Inc., Oakville, Ont. Canada
S.B. Gross, North American Pipe, Wayne, Pa.
G. Gundel, Specified Fittings, Bellingham, Wash.
J. Hebenstreit, UL LLC, Northbrook, Ill.
W. Hitchcock, (Staff Adviser) AWWA, Denver, Colo.
J. F. Houle, John F. Houle LLC, Livingston, Tex.
M. Huynh, JM Manufacturing Company Inc. DBA JM Eagle, Los Angeles, Calif.
K. S. Jeng-Bulloch, City of Houston, Houston, Tex.
A. Korell, City of North Bay, North Bay, Ont. Canada
J. Larson, Marshall Municipal Utilities, Marshall, Minn.
T. E. Layton, Orange County Utilities, Orlando, Fla.
S. C. Macleod, UL LLC, Melville, N.Y.
M. T. Marino, Nussbaumer & Clarke, Inc., Buffalo, N.Y.

- A. Marner, Bureau of Reclamation, Denver, Colo.
- T. Marti, (Chapter Chair) Underground Solutions Inc., Warrendale, Pa.
- T.J. McCandless, (Staff Engineer) AWWA, Denver, Colo.
- S. A. McKelvie, HDR Engineering Inc., Boston, Mass.
- J. R. Paschal, Paschal Engineering, Sandy, Utah
- M. Rennau, Diamond Plastics Corporation, Grand Island, Neb.
- J. Riordan, HARCO Fittings, Lynchburg, Va.
- J. Rudolf, Diamond Plastics Corporation, Grand Island, Neb.
- V. B. Sandoval, Natural Resources Cons. Svc., Boise, Idaho
- L. D. Schmidt, (Chapter Chair) Diamond Plastics Corporation, Grand Island, Neb.
- S. Scott, (Chapter Chair) Royal Building Products, Woodbridge, Ont. Canada
- D. Shumard, EBAA Iron, Katy, Tex.
- J. K. Snyder, Snyder Environmental Engineering Associates, Audubon, Pa.
- B. Sukolsky, Specified Fittings, Bellingham, Wash.
- S. Titus, Washington Suburban Sanitary Commission, Laurel, Md.
- R. P. Walker, (Chapter Chair) Underground Solutions, Southlake, Tex.

Chapter **1**

General Properties of Polyvinyl Chloride Pipe

Polyvinyl chloride (PVC)* was discovered in the late nineteenth century. Scientists at that time found the new plastic material unusual in that it appeared nearly inert to most chemicals. However, it was soon discovered that the material was resistant to change, and it was concluded that the material could not be easily formed or processed into usable applications.

In the 1920s, scientific curiosity again brought PVC to public attention. In Europe and America, extended efforts eventually brought PVC plastics to the modern world. Technology, worldwide and particularly in Germany, slowly evolved for the use of PVC in its unplasticized, rigid form, which today is used in the production of a great many extruded and molded products. In the mid-1930s, German scientists and engineers developed and produced limited quantities of PVC pipe. Some PVC pipe installed at that time continues to provide satisfactory service today. Molecularly oriented polyvinyl chloride (PVCO) pressure pipe has been installed in Europe since the early 1970s and in North America since 1991. Fusible PVC pipe has been installed in North America since 2004.

MATERIAL PROPERTIES OF PVC PIPE COMPOUNDS

Polyvinyl chloride pipe and fabricated fittings derive properties and characteristics from the properties of their raw material components. Essentially, PVC pipe and fabricated

* Unless otherwise noted in this manual, "polyvinyl chloride pipe" or "PVC" refers to PVC bell-and-spigot pipe and PVC fusible pipe; "PVCO" refers to molecularly oriented PVC pipe.