

BS 3L 500:2011+A1:2017



BSI Standards Publication

**Procedure for inspection, testing
and acceptance of wrought
magnesium base alloys**

bsi.

Publishing and copyright information

The BSI copyright notice displayed in this document indicates when the document was last issued.

© The British Standards Institution 2017

Published by BSI Standards Limited 2017

ISBN 978 0 500 97048 1

ICS 02.02.99

The following BSI references relate to the work on this document:

Committee reference ACE/61

Drafts for comment 10/30216237 DC; 17/30354462 DC

Amendments/corrigenda issued since publication

Date	Text affected
30 September 2017	A1 – See Foreword

Contents

	Page
Foreword	iv
Section 1: General requirements	1
1 Scope	1
2 Normative references	1
3 Definitions	1
4 General	3
5 Information and requirements to be agreed and to be documented	4
6 Manufacture and freedom from defects	6
7 Heat treatment	6
8 Chemical composition	6
9 Testing	7
10 Marking	8
11 Protection and packaging	8
12 Certification	8
Section 2: Cast billets and slabs for hot working	10
13 General	10
14 Condition	10
15 Dimensions and tolerances	10
16 Internal and external defects	10
17 Retesting procedure	10
18 Marking	10
Section 3: Extruded bar and section for forging	12
19 General	12
20 Condition	12
21 Dimensions and tolerances	12
22 Selection and preparation of mechanical test samples	12
<i>Table 1 — Batch sizes for extruded bar and section for forging</i>	12
23 Tensile testing	13
24 Etch inspection	13
25 Fracture test	13
26 Internal defects	14
27 External defects	14
28 Retesting procedures for etch inspection, fracture test and external defects	14
29 Marking	14
Section 4: Bars for machining and extruded sections	15
30 General	15
31 Condition	15
32 Dimensional tolerances	15
<i>Table 2 — Tolerances for bars for machining and extruded sections</i>	16
33 Selection and preparation of mechanical test samples	16
<i>Table 3 — Batch sizes for bars for machining and extruded sections</i>	16
34 Tensile testing	17
35 Etch inspection	17
36 Internal defects	17
37 Retesting procedures for etch inspection, fracture test and external defects	17
38 Marking	17
Section 5: Forgings	19
39 General	19

40	Manufacture	19
41	Pre-production forgings	19
42	Production forgings	20
43	Procedure X for process control testing	20
	<i>Table 4 — Maximum number of forgings to be manufactured between the collection of test samples</i>	21
45	Batch acceptance tensile tests	21
	<i>Table 5 — Tensile property requirements for forgings</i>	23
46	External defects	23
47	Internal defects	23
48	Grain flow and grain size	23
49	Special tests	24
50	Marking	24
	Section 6: Sheet and strip	25
51	General	25
52	Condition	25
53	Dimensional tolerances	25
	<i>Table 6 — Tolerances for sheet and strip</i>	25
54	Selection and preparation of mechanical test samples	25
55	Tensile testing	26
56	Marking	26
	Section 7: Plate	27
57	General	27
58	Condition	27
59	Dimensional tolerances	27
	<i>Table 7 — Tolerances for plate</i>	27
60	Selection and preparation of mechanical test samples	27
	<i>Table 8 — Direction of tensile test samples and position of tensile test pieces</i>	28
61	Tensile testing	28
62	Internal defects	28
63	Marking	28
	Section 8: Tube	29
64	General	29
65	Manufacture	29
66	Condition	29
67	Dimensional tolerances	29
	<i>Table 9 — Tolerances for tube</i>	29
68	Selection and preparation of mechanical test samples	29
	<i>Table 10 — Batch sizes for tubes</i>	29
69	Tensile testing	30
70	Marking	30
Annex A	(normative) Rules for application of values for chemical composition and mechanical properties given in material specifications	31
Annex B	(normative) Protection against corrosion	31
	<i>Table B.1 — Standard routes for protection against corrosion</i>	34
Annex C	(normative) Tolerances for bars and extruded sections	35
	<i>Table C.1 — Tolerances on straightness of bars and regular sections</i>	37
	<i>Table C.2 — Tolerances on twist of extruded sections</i>	37
	<i>Table C.3 — Tolerances on angles of regular sections</i>	37
	<i>Table C.4 — Tolerances on lengths of bars and extruded sections</i>	37

	<i>Table C.5 — Tolerances on thickness of bars and regular sections</i>	38
	<i>Table C.6 — Tolerances on thickness of hollow sections</i>	38
	<i>Table C.7 — Tolerances on diameters, overall widths and widths across flats of bars, regular sections and hollow sections</i>	39
	<i>Table C.8 — Tolerances on open ends of channels and I beams</i>	40
	<i>Table C.9 — Normal radii for corners on square and rectangular sections (informative)</i>	42
	<i>Table C.10 — Normal radii for corners on rectangular sections: angle, channel, I and T sections (informative)</i>	42
Annex D	(normative) Tolerances for sheet, strip and plate	42
	<i>Table D.1 — Tolerances on thickness of sheet and strip</i>	42
	<i>Table D.2 — Tolerances on thickness of plate</i>	44
	<i>Table D.3 — Cutting tolerances for sheet and plate</i>	44
	<i>Table D.4 — Shearing tolerances for strip</i>	45
	<i>Table D.5 — Tolerances on flatness of plate</i>	45
Annex E	(normative) Tolerances for tube	45
	<i>Table E.1 — Tolerances on straightness of tube</i>	45
	<i>Table E.2 — Tolerances on lengths of tube</i>	46
	<i>Table E.3 — Tolerances on outside and inside diameters of extruded round tube</i>	46
	<i>Table E.4 — Tolerances on wall thickness of extruded round tube</i>	47

Summary of pages

This document comprises a front cover, and inside front cover, pages i to vi, pages 1 to 47, an inside back cover and a back cover.

Foreword

Publishing information

This British Standard is published by BSI Standards Limited, under licence from The British Standards Institution and came into effect on 31 December 2011. It was prepared by Panel ACE/61/-/24, *Light alloys*, under the authority of Technical Committee ACE/61, *Metallic materials for aerospace purposes*. A list of organizations represented on this committee can be obtained on request to its secretary.

Supersession

BS 3L 500:2011 superseded BS 2L 500:1973, which has been withdrawn.

BS 3L 500:2011+A1:2017 supersedes BS 3L 500:2011, which is withdrawn.

Information about this document

BS 3L 500:2011 was a full revision of the standard, and introduced the following principal changes.

Section 1:

- a) Information to be supplied by purchaser added.
- b) Information to be agreed by manufacturer and purchaser added.
- c) Heat treatment requirements added.
- d) Application of values requirements added.
- e) Tensile testing at ambient temperature to BS A4-1.1 replaced by BS EN 2002-1.

Section 5:

External and internal defects requirements added.

Section 6:

Position of tensile test piece requirements added.

Section 7:

Position of tensile test piece requirements added.

Appendix A: Re-identified as Annex A (Rules for application of values for chemical composition and mechanical properties given in material specifications).

Appendix B: Re-identified as Annex B (Protection against corrosion).

Appendix C: Re-identified as Annex C (Tolerances for bars and extruded sections).

Appendix D: Re-identified as Annex D (Tolerances for sheet, strip and plate).

Appendix E: Re-identified as Annex E (Tolerances for tube).

Text introduced or altered by Amendment No. 1 is indicated in the text by tags A1 A1. Minor editorial changes are not tagged.

Hazard warnings

WARNING. This British Standard calls for the use of substances and/or procedures that can be injurious to health if adequate precautions are not taken. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

Use of this document

It has been assumed in the preparation of this British Standard that the execution of its provisions will be entrusted to appropriately qualified and experienced people, for whose use it has been produced.

Presentational conventions

The provisions of this standard are presented in roman (i.e. upright) type. Its requirements are expressed in sentences in which the principal auxiliary verb is “shall”.

Commentary, explanation and general informative material is presented in smaller italic type, and does not constitute a normative element.

Where words have alternative spellings, the preferred spelling of the Shorter Oxford English Dictionary is used (e.g. “organization” rather than “organisation”).

Contractual and legal considerations

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

Currently in preview, click buy full version

Currently in preview, click buy full version

Section 1: General requirements

1 Scope

This British Standard specifies procedures for inspection, testing and acceptance of wrought magnesium-base alloys for aerospace purposes.

The standard is applicable to material specifications in the British Standard Aerospace L series and also to other British Standard material specifications for wrought magnesium-base alloys which are suitable for aerospace use.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

BS M 93, *Protection of magnesium — Rich alloys against corrosion — Specification*

BS X 38, *Heat curing paint scheme for aerospace purposes — Specification*

BS EN 2002-1, *Metallic materials — Test methods — Part 1: Tensile testing at ambient temperature*

EN 2002-16, *Metallic materials — Test methods — Part 16: Non-destructive testing — Penetrant testing*¹

EN 4050-2, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 2: Performance of test*¹

EN 4050-4, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 4: Acceptance criteria*¹

3 Definitions

For the purposes of this British Standard, the following terms and definitions apply.

3.1 approved scrap

scrap which has been segregated and identified as being derived from material, the composition of which has been established with regard to the complete range of both alloying and impurity elements given in the material specification

3.2 bar

wrought material of uniformly round, half round, square, rectangular, hexagonal, octagonal or regular polygonal solid section supplied in straight lengths

3.3 batch

material which is of the same product form and of the same nominal dimensions; from the same cast; manufactured in the same production period; from the same heat treatment charge

NOTE 1 In the case of solution heat treatment in a continuous furnace, material from a maximum period of 8 h is regarded as the same heat treatment charge.

NOTE 2 Where applicable, batch sizes for specific products are given in the relevant sections of this standard.

¹ Published as ASD Prestandard at the date of publication of this standard.