



BSI Standards Publication

## Railway rolling stock materials

Part 1: Specification for axles for traction and trailing stock

**Publishing and copyright information**

The BSI copyright notice displayed in this document indicates when the document was last issued.

© The British Standards Institution 2023

Published by BSI Standards Limited 2023

ISBN 978 0 59 21809 1

ICS 5.04

The following BSI references relate to the work on this document:

Committee reference RAE/3

Draft for comment 22/30454253 DC

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

# Contents

	Page
<b>Foreword</b>	<b>III</b>
1 Scope	1
2 Normative references	1
3 Terms and Definitions	1
4 Information to be supplied by the purchaser	2
5 Classification and heat treatment	2
5.1 Grades of steels	2
5.2 Heat treatment condition	3
5.3 Degree of finish	3
6 Manufacture	3
6.1 Steelmaking	3
<i>Table 1 — Chemical composition</i>	3
<i>Table 2 — Permitted variations of product analysis from the specified range for significant elements</i>	4
<i>Table 3 — Heat treatment condition and mechanical properties</i>	4
<i>Table 4 — Heat treatment after straightening</i>	5
6.2 Manufacture of the axles	5
6.3 Hydrogen cracking (flakes)	5
6.4 Identification of axles during manufacture	5
6.5 Heat treatment	5
6.6 Straightening of rough axles	6
6.7 Dimensions	6
<i>Table 5 — Machining allowances and dimensional tolerances for unmachined<sup>A)</sup> forged and rolled axles</i>	6
<i>Table 6 — Dimensional requirements for part machined<sup>B)</sup> and ready for assembly<sup>B)</sup> axles</i>	7
<i>Table 7 — Average surface roughness for part machined<sup>A)</sup> and ready for assembly<sup>A)</sup> axles</i>	9
<i>Figure 1 — Key to the symbols used in Table 5</i>	9
<i>Figure 2 — Key to the symbols used for dimensional characteristics and surface roughness in Table 6 and Table 7</i>	10
<i>Figure 3 — Key to the symbols used for geometrical tolerances in Table 6 and Table 7</i>	10
6.8 Rectification	10
7 Manufacturer's brand marks	11
8 Inspection	11
9 Type and number of tests	11
9.1 Type of tests	11
9.2 Test units and subdivision into batches	11
9.3 Sampling and preparation of samples and test pieces	11
<i>Figure 4 — Micrographic examination sampling location (solid axle and hollow axle)</i>	12
9.4 Surface condition	13
9.5 Dimensional checks	13
<i>Table 8 — Type and number of tests</i>	13
<i>Figure 5 — Position of tensile test samples and test pieces (see 9.3.3)</i>	14
<i>Figure 6 — Position of impact test samples and test pieces (see 9.3.4)</i>	15
10 Test methods	15
10.1 Chemical analysis	15
10.2 Mechanical tests	15
10.3 Non-destructive tests	16
10.4 Micrographic cleanliness	16

10.5	Checking of surface condition	16
10.6	Checking of dimensions	16
11	Test results	16
11.1	Chemical composition	16
11.2	Mechanical properties	16
11.3	Non-destructive tests	16
11.4	Micrographic cleanliness	16
	<i>Table 9 — Level to be achieved for micrographic examination</i>	17
11.5	Surface condition	17
11.6	Dimensions	17
11.7	Retests	17
12	Conclusion of inspection	17
13	Certification	17
14	Protection in transport	18
14.1	Protection against corrosion	18
14.2	Protection against mechanical damage	18
<b>Annex A</b>	(informative) <b>Method for ultrasonic testing of part finished axles</b>	<b>19</b>
	<i>Figure A.1 — Standard calibration block</i>	21
<b>Annex B</b>	(normative) <b>Method for surface magnetic particle inspection</b>	<b>22</b>
	<b>Bibliography</b>	<b>24</b>

### Summary of pages

This document comprises a front cover, an inside front cover, pages I to IV, pages 1 to 24, an inside back cover and a back cover.

# Foreword

## Publishing information

This part of [BS 5892](#) is published by BSI Standards Limited, under licence from The British Standards Institution, and came into effect on 31 January 2023. It was prepared by Technical Committee RAE/3, *Railway Rolling Stock Products*. A list of organizations represented on this committee can be obtained on request to the committee manager.

## Supersession

BS 5892-1:2023 supersedes BS 5892-1:1992+A3:2009, which is withdrawn.

## Relationship with other publications

[BS 5892](#), which covers railway rolling stock materials, is published in the following eight parts:

- Part 1: Specification for axles for traction and trailing stock;
- Part 2: Specification for forged and rolled wheel centres;
- Part 3: Specification for monobloc wheels for traction and trailing stock;
- Part 4: Specification for forged and rolled tyres;
- Part 5: Specification for steel bars for retaining rings for tyre wheels;
- Part 6: Specification for wheelsets for traction and trailing stock;
- Part 7: Specification for product and technical approval requirements for cast wheels; and
- Part 8: Railway applications – Wheelsets and bogies – Powered and non-powered wheelsets with inboard bearings – Product requirements.

## Information about this document

This new edition of BS 5892-1 incorporates changes made necessary by the publication of [BS EN 13261:2020](#), particularly for axle manufacture and testing which is now included in the revised BS EN 13261. The additions include a grain size change and micro cleanliness assessment on the axle. It does not represent a full review or revision of the standard, which will be undertaken in due course.

**Product certification.** Users of this British Standard are advised to consider the desirability of third-party certification of product conformity with this British Standard based on testing and continuing surveillance, which may be coupled with assessment of a supplier's quality systems against the appropriate part of BS EN ISO 9001.

Enquiries as to the availability of third-party certification schemes will be forwarded by BSI to the Association of Certification Bodies. If a third-party certification scheme does not already exist, users should consider approaching an appropriate body from the list of Association members.

This publication can be withdrawn, revised, partially superseded or superseded. Information regarding the status of this publication can be found in the Standards Catalogue on the BSI website at [bsigroup.com/standards](https://bsigroup.com/standards), or by contacting the Customer Services team.

Where websites and webpages have been cited, they are provided for ease of reference and are correct at the time of publication. The location of a webpage or website, or its contents, cannot be guaranteed.

### **Presentational conventions**

The provisions of this standard are presented in roman (i.e. upright) type. Its requirements are expressed in sentences in which the principal auxiliary verb is “shall”.

*Commentary, explanation and general informative material is presented in smaller italic type, and does not constitute a normative element.*

Where words have alternative spellings, the preferred spelling of the *Shorter Oxford English Dictionary* is used (e.g. “organization” rather than “organisation”).

### **Contractual and legal considerations**

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient’s own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

## 1 Scope

This part of [BS 5892](#) specifies requirements for the manufacture, inspection and testing of forged and/or rolled axles (solid or hollow) in the unmachined, part machined or ready for assembly condition for traction and trailing stock. This part of [BS 5892](#) includes requirements for the dimensions, tolerances and surface finish that are to be adopted unless otherwise specified in the design drawing.

This part of [BS 5892](#) is not applicable to axles designed to BS EN 13103 and BS EN 13104, the manufacture, inspection and testing of which are specified in BS EN 13261.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes provisions of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[BS 1104](#), *Specification for general purpose Acme screw threads*

[BS 1134-1](#), *Assessment of surface texture – Methods and instrumentation*

[BS 6072](#), *Method for magnetic particle flow detection*

[BS 6200](#), *Sampling and analysis of iron, steel and other ferrous metals*

BS EN 10002-1, *Tensile testing of metallic materials – Part 1: Method of test at ambient temperature*

BS EN 10045-1, *Charpy impact test on metallic materials – Part 1: Test method (V- and U-Notches)*

BS EN ISO 643:2019, *Steels – Micrographic determination of the apparent grain size*

BS EN ISO 4967:2013, *Steel – Determination of content of nonmetallic inclusions – Micrographic method using standard diagrams*

BS EN ISO 9934-2, *Non-destructive testing – Magnetic particle testing – Detection media*

BS EN ISO 10012, *Measurement management systems – Requirements for measurement processes and measuring equipment*

## 3 Terms and Definitions

For the purpose of this part of [BS 5892](#), the following definitions apply.

### 3.1 solid axle

axle of homogeneous steel, produced by forging and/or rolling, that has not been bored

### 3.2 hollow axle

axle of homogeneous steel, produced by forging and/or rolling, that has been through bored along its centre line

### 3.3 unmachined

condition of an axle that has been forged and/or rolled having undergone no machining operation other than finishing to length and providing machining centres but is in the heat treatment condition specified