

Fracture mechanics toughness tests —

**Part 1: Method for determination of K_{Ic} ,
critical CTOD and critical J values of
metallic materials**

ICS 77.040.10

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Iron and Steel Standards Policy Committee (ISM/-) and the Non-ferrous Metals Standards Policy Committee (NFM/-) to Technical Committee ISM/NFM/4, upon which the following bodies were represented:

Aluminium Federation
 British Gas plc
 British Non-ferrous Metals Federation
 British Railways Board
 British Steel Industry
 Copper Development Association
 Department of Trade and Industry (National Engineering Laboratory)
 Department of Trade and Industry (National Measurement Accreditation Service)
 Department of Trade and Industry (National Physical Laboratory)
 ERA Technology Ltd.
 GAMBICA (BEAMA Ltd.)
 Ministry of Defence
 Society of British Aerospace Companies Limited
 Welding Institute

The following bodies were also represented in the drafting of the standard, through subcommittees and panels:

BCIRA
 BEAMA Ltd.
 Electricity Supply Industry in United Kingdom
 Lloyd's Register of Shipping
 Steel Casting Research and Trade Association
 United Kingdom Atomic Energy Authority

This British Standard, having been prepared under the direction of the Iron and Steel and the Non-ferrous Metals Standards Policy Committees, was published under the authority of the Standards Board and comes into effect on 20 December 1991.

© BSI 27 February 2002

The following BSI references relate to the work on this standard:
 Committee reference ISM/NFM/4
 Draft for comment 90/41825 DC

Amendments issued since publication

Amd. No.	Date	Comments
10543	August 1999	
12018 Corrigendum No. 1	27 February 2002	Corrections to Figure 10, Table 2 and 8.2.

Contents

	Page
Committees responsible	Inside front cover
Foreword	iii
<hr/>	
1 Scope	1
2 Definitions	1
3 Symbols and designations	2
4 Principle	4
5 Test specimens	4
6 Specimen preparation and fatigue precracking	9
7 Test equipment	18
8 Test procedure	22
9 Analysis of test data	25
10 Validity check lists	32
11 Test report	33
<hr/>	
Appendix A Bibliography	34
Appendix B Crack plane identification	34
Appendix C Measurement of load-line displacement (q) in a three point bend test	37
<hr/>	
Figure 1 — Flow chart for choice of fracture toughness parameter, specimen design and displacement measurement	5
Figure 2 — Proportional dimensions and tolerances for a rectangular section bend specimen	6
Figure 3 — Proportional dimensions and tolerances for a square section bend specimen	6
Figure 4 — Proportional dimensions and tolerances for a straight notch compact specimen	7
Figure 5 — Proportional dimensions and tolerances for a stepped notch compact specimen	8
Figure 6 — Acceptable fatigue crack starter notches and fatigue crack configurations	10
Figure 7 — Chevron notch	11
Figure 8 — Outward pointing knife edges and corresponding notch geometries	12
Figure 9 — Inward pointing knife edges and corresponding notch geometries	13
Figure 10 — Fixture for three point bend tests	14
Figure 11 — Typical design of clevis for applying a tensile force to a compact specimen using a circular hole in the clevis, and a pin having a diameter of $0.24W - 0.005W, - 0.015W$	20
Figure 12 — Typical design of clevis for applying a tensile force to a compact specimen using a hole with a flat in the clevis, and a pin having a diameter of $0.24W + 0.000W, - 0.005W$	21
Figure 13 — Characteristic type of force versus displacement records in fracture tests	23
Figure 14 — Assessment of pop-in behaviour	26
Figure 15 — Definition of F_Q (for the determination of K_Q)	27
Figure 16 — Definition of V_p (for the determination of CTOD)	29
Figure 17 — Definition of U_p (for the determination of J)	31
Figure 18 — Basic fracture plane identification: rectangular section	35
Figure 19 — Basic fracture plane identification: cylindrical sections	36
Figure 20 — Non-basic fracture plane identification	36

	Page
Figure 21 — Principle of the “comparator” bar measurement	37
Figure 22 — Displacements associated with three point bend specimens	38
Figure 23 — Simultaneous determination of extraneous displacements ($\Delta_1 + \Delta_2$)	38
Figure 24 — Location of two notch opening displacement measurements (V_1 and V_2) for the determination of load-line displacement	39
Table 1 — Dimensions of specimens that may lead to valid K_{Ic} values	9
Table 2 — Values of $f\left(\frac{a_0}{W}\right)$ for three point bend specimens	16
Table 3 — Values of $f'\left(\frac{a_0}{W}\right)$ for compact specimens	18
Publication(s) referred to	40

Foreword

This part of BS 7448 has been published under the direction of the Iron and Steel and the Non-ferrous Metals Standards Policy Committees.

It gives a method for determining plane strain fracture toughness (K_{Ic}), critical crack tip opening displacement (CTOD)¹⁾ and critical J fracture toughness values for metallic materials under displacement controlled monotonic loading at quasistatic rates.

This part of BS 7448 combines and extends the methods for determining K_{Ic} values, given in BS 5447, and the method for determining crack opening displacement (COD), given in BS 5762:1979, BS 5447:1977 and BS 5762:1979, which are withdrawn.

Determination of K_{Ic} for materials and conditions for which it is appropriate to determine fracture toughness in terms of K_{Ic} alone are covered in BS EN ISO 12737. General determinations of fracture toughness, where the fracture behaviour determines the relevant fracture parameter (e.g. K_{Ic} , CTOD or J) are covered in the procedures in this part of BS 7448, BS 7448-2 and BS 7448-4.

The other three parts of BS 7448 are as follows:

- *Part 2: Method for determination of K_{Ic} , critical CTOD or J values of welds in metallic materials;*
- *Part 3: Method for determination of dynamic toughness²⁾;*
- *Part 4: Method for determination of fracture resistance curves and initiation values for stable crack extension in metallic materials.*

It has been assumed in the drafting of this standard that the execution of its provisions is entrusted to appropriately qualified and experienced people.

Safety note. It is important to note that tests of the type described involve the use of large forces, and may involve the rapid movement of machine parts and fractured test specimens. Therefore it is important to consider the safety of machine operators.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i to iv, pages 1 to 40, an inside back cover and a back cover.

The BSI copyright notice displayed throughout this document indicates when the document was last issued.

¹⁾ In this British Standard the term CTOD, which refers to crack tip opening displacement, is synonymous with the term COD in BS 5762.

²⁾ In preparation.

Currently in preview, click buy full version

1 Scope

This part of BS 7448 specifies a method for determining the opening mode plane strain fracture toughness (K_{Ic}), the critical crack tip opening displacement (CTOD) fracture toughness, and the critical J fracture toughness of metallic materials. The method uses fatigue precracked specimens. These are tested in displacement controlled monotonic loading at a constant rate of increase in stress intensity factor within the range $0.5 \text{ MPa}\cdot\text{m}^{0.5}\text{s}^{-1}$ to $3.0 \text{ MPa}\cdot\text{m}^{0.5}\text{s}^{-1}$ ³⁾ during the initial elastic deformation. The specimens are loaded to fracture or the maximum force associated with plastic collapse. The method is especially appropriate to materials that exhibit a change from ductile to brittle behaviour with decreasing temperature. No other influences of environment are covered.

The definition of fracture toughness values relevant to particular structural integrity assessments is outside the scope of this British Standard.

NOTE 1 The titles of the publications referred to in this standard are listed on the inside back cover.

NOTE 2 Numbers in square brackets in the text refer to numbered items in the Bibliography in Appendix A.

NOTE 3 This British Standard does not cover the determination of K_{Ic} alone. Such determinations are covered in BS EN ISO 12737.

2 Definitions

For the purposes of this part of BS 7448 the following definitions apply.

2.1

stress intensity factor (K)

the magnitude of the stress field near the crack tip (a stress-field singularity) for a particular mode (see 2.2) in a homogeneous, ideally linear-elastic body

NOTE It is a function of applied force, crack length and specimen geometry, and is expressed in units of $\text{MPa}\cdot\text{m}^{0.5}$.

2.2

opening mode

opening displacement of the surfaces of a crack in a direction normal to the original (undeformed) crack plane near the crack tip

2.3

plane strain fracture toughness (K_{Ic})

a measure of a material's resistance to crack extension when the stress state near the crack tip is predominantly plane strain, plastic deformation is limited, and opening mode monotonic loading is applied

2.4

maximum fatigue stress intensity factor (K_f)

the maximum value of opening mode stress intensity factor which is applied during the final stages of fatigue crack extension

2.5

crack tip opening displacement (CTOD)

the displacement of the surfaces of a crack normal to the original (undeformed) crack plane at the tip of the fatigue precrack, expressed in mm

2.6

critical CTOD

value of CTOD associated with a particular type of crack extension (see clause 3)

2.7

J integral

a mathematical expression for a line or surface integral that encloses the crack front from one crack surface to the other, used to characterize the local stress-strain field around the crack front [1], expressed in J/mm^2 ⁴⁾

³⁾ $0.031\ 6 \text{ MPa}\cdot\text{m}^{0.5} = 1 \text{ N}\cdot\text{mm}^{-1.5} = 0.031\ 6 \text{ MN}\cdot\text{m}^{-1.5}$.

⁴⁾ $1 \text{ J}/\text{mm}^2 = 1 \text{ MJ}/\text{m}^2$.