



BSI Standards Publication

European certified reference materials (EURONORM-CRMs) for the determination of the chemical composition of iron and steel products prepared under the auspices of the European Committee for Iron and Steel Standardization (ECIS)

National foreword

This Published Document is the UK implementation of CEN/TR 10317:2014. It supersedes PD CEN/TR 10317:2013 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/102, Methods of Chemical Analysis for Iron and Steel.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.

Published by BSI Standards Limited 2014

ISBN 978 0 580 84752 3

ICS 71.040.30; 77.150.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 December 2014.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

European certified reference materials (EURONORM-CRMs) for
the determination of the chemical composition of iron and steel
products prepared under the auspices of the European
Committee for Iron and Steel Standardization (ECISS)

Matériaux de référence certifiés européens (EURONORM-
MRC) destinés à la détermination de la composition
chimique des produits en acier et en fonte préparés sous
les auspices du comité européen de normalisation du fer et
de l'acier (ECISS)

Europäische zertifizierte Referenzmaterialien
(EURONORM-ZRMs) für die Bestimmung der chemischen
Zusammensetzung von Eisen- und Stahlerzeugnissen,
hergestellt unter der Schirmherrschaft des Europäischen
Komitees für Eisen- und Stahlnormung (ECISS)

This Technical Report was approved by CEN on 10 May 2014. It has been drawn up by the Technical Committee ECISS/TC 102.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Classification of EURONORM-CRMs	5
3 Preparation of the samples.....	6
3.1 EURONORM-CRMs of cast and wrought materials.....	6
3.2 EURONORM-CRMs of non-metallic materials	6
4 Certification	7
4.1 Main rules	7
4.2 Main content of the certificates.....	7
5 Sample presentation	9
6 Distribution of EURONORM-CRMs	9
7 Details of current EURONORM-CRMs	10
Bibliography.....	11

Foreword

This document (CEN/TR 10317:2014) has been prepared by Technical Committee ECISS/TC 102 "Methods of chemical analysis for iron and steel", the secretariat of which is held by SIS.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TR 10317:2013.

In comparison with the previous edition, CEN/TR 10317:2013, significant technical changes were made to the introduction and Clause 5 following the withdrawal of Bureau of Analysed Samples Limited from the Euronorm-CRM Producers' Group in 2013.

Currently in preview, click buy full version.

Introduction

In accordance with the definition in ISO Guide 30, Amendment 1:2008, a Certified Reference Material (CRM) as described in this CEN Technical Report is a “reference material characterized by a metrologically valid procedure for one or more specified properties, accompanied by a certificate that provides the value of the specified property, its associated uncertainty, and a statement of metrological traceability”. Furthermore, it is accompanied by a certificate issued by the producing organization on behalf of the Co-ordinating Committee (COCOR) of ECISS after approval by the participating laboratories and all the producing organizations:

- a) France:
 - 1) ArcelorMittal Maizières Research SA (AMMZ) [former Institut de Recherches de la Sidérurgie Française (IRSID)],
 - 2) Centre Technique des Industries de la Fonderie (CTIF);
- b) Germany: Iron and Steel CRM Working Group (AGZRM) comprising:
 - 1) BAM Bundesanstalt für Materialforschung und -prüfung,
 - 2) Max-Planck-Institut für Eisenforschung (MPI),
 - 3) Stahlinstitut VDEh;
- c) Nordic Countries: Nordic CRM Working Group, (NCRMWG) comprising:
 - 1) Swerea KIMAB [former Swedish Institute for Metals Research (SIMR)],
 - 2) Jernkontoret.

NOTE Bureau of Analysed Samples Ltd (BAS) - United Kingdom – was a member of the EURONORM-CRM Producer's Group from 1975 until 2013.

Since 1968, EURONORM-CRMs have been analysed by laboratories in most countries in the European Union (EU) or former European Community (EC).

Pending their eventual replacement by EURONORM-CRMs, a number of former national CRMs prepared, analysed and certified by laboratories in Germany, France and the United Kingdom respectively, were accepted as EURONORM-CRMs after their accuracy had been checked by other European laboratories. This procedure ceased in 1990.

1 Scope

This Technical Report describes the classification, method of sample preparation, certification main rules and certificate content of the EURONORM-CRMs.

It also details the sample presentation of the various producers' organizations and the distributing sources.

2 Classification of EURONORM-CRMs

EURONORM-CRMs, prepared under the auspices of ECISS, are classified into two main groups:

- cast and wrought materials: irons, steels, special alloys and ferro-alloys;
- non-metallic materials: raw materials (ores, concentrates, additives and refractories) and by-products (slags, dusts and similar materials).

Besides this first generic classification, EURONORM-CRMs are grouped into the following categories:

a) From 001 to 099 – high purity irons and unalloyed steels

Normally no element has a content (mass fraction) greater than the limit value in the following list:

- 1) silicon, limit value 1,0 %;
- 2) manganese, limit value 1,5 %;
- 3) chromium and nickel, limit value for each 0,5 %;
- 4) cobalt, copper and tungsten, limit value for each 0,3 %;
- 5) other elements, limit value for each 0,1 %;
- 6) boron, carbon, phosphorus, lead and sulphur, no limit value.

b) From 101 to 199 – low alloy steels

The content of one or more elements is greater than the limit given for unalloyed steels but none exceeds 5 %. The sum of these alloying elements remains under 10 %.

c) From 201 – 299 – high alloyed steels

The content of one or more elements is greater than 5 % or the sum of all these alloying elements is at least 10 %. Nevertheless the iron content will normally be greater than 50 %.

d) From 301 to 399 - special alloys

The iron content is less than 50 %.

e) From 401 to 499 – pig irons and cast irons

f) From 501 to 599 – ferro-alloys

g) From 601 to 699 – ores, concentrates, sinters and miscellaneous materials

h) From 701 to 799 – additives and refractories