



BSI Standards Publication

Principles of the equivalent durability procedure

Currently in preview, click buy full version

National foreword

This Published Document is the UK implementation of CEN/TR 16563:2013.

The UK participation in its preparation was entrusted to Technical Committee B/517, Concrete.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 81434 1

ICS 91.100.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 September 2013.

Amendments issued since publication

Date	Text affected
------	---------------

ICS 91.100.30

English Version

Principles of the equivalent durability procedure

Principes de la procédure de durabilité équivalente

Verfahrensgrundsätze zum Nachweis gleichwertiger
Dauerhaftigkeit

This Technical Report was approved by CEN on 22 June 2013. It has been drawn up by the Technical Committee CEN/TC 104.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Principle.....	7
5 Selection of test methods	8
6 Determination of the reference value	9
7 Determination of equivalent durability-related test performance.....	11
8 Production control.....	13
9 Evaluation and declaration of equivalent durability-related test performance	14
10 Interface with users	14
Annex A (informative) Finland —Testing of freeze-thaw resistance of candidate concrete	16
Annex B (informative) Germany.....	19
Annex C (informative) Italy	28
Annex D (informative) The Netherlands.....	29
Annex E (informative) Norway	31
Annex F (normative) The system used in Portugal and defined in their national annex to EN 206-1....	32
Annex G (informative) Spain	34
Annex H (informative) United Kingdom	36
Bibliography.....	37

Foreword

This document (CEN/TR 16563:2013) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by DIN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Currently in preview, click buy full version

Introduction

(1) The Equivalent Durability Procedure (EDP) is a scheme that builds on the traditional method of ensuring durable concrete by specifying established limiting values in terms of maximum w/c ratio, minimum cement content etc. Essentially, a reference value is determined and a candidate concrete can be confirmed as being of equivalent performance where testing and other appropriate assessments are made to demonstrate equivalent performance with this reference value or reference concrete. The reference value is determined based on concretes that satisfy fully the limiting value specification valid in the place of use and are representative of concretes that are successfully used in the local environment as providing a satisfactory service-life. To be considered a viable alternative, the proposed candidate concrete need to have a test performance that equals, or is better than, the reference value when tested by the same method and at the same age as used to establish the reference performance. Such a comparison leads to equivalent performance in the test at the age of testing. As the rate of improvement in resistance is not constant between concretes, the reference value will be appropriate for the constituents used in the candidate concrete.

(2) No relatively short-term laboratory test will give a precise quantitative indication of in-situ performance of in-situ concrete. One reason for this is that concrete will continue to gain strength and resistance to the permeation of aggressive species in most natural environments, e.g. concrete will increase its resistance to the permeation of chloride ions with time, albeit at an ever decreasing rate. Such changes in performance over time, collectively called 'ageing effects', need to be taken into account when determining if the candidate concrete will provides an equivalent durability over the service-life.

NOTE With respect to durability, the changes can be positive or negative. For example, reaction with seawater may result in a surface layer that increasingly inhibits the penetration of chloride ions and hence improve durability. On the other hand, carbonation of concrete may release chlorides ions that were previously bound into the hydrate structure and, as these are then free to migrate towards any reinforcement, the durability may be reduced.

(3) Some CEN members have established national EDP type procedures which provide results that are likely to be reasonably indicative of in-situ performance or procedures whereby equivalent durability may be safely assumed for defined sets of materials. See Annex A to Annex H for some examples.

(4) This Technical Report provides guidance to national Standards Bodies who want to establish an EDP in their national provisions to EN 206.

1 Scope

This Technical Report sets out the principles of the equivalent durability procedure. It provides guidance on the selection of the reference value, production control, evaluation of conformity and the exchange of information between the parties.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, *Methods of testing cement — Part 1: Determination of strength*

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 206-1, *Concrete — Part 1: Specification, performance, production and conformity criteria*

EN 450-1, *Fly ash for concrete — Part 1: Definition, specifications and conformity criteria*

EN 480-11, *Admixtures for concrete, mortar and grout — Test methods — Part 11: Determination of air void characteristics in hardened concrete*

EN 933-9, *Tests for the geometrical properties of aggregates — Part 9: Assessment of fines — Methylene blue test*

EN 1992-1-1, *Eurocode 2 — Design of concrete structures — Part 1-1: General rules, and rules for buildings*

EN 12350-1, *Testing fresh concrete — Part 1: Sampling*

EN 12390-2, *Testing hardened concrete — Part 2: Making and curing specimens for strength tests*

EN 12390-3, *Testing hardened concrete — Part 3: Compressive strength of test specimens*

EN 12390-8, *Testing hardened concrete — Part 8: Depth of penetration of water under pressure*

CEN/TS 12390-9, *Testing hardened concrete — Part 9: Freeze-thaw resistance — Scaling*

CEN/TS 12390-10, *Testing hardened concrete — Part 10: Determination of the relative carbonation resistance of concrete*

CEN/TS 12390-11, *Testing hardened concrete — Part 11: Determination of the chloride resistance of concrete, unidirectional diffusion*

EN 12620, *Aggregates for concrete*

EN 1326-1, *Silica fume for concrete — Part 1: Definitions, requirements and conformity criteria*

EN 13295, *Products and systems for the protection and repair of concrete structures — Test methods — Determination of resistance to carbonation*

EN 13369, *Common rules for precast concrete products*

EN 13396, *Products and systems for the protection and repair of concrete structures — Test methods — Measurement of chloride ion ingress*

EN 13670, *Execution of concrete structures*