



BSI Standards Publication

**Aluminium and aluminium
alloys — Classification of
Defects and Imperfections in
High Pressure, Low Pressure
and Gravity Die Cast Products**

National foreword

This Published Document is the UK implementation of CEN/TR 16749:2014.

The UK participation in its preparation was entrusted to Technical Committee NFE/35, Light metals and their alloys.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.
Published by BSI Standards Limited 2014

ISBN 978 0 580 86320 2
ICS 77.120.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 October 2014.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

ICS 77.120.10

English Version

Aluminium and aluminium alloys - Classification of Defects and Imperfections in High Pressure, Low Pressure and Gravity Die Cast Products

Aluminium et alliages d'aluminium - Classification des défauts et imperfections des produits moulés par coulée à haute pression, basse pression et gravité

Aluminium und Aluminiumlegierungen - Klassifikation von Fehlern und Unvollkommenheiten für Druckguss, Niederdruckguss und Schwerkraftkokillenguss

This Technical Report was approved by CEN on 9 September 2014. It has been drawn up by the Technical Committee CEN/TC 132.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	5
1 Scope	6
2 Normative references	7
3 Terms and definitions	6
4 Classification of defects and imperfections in high pressure, low pressure and gravity die cast products	8
4.1 General	8
4.2 Classification	9
5 Definition of defects and imperfections	10
5.1 General	10
5.2 Shrinkage defects and imperfections	11
5.3 Gas-related defects and imperfections	11
5.4 Filling-related defects and imperfections	12
5.5 Undesired phases	12
5.6 Thermal contraction defects and imperfections	12
5.7 Metal-die interaction defects and imperfections	13
5.8 Geometrical defects and imperfections	13
Annex A (informative) Description of defects and imperfections in High Pressure, Low Pressure and Gravity Die Cast Products	14
A.1 Internal defects and imperfections	14
A.1.1 Shrinkage defects and imperfections	14
A.1.1.1 Macroshrinkage (Type A1.1)	14
A.1.1.2 Interdendritic shrinkage (Type A1.2)	14
A.1.1.3 Layer porosity (Type A1.3)	15
A.1.2 Gas-related defects and imperfections	16
A.1.2.1 Air entrapment porosity (Type A2.1)	16
A.1.2.2 Hydrogen porosity (Type A2.2)	17
A.1.2.3 Vapor entrapment porosity (Type A2.3)	18

A.1.2.4 Lubricant/release agent entrapment porosity (Type A2.4)	18
A.1.3 Filling-related defects and imperfections	19
A.1.3.1 Cold joint (Type A3.1)	19
A.1.3.2 Lamination (Type A3.2)	20
A.1.3.3 Cold shot (Type A3.3)	20
A.1.4 Undesired phases	21
A.1.4.1 Inclusion (Type A4.1)	21
A.1.4.2 Undesired structure (Type A4.2)	21
A.1.5 Thermal contraction defects and imperfections	22
A.1.5.1 Cold crack (Type A5.1)	22
A.1.5.2 Hot tear, hot crack (Type A5.2)	23
A.2 Surface defects and imperfections	24
A.2.1 Shrinkage defects and imperfections	24
A.2.1.1 Sink (Type B1.1)	24
A.2.2 Gas-related defects and imperfections	25
A.2.2.1 Blister (Type B2.1)	25
A.2.2.2 Pinhole (Type B2.2)	25
A.2.3 Filling-related defects and imperfections	26
A.2.3.1 Cold joint and vortex (Type B3.1)	26
A.2.3.2 Lamination (Type B3.2)	27
A.2.3.3 Cold shot (Type B3.3)	27
A.2.4 Undesired phase	28
A.2.4.1 Surface deposit (Type B4.1)	28
A.2.4.2 Contaminant or inclusion (Type B4.2)	28
A.2.5 Thermal contraction defects and imperfections	29
A.2.5.1 Cold crack (Type B5.1)	29
A.2.5.2 Hot tear, hot crack (Type B5.2)	30
A.2.6 Metal/die interaction defects and imperfections	30
A.2.6.1 Erosion (Type B6.1)	30
A.2.6.2 Soldering (Type B6.2)	31

A.2.6.3 Thermal fatigue marks (Type B6.3)	31
A.2.6.4 Ejection mark (Type B6.4)	32
A.2.6.5 Corrosion of the die (Type B6.5)	32
A.3 Geometry defects and imperfections	33
A.3.1 Lack of material - Incompleteness (Type C1.1)	33
A.3.2 Excess of material - Flash (Type C2.1)	33
A.3.3 Out of tolerance - Deformation (Type C3.1)	34
Annex B (informative) Translations of defects and imperfections terminology	35
Annex C (informative) Examples of detection techniques and size of defects and imperfections	37
Bibliography	39

Foreword

This document (CEN/TR 16749:2014) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Currently in preview, click buy full version

1 Scope

This Technical Report specifies the classification of the defects and imperfections may be present in cast products manufactured by high pressure, low pressure and gravity die casting of aluminium alloys.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references the latest edition of the referenced document (including any amendments) applies.

EN 12258-1:2012, *Aluminium and aluminium alloys - Terms and definitions - Part 1: General terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12258-1:2012 and the following apply.

3.1

casting process

process in which molten metal is introduced into a mould where it solidifies

[SOURCE: EN 12258-1:2012, 3.1.1]

3.2

die casting process

casting process in which molten metal is injected under substantial pressure, typically above 70 bars, into a metal die and solidifies under this pressure

Note 1 to entry: Die casting process is also referred to as “high pressure die casting (process)” or “high pressure die casting (process)”.

[SOURCE: EN 12258-1:2012, 3.1.10]

3.3

permanent mould casting process

casting process in which molten metal is introduced by gravity or low pressure into a mould constructed of durable material, typically iron or steel

Note 1 to entry: A permanent mould casting process where the metal solidifies in a metal mould under low pressure (typically less than 1 bar above atmospheric pressure) is also referred to as a “low pressure die casting process”.

[SOURCE: EN 12258-1:2012, 3.1.9]

3.4

casting

product at or near finished shape, formed by solidification of the metal in a mould or a die

[SOURCE: EN 12258-1:2012, 2.5.1]

3.5

dendrite

crystal that has a tree-like, branching pattern, being most evident in cast metals slowly cooled through the solidification range

[SOURCE: EN 12258-1:2012, 4.5.17]