

PD CEN/TS 12697-50:2016



BSI Standards Publication

Bituminous mixtures — Test methods

Part 50: Resistance to scuffing

bsi.

National foreword

This Published Document is the UK implementation of CEN/TS 12697-50:2016.

The UK participation in its preparation was entrusted to Technical Committee B/510/1, Asphalt products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 91182 8

ICS 93.080.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 July 2016.

Amendments issued since publication

Date	Text affected
------	---------------

TECHNICAL SPECIFICATION
 SPÉCIFICATION TECHNIQUE
 TECHNISCHE SPEZIFIKATION

CEN/TS 12697-50

April 2016

ICS 93.080.20

English Version

Bituminous mixtures - Test methods - Part 50: Resistance to scuffing

Mélanges bitumineux - Méthodes d'essai - Partie 50:
 Résistance aux arrachements superficiels

Asphalt - Prüfverfahren - Teil 50: Widerstand gegen
 Oberflächeverbleis

This Technical Specification (CEN/TS) was approved by CEN on 11 February 2016 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
 COMITÉ EUROPÉEN DE NORMALISATION
 EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	5
1 Scope	6
2 Normative references	6
3 Principle	6
4 Terms, definitions, symbols and abbreviations	7
4.1 Terms and definitions.....	7
4.2 Symbols and abbreviations.....	7
5 Preparation of test specimens	7
5.1 General.....	7
5.2 Compaction of the slabs.....	7
5.3 Dimensions of the specimens.....	8
5.4 Age of the specimens.....	8
5.5 Dimensions and bulk density of the specimens.....	8
6 Loading devices	8
7 Test results	9
8 Test report	10
8.1 General.....	10
8.2 Precision.....	11
8.2.1 Repeatability.....	11
8.2.2 Reproducibility.....	11
Annex A (normative) The ARTe	12
A.1 Equipment.....	12
A.1.1 General.....	12
A.1.2 Lateral moving table.....	12
A.1.3 Set of rotating wheels.....	12
A.1.4 Slab fixation box.....	13
A.1.5 Temperature controlled room.....	13
A.1.6 Temperature measuring devices.....	13
A.1.7 Electric fan (optional).....	13
A.2 Test procedure.....	14
Annex B (normative) The Darmstadt device	18
B.1 Equipment.....	18
B.1.1 General.....	18
B.1.2 Lateral moving table.....	18
B.1.3 Test tyre.....	18

B.1.4	Asphalt specimen fixture	18
B.1.5	Heating/temperature.....	18
B.1.6	Vacuum wipe-off apparatus.....	19
B.1.7	Temperature measurements	19
B.1.8	Oven.....	19
B.2	Test procedure	19
Annex C (informative) The Rotating Surface Abrasion Test (RSAT)		21
C.1	General	22
C.2	Equipment.....	22
C.2.1	Motion mechanism.....	22
C.2.2	Test tyre	23
C.2.3	Wheel load and contact pressure.....	23
C.2.4	Wheel arm guide	24
C.2.5	Attachment of the wheel to the wheel arm.....	24
C.2.6	Rotation hinge (wheel arm guide).....	24
C.2.7	Slab holder test specimen RSAT	24
C.2.8	Bearing and rotary axle, consisting of a ring bearing	25
C.2.9	Braking mechanism	25
C.2.10	Asphalt specimen fixture	25
C.2.11	Vacuum wipe-off apparatus.....	26
C.3	Test temperature.....	26
C.3.1	Heating/temperature.....	26
C.3.2	Temperature measurements	26
Annex D (informative) The TriboRoute Device).....		29
D.1	Equipment.....	29
D.1.1	General	29
D.1.2	Load application	29
D.1.3	Lateral moving table.....	30
D.1.4	Asphalt specimen fixture	30
D.1.5	Heating/temperature.....	30
D.1.6	Vacuum wipe-off apparatus.....	31
D.2	Test procedure	31
D.2.1	Specimen preparation	31
D.2.2	Control of the specimen surface characteristics	31
D.2.3	Test performance	32
D.2.3.1	General	32

D.2.3.2 Test performed with controlled force (TRD-CF)	32
D.2.3.3 Test performed with controlled displacement rate (TRD-CD)	33
Bibliography	34

Currently in preview, click buy full version

European foreword

This document (CEN/TS 12697-50:2016) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by DIN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Currently in preview, click buy full version.

1 Scope

This European Technical Specification specifies a test method for determining the resistance to scuffing of asphalt mixtures which are used in surface layers and are loaded with high shear stresses in road or airfield pavement. These shear stresses occur in the contact area between tyre and pavement surface and can be caused by cornering of the vehicle. Due to these shear stresses, material loss will occur at the surface of these layers. The test is normally performed on asphalt layers with a high amount of air voids (e.g. porous asphalt), but can also be applied on other asphaltic mixtures. Test specimens are used either produced in a laboratory or cut from the pavement.

NOTE The test is developed to determine the resistance to scuffing for noise reducing surface layers where raveling is the normative damage criterion. The test can also be performed on other surface mixtures with a high resistance to permanent deformation. In case a mixture has a low resistance to permanent deformation, rutting can occur during the test. This can influence the test results.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-6, *Bituminous mixtures — Test methods for hot mix asphalt — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-29, *Bituminous mixtures — Test method for hot mix asphalt — Part 29: Determination of the dimensions of a bituminous specimen*

EN 12697-33, *Bituminous mixtures — Test methods for hot mix asphalt — Part 33: Specimen prepared by roller compactor*

3 Principle

Laboratory compacted asphalt specimens or asphalt specimens cut from a pavement is fixed in a test facility. In this facility, the asphalt material is loaded simultaneously with both normal and shear stresses. Due to these stresses, material loss will occur from the surface of the slab. This material loss depends on the resistance to scuffing of the tested asphalt mixture: the higher the resistance, the less material will disappear.

To determine the resistance to scuffing, two slabs or (set of) cores shall be tested. The average of both test results is reported as the resistance to scuffing.

In this Technical Specification four different kinds of loading facilities are described:

- The ART (the Aachener Raveling Tester);
- The LSD (the Darmstadt Scuffing Device);
- The RSAT (the Rotating Surface Abrasion Test) and
- The Triboroute.