



BSI Standards Publication

Environmental testing

Part 3-12: Supporting documentation and guidance — Method to evaluate a possible lead-free solder reflow temperature profile

National foreword

This Published Document is the UK implementation of IEC/TR 60068-3-12:2014. It supersedes PD IEC/TR 60068-3-12:2007 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee EPL/501, Electronic assembly technology & Printed Electronics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.
Published by BSI Standards Limited 2014

ISBN 978 0 580 85604 4
ICS 19.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 October 2014.

Amendments issued since publication

Date	Text affected
------	---------------



TECHNICAL REPORT

RAPPORT TECHNIQUE

Environmental testing –

Part 3-12: Supporting documentation and guidance – Method to evaluate a possible lead-free solder reflow temperature profile

Essais d'environnement –

Partie 3-12: Documentation d'accompagnement et guide – Méthode d'évaluation d'un profil de température possible de brasage sans plomb par refusion

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

Q

ICS 19.040

ISBN 978-2-8322-1888-4

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Basics	5
3 Boards under investigation	6
3.1 Test board approach.....	6
3.2 Production board approach.....	6
4 Temperature tolerances.....	7
4.1 Temperature tolerances in Study A.....	7
4.2 Temperature tolerance and board size influence in Study B.....	8
5 Peak form and width.....	9
5.1 Peak form and width in Study A.....	9
5.2 Reflow oven investigation in Study B.....	9
6 Classification.....	10
6.1 Device classification in Study A.....	10
6.2 Board classification in Study B.....	12
7 Consideration for a lead-free reflow temperature profile.....	13
7.1 Determined lead-free reflow temperature profile in Study A.....	13
7.2 Lead-free reflow temperature profile approach in Study B.....	14
8 Conclusion	15
Bibliography.....	16
Figure 1 – Curve shape for a peak temperature of at least 20 s at 230 °C and 1 s at 233 °C.....	6
Figure 2 – Position of the assembled devices and temperature dependence on the device position.....	7
Figure 3 – Lower and upper temperature tolerances of the reflow solder profile.....	8
Figure 4 – Temperature tolerance and board size influence.....	8
Figure 5 – Hat type peak profile with 40 s at $T_{max} - 5 K = 255 °C$ for the small devices and the PCB.....	9
Figure 6 – ΔT by different reflow oven capabilities.....	10
Figure 7 – Representative test board measurements.....	11
Figure 8 – Example of the small board (camcorder).....	13
Figure 9 – Example of the mid-size board (personal computer (PC)).....	13
Figure 10 – Lead-free reflow temperature profile for device qualification.....	14
Table 1 – Measured temperatures of devices and values including lower and upper tolerances.....	11
Table 2 – Possible temperature classification of surface mount devices.....	12
Table 3 – Proposed requirements for a lead-free reflow profile.....	14

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ENVIRONMENTAL TESTING –

**Part 3-12: Supporting documentation and guidance –
Method to evaluate a possible lead-free solder
reflow temperature profile**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, accept to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC TR 60068-3-12, which is a technical report, has been prepared by IEC technical committee 91: Electronics assembly technology.

This second edition cancels and replaces the first edition published in 2007 and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- the content has been adapted to the state-of-the-art of reflow-oven technology and termination finishes;
- minor language adjustments were performed.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
91/1158/DTR	91/1177/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60068 series, under the general title *Environmental testing*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

ENVIRONMENTAL TESTING –

Part 3-12: Supporting documentation and guidance – Method to evaluate a possible lead-free solder reflow temperature profile

1 Scope

This part of IEC 60068, which is a technical report, presents two approaches for establishing a possible temperature profile for a lead-free reflow soldering process using SnAgCu solder paste.

This process covers a great variety of electronic products, including a large range of package sizes (e.g. molded active electronic components, passive components and electromechanical components).

Study A addresses requirements needed in the production of high reliability electronic control units (ECU), as for example in automotive electronics. These requirements include measurement and production tolerances.

Study B represents consumer electronics products and includes reflow oven capability, board design and package sizes.

2 Basics

The process temperature for SnPb solder paste has a wide margin due to the liquid temperature of the solder alloy. During reflow soldering, temperature differences between components exist but are not critical. The process temperature of SnAgCu solder paste is about 20 K to 30 K higher than SnPb solder paste. Furthermore, the temperature difference between components (ΔT) becomes wider and sometimes the heat resistance temperature of components can become critical.

To avoid soldering failures which could be very harmful in safety-related applications and also generate higher failure costs, the capability of the soldering process is very important. A compromise between the temperature requirements of highly reliable solder joints and the limited solder-heat resistance of the electronic components has to be sought. In addition, the different aspects of mass production have to be considered. To achieve a reliable solder joint, the conventional reflow soldering process with eutectic SnPb solder paste is usually performed at a minimum peak temperature of about 203 °C at the coldest solder joint (i.e. at least 20 K above the liquid temperature of SnPb $T_{\text{liquid}} = 183$ °C).

The selected lead-free solder is SnAgCu with a melting point at around $T_{\text{liquid}} = 217$ °C [1]¹. It is a generally preferred material for lead-free reflow and wave soldering in mass production [2]. Using SnAgCu solder paste, it is not possible to solder the coldest solder joints at least 20 K above the liquid temperature ($T_{\text{liquid}} = 217$ °C), which would result in minimum temperatures of 237 °C. When the coldest solder joint is 237 °C, the temperature spread between small and large components, small semiconductor, and passive components, as well as the printed circuit board (PCB), will be too large for the components to survive the heat impact. Despite the aim to achieve a relatively low temperature at the coldest solder joint, the reliability of the solder joint has to be assured.

¹ Numbers in square brackets refer to the Bibliography.