



BSI Standards Publication

# Determination of long-term radiation ageing in polymers

Part 2: Procedures for predicting ageing at low dose rates

**National foreword**

This Published Document is the UK implementation of IEC/TS 61244-2:2014. It supersedes BS 7816-2:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee GEL/112, Evaluation and qualification of electrical insulating materials and systems.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.  
Published by BSI Standards Limited 2014

ISBN 978 0 580 85144 5  
ICS 17.240; 29.035.01

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 August 2014.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---



# TECHNICAL SPECIFICATION

# SPECIFICATION TECHNIQUE

**Determination of long-term radiation ageing in polymers –  
Part 2: Procedures for predicting ageing at low dose rates**

**Détermination du vieillissement à long terme sous rayonnement dans les  
polymères –  
Partie 2: Méthodes pour prédire le vieillissement à faible débit de dose**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX

V

ICS 17.240; 29.035.01

ISBN 978-2-8322-1828-0

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references .....	6
3 General .....	6
4 Power law extrapolation method.....	7
4.1 Description .....	7
4.2 Test procedure.....	7
4.3 Determination of model parameters .....	7
4.4 Limitations .....	7
5 Superposition of time dependent data .....	9
5.1 Description .....	9
5.2 Test procedure.....	9
5.3 Determination of model parameters .....	10
5.4 Limitations .....	13
6 Superposition of DED data.....	14
6.1 Description .....	14
6.2 Test procedure.....	14
6.3 Evaluation.....	14
6.4 Limitations .....	15
Annex A (informative) Behaviour of polymeric materials in radiation environments .....	17
Annex B (informative) Examples of use of the power law method .....	19
B.1 General.....	19
B.2 Polypropylene filaments .....	19
B.3 Crosslinked polyethylene (XLPE) .....	19
Annex C (informative) Use of the superposition principle .....	21
Annex D (informative) Examples of use of the superposition of time dependent data .....	23
D.1 Ethylene propylene (EPDM) elastomer.....	23
D.2 Nitrile elastomer .....	23
D.3 Ethylene vinyl acetate (EVA) polymer .....	23
Annex E (informative) Examples of use of the superposition of dose to equivalent damage (DED) data .....	26
E.1 General.....	26
E.2 Neoprene cable jacket.....	26
E.3 Chloro sulphonated polyethylene (CSPE) cable jacket .....	26
E.4 Crosslinked polyolefin (XLPO) cable insulation .....	26
E.5 Poly vinyl chloride (PVC) cable jacket.....	26
Bibliography .....	30
Figure 1 – Interpolation of the end-point dose (schematic), showing a plot of relative elongation at break plotted vs dose with interpolation of DED values at 0,75 and 0,5.....	8
Figure 2 – Extrapolation of end-point dose to lower dose rates (schematic) C showing the plot of DED values vs dose rate.....	8
Figure 3 – Limitations – Extrapolation of DED near thermal ageing limit (schematic) .....	9
Figure 4 – Determining shift factors a (T,0) for thermal ageing .....	10
Figure 5 – Superposition of data to yield master curve.....	11

Figure 6 – Determination of activation energy $E$ .....	11
Figure 7 – Determination of shift factors $a(T, \dot{D})$ for combined thermal-radiation ageing, relative to the master curve in Figure 4 .....	12
Figure 8 – Fitting experimental values of $a(T, \dot{D})$ to the empirical model Equation (2).....	13
Figure 9 – Calculated DED using Equation (5).....	13
Figure 10 – DED values under combined thermal-radiation conditions (schematic).....	15
Figure 11– Superposition of DED data (schematic).....	15
Figure A.1 – Schematic illustrating the types of dose rate effects which can occur in radiation aged polymeric materials .....	18
Figure B.1 – Elongation at break of polypropylene irradiated in air (from [10]) .....	19
Figure B.2 – Extrapolation of end-point dose from data in Figure B.1 .....	20
Figure B.3 – Dose required to reach 100 % elongation at 20 °C for an XLPE cable insulation material [11].....	20
Figure C.1 – Schematic – Superposition principle for thermal ageing .....	21
Figure C.2 – Schematic – Superposition principle for combined thermal-radiation ageing .....	22
Figure D.1 – Experimental data for EPDM elastomer fitted to the superposition model.....	24
Figure D.2 – Calculated DED for 50 % compression set at 20 °C .....	24
Figure D.3 – Calculated DED for 50 % compression set at 40 °C .....	25
Figure D.4 – Calculated DED for $e/e_0 = 0,5$ .....	25
Figure E.1 – Superposition of DED data at 50 °C for neoprene cable jacket material [7].....	27
Figure E.2 – Superposition of DED data for several different CSPE cable jacket materials .....	28
Figure E.3 – Superposition of DED data for a XLPO cable insulation material [7].....	29
Figure E.4 – Superposition of DED data for PVC showing complex dose rate dependence – Homogeneous oxidation data only .....	29

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**DETERMINATION OF LONG-TERM RADIATION AGEING IN POLYMERS –****Part 2: Procedures for predicting ageing at low dose rates**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 61244-2, which is a technical specification, has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems.

This second edition cancels and replaces the first edition published in 1996 and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) examples and background information moved to annexes;
- b) examples updated with more recent references.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
112/288/DTS	112/305/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 61244 series, published under the general title *Determination of long-term ageing in polymers*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://www.eiec.ch>" in the data related to the specific publication. At this date, the publication will be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## DETERMINATION OF LONG-TERM RADIATION AGEING IN POLYMERS –

### Part 2: Procedures for predicting ageing at low dose rates

#### 1 Scope

This part of IEC TS 61244, which is a technical specification, applies to procedures for predicting ageing of polymeric materials at low dose rates.

The object is to present three methods which can be used to extrapolate data obtained from high dose rate experiments to the low dose rates typical of service conditions. These methods assume that homogeneous oxidation has been achieved under the test conditions. The techniques described in the following clauses are methods which have been found to be useful for a range of elastomeric, thermoplastic and thermoset materials. The procedures require a considerable number of test data to enable predictions to be made under low dose rate conditions.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60544-2, *Guide for determining the effects of ionizing radiation on insulating materials – Part 2: Procedures for irradiation and test*

IEC 61244-1, *Determination of long-term radiation ageing in polymers – Part 1: Techniques for monitoring diffusion-limited oxidation*

#### 3 General

The general guidelines of IEC 60544-2 shall be used in the selection of specimen types, radiation source, dosimetry and temperature control. All irradiations shall be carried out in air or at constant oxygen overpressure, although as noted in IEC 61244-1, oxygen overpressure techniques entail some risk of over-ageing the samples. The homogeneity of oxidation through the specimen thickness can be checked using profiling techniques such as those described in IEC 61244-1. The test report shall include details of the irradiation source, dose rate, atmosphere, temperature, sample type and thickness.

All of the procedures described require extensive data obtained over considerable periods of time. Each method has been found to be of practical use within its limitations, but none of the methods can be used where there is more than one mechanism operating with different apparent activation energies.

The power-law extrapolation method (Clause 4) is the simplest of the predictive techniques and requires the least amount of experimental data. This procedure cannot be used at dose rates low enough for thermal ageing to dominate, but appears to be valid for extrapolation of data obtained at near ambient temperatures (20 °C to 30 °C) for polymers such as polyolefins.

Because of the limited data involved, caution should be used in extrapolating by more than a factor of 10 in dose rate.