



BSI Standards Publication

**Iron ores — Determination
of chlorine content — X-ray
fluorescence spectrometric
method**

National foreword

This Published Document is the UK implementation of ISO/TR 16043:2015.

The UK participation in its preparation was entrusted to Technical Committee ISE/58, Iron ores.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.

Published by BSI Standards Limited 2015

ISBN 978 0 580 86762 0

ICS 73.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 November 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

TECHNICAL
REPORT

ISO/TR
16043

First edition
2015-10-15

**Iron ores — Determination of
chlorine content — X-ray fluorescence
spectrometric method**

*Minerais de fer — Dosage du chlore — Méthode par spectrométrie de
fluorescence de rayons X*



Reference number
ISO/TR 16043:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015. Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Principle	1
3 Reagents and materials	1
4 Apparatus	2
5 Sampling and samples	3
5.1 Laboratory sample.....	3
5.2 Preparation of test sample.....	3
5.2.1 Preparation of pre-dried test samples.....	3
5.2.2 Ores having significant contents of combined water or oxidizable compounds.....	4
6 Procedure	4
6.1 Preparation of discs.....	4
6.1.1 General.....	4
6.1.2 Weighing.....	4
6.1.3 Mixing.....	5
6.1.4 Fusion.....	5
6.1.5 Casting.....	5
6.1.6 Calibration discs.....	5
6.1.7 Test discs.....	6
6.1.8 Visual inspection.....	6
6.1.9 Disc storage.....	6
6.1.10 Cleaning of platinum ware.....	6
6.2 Measurements.....	7
6.2.1 General.....	7
6.2.2 Analytical lines.....	7
6.2.3 XRF generator settings.....	7
6.2.4 Crystals.....	7
6.2.5 Counting times.....	7
6.2.6 Collimators.....	8
6.2.7 Simultaneous α -type instruments.....	8
6.2.8 Sample holders.....	8
6.2.9 Subsequent determinations.....	8
7 Calculation of results	8
7.1 General.....	8
7.2 Correction for background.....	9
7.3 Calibration.....	9
8 General treatment of results	10
8.1 Acceptability of background equivalent concentration (BEC).....	10
8.2 Repeatability and permissible tolerances.....	10
8.3 Determination of analytical result.....	11
8.3.1 Mean of duplicates.....	11
8.3.2 Between-laboratories precision.....	11
8.4 Check for trueness.....	11
8.5 Calculation of final result.....	12
8.6 Oxide factor.....	12
9 Test report	12
Annex A (informative) Preparation of flux A	13
Annex B (informative) Preparation of flux B	15

Annex C (informative) Flowsheet of the procedure for the acceptance of analytical values for test samples	16
Annex D (informative) Derivation of repeatability and permissible tolerance	17
Bibliography	18

Currently in preview, click buy full version

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/IEC 102, *Iron ore and direct reduced iron*, Subcommittee SC 2, *Chemical analysis*.

Introduction

This Technical Report summarizes the results of inter-laboratory testing for the determination of chlorine in iron ores by X-ray fluorescence. The method was developed by Technical Committee ISO/TC 102, *Iron ore and direct reduced iron*, Subcommittee SC 2, *Chemical analysis*. As no other methods for determination of chlorine exist in ISO/TC 102, the method was designed to complement method ISO 9516-1. A method for water soluble chloride does exist (ISO 9517) but the range of application of ISO 9517 is significantly less than the XRF method described in this Technical Report. The method described in this Technical Report represents the first attempt of the committee to determine total chloride.

Evaluation of the data from the inter-laboratory test indicated that the method could not be considered for publication as an International Standard as the precision of the method was less good than the precision of the method for water soluble chloride described in ISO 9517. In addition, a test of the trueness of the method was not possible as no potential test samples that were certified for Cl were available. Although the test samples used were characterized using neutron activation, the XRF values were biased with respect to the neutron activation values and the neutron activation method itself was not considered to be a standard method.

Although the method was not considered suitable for publication as an International Standard, it was agreed that the method was otherwise suitable for use in the industry and the committee agreed that it should be published as a Technical Report.

Iron ores — Determination of chlorine content — X-ray fluorescence spectrometric method

WARNING — This Technical Report may involve hazardous materials, operations and equipment. This Technical Report does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this Technical Report to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This Technical Report sets out a wavelength dispersive X-ray fluorescence procedure for the determination of chlorine in iron ores.

The method is applicable to a concentration range of 0,027 % to 1,15 % of chlorine in iron ores regardless of mineralogical type.

It is not intended that this method be used for the purpose of trade in iron ores due to the precision of the method.

2 Principle

The glass discs for X-ray fluorescence measurement are prepared by incorporating the test portion of the iron ore sample, via fusion, into a borate glass disc using a casting procedure. By using a fused glass disc, particle size effects are eliminated.

The method is applicable to data from simultaneous and sequential X-ray fluorescence spectrometers.

Calibration is carried out using pure chemicals, with chlorine added as a stock solution of sodium chloride. Because the oxygen of the flux is the dominant element in the glass disc, and because oxygen is a heavy absorber to Cl K α , matrix effects are small and calibration is based on a linear relationship between concentration and measured fluorescent intensity. Background measurements are made to determine net line intensities.

3 Reagents and materials

3.1 During analysis, use only reagents of recognized high purity.

Where reagents have been ignited, they should be covered during cooling in the desiccator and weighed as soon as possible.

3.2 Iron (III) oxide (Fe₂O₃), nominally 99,999 % Fe₂O₃.

The iron (III) oxide should contain less than 3 $\mu\text{g/g}$ of chlorine. It should initially be heated at 1 000 °C in a platinum crucible for a minimum of 12 h to reduce contaminant concentrations and cooled in a desiccator. Subsequently, if required, it should be re-ignited at 1 000 °C for 1 h and cooled in a desiccator.

3.3 Sodium chloride (NaCl), 13,2 g/l solution.

Analytical grade sodium chloride should be dried at 105 °C for 1 h and cooled in a desiccator. Weigh 13,2 g dried sodium chloride into a 1 000 ml one-mark volumetric flask and dilute to volume.

3.4 Desiccant, should be a freshly-regenerated self-indicating silica gel.