



BSI Standards Publication

Nanotechnologies — Characterization of cellulose nanocrystals

National foreword

This Published Document is the UK implementation of ISO/TR 19716:2016.

The UK participation in its preparation was entrusted to Technical Committee NTI/1, Nanotechnologies.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 90974 0

ICS 07.030

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 May 2016.

Amendments issued since publication

Date	Text affected
------	---------------

TECHNICAL
REPORT

PD ISO/TR 19716:2016

ISO/TR
19716

First edition
2016-05-01

**Nanotechnologies — Characterization
of cellulose nanocrystals**

Nanotechnologies — Caractérisation des nanocristaux de cellulose



Reference number
ISO/TR 19716:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016. Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Terms and definitions	1
3 Symbols and abbreviated terms	2
4 Production of cellulose nanocrystals (CNCs)	3
5 Composition	6
5.1 Chemical composition.....	6
5.2 Surface functional groups.....	7
5.2.1 Determination of sulfate half-esters.....	7
5.2.2 Determination of carboxylic acids.....	11
5.3 Degree of polymerization.....	12
5.4 Crystallinity.....	13
5.4.1 General.....	13
5.4.2 X-ray diffraction.....	14
5.4.3 Nuclear magnetic resonance.....	16
5.4.4 Vibrational spectroscopy.....	18
5.4.5 Crystallinity measurements for CNCs.....	18
5.5 Moisture content.....	20
5.6 Contaminants.....	20
5.6.1 General.....	20
5.6.2 Residual impurities derived from cellulosic biomass.....	21
5.6.3 Metal ions.....	21
5.6.4 Detection of contaminants by X-ray photoelectron spectroscopy.....	21
6 CNC Morphology	22
6.1 Distributions of length and cross-section from microscopy.....	22
6.1.1 General.....	22
6.1.2 Electron microscopy.....	23
6.1.3 Atomic force microscopy.....	25
6.1.4 Image analysis considerations.....	27
6.1.5 Microscopy size distributions for CNCs.....	27
6.2 Size measurement by dynamic light scattering (DLS).....	31
7 CNC Surface characteristics	33
7.1 Specific surface area.....	33
7.2 Surface charge.....	34
8 Miscellaneous	35
8.1 Thermal properties.....	35
8.2 Viscosity.....	38
9 Concluding comments	38
Bibliography	40

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 229, *Nanotechnologies*.

Introduction

Cellulose nanomaterials, including cellulose nanocrystals (CNCs) and cellulose nanofibrils, are anticipated to have significant commercial impact. Cellulose nanocrystals are extracted from naturally occurring cellulose, primarily from wood and annual plants, by acid hydrolysis, or chemical or enzymatic oxidation.[1][2][3] Their production from cellulose sources, such as wood pulps makes them a candidate for use as a potentially non-toxic, biodegradable and sustainable nanomaterial. Furthermore, the recent demonstration of the feasibility of CNC production on a large scale and the availability of infrastructure for harvesting raw materials will facilitate their commercial development. CNCs and cellulose nanofibrils are produced in a number of countries on pilot, pre-commercial or commercial scales. Estimates of the market potential for cellulosic nanomaterials are as high as 35 million metric tons annually, depending on the predicted applications and the estimated market penetration.[4][5] Standards for characterization of CNCs are required for material certification to allow sustained commercial development and applications.

Cellulose nanocrystals are nanorods that have high aspect ratio, surface area and mechanical strength and assemble to give a chiral nematic phase with unique optical properties. They are smaller than cellulose nanofibrils and have a higher crystalline content. These properties, plus the ability to control CNC surface charge and chemistry for dispersion in a variety of matrices, lead to potential applications in many areas including nanocomposite materials, paints and adhesives, optical films and devices, rheology modifiers, catalysts and biomedical products. There are currently no International Standards for this emerging commercial nanomaterial, although an ISO/TC 229 project on terminology is in progress, a Canadian National Standard (CSA Z5100) was published in 2014 and two CNC reference materials were released in 2013. This Technical Report reviews information on sample preparation, data collection and data analysis/interpretation for the measurements that are predicted to be important for the development of commercial products containing CNCs. Information for the following CNC properties is included: composition (crystallinity, surface functional groups, degree of polymerization and contaminants), morphology as assessed by microscopy and light scattering methods, surface charge and specific surface area, viscosity and thermal stability. The Technical Report reviews various approaches that have been used for specific properties, but does not recommend standard methods or provide detailed information on the techniques. The coverage is restricted to CNCs as produced and does not extend to post-production modified CNCs or CNC-enhanced materials or products.

Currently in preview, click buy full version

Nanotechnologies — Characterization of cellulose nanocrystals

1 Scope

This Technical Report reviews commonly used methods for the characterization of cellulose nanocrystals (CNCs), including sample preparation, measurement methods and data analysis. Selected measurands for characterization of CNCs for commercial production and application are covered. These include CNC composition, morphology and surface characteristics.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply

2.1

agglomerate

collection of weakly or medium strongly bound particles where the resulting external surface area is similar to the sum of the surface areas of the individual components

Note 1 to entry: The forces holding an agglomerate together are weak forces, for example, van der Waals forces or simple physical entanglement.

Note 2 to entry: Agglomerates are also termed secondary particles and the original source particles are termed primary particles.

[SOURCE: ISO/TS 80004-2:2015, 3.3]

2.2

aggregate

particle comprising strongly bonded or fused particles where the resulting external surface area is significantly smaller than the sum of surface areas of the individual components

Note 1 to entry: The forces holding an aggregate together are strong forces, for example, covalent bonds, or those resulting from sintering or complex physical entanglement, or otherwise combined former primary particles.

Note 2 to entry: Aggregates are also termed secondary particles and the original source particles are termed primary particles.

[SOURCE: ISO/TS 80004-2:2015, 3.4]

2.3

nanocrystal

nano-object with a crystalline structure

[SOURCE: ISO/TS 80004-2:2015, 4.15]

2.4

nanofibre

nano-object with two external dimensions in the nanoscale and the third dimension significantly larger

Note 1 to entry: The largest external dimension is not necessarily in the nanoscale.

Note 2 to entry: The terms nanofibril and nanofilament can also be used.