



BSI Standards Publication

Carbon dioxide capture — Overview of carbon dioxide capture technologies in the cement industry

National foreword

This Published Document is the UK implementation of ISO/TR 27922:2021.

The UK participation in its preparation was entrusted to Technical Committee PSE/265, Carbon Capture Transportation and Storage.

A list of organizations represented on this committee can be obtained on request to its committee manager.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2021
Published by BSI Standards Limited 2021

ISBN 978 0 539 13349 3

ICS 13.020.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 28 February 2021.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**Carbon dioxide capture — Overview of
carbon dioxide capture technologies
in the cement industry**

*Captage du dioxyde de carbone — Vue d'ensemble des technologies de
captage du dioxyde de carbone dans l'industrie du ciment*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2021. Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 CO₂ and the cement industry	1
4.1 Cement manufacture.....	1
4.2 CO ₂ emissions from the cement industry.....	3
4.2.1 Production process description.....	3
4.2.2 Process emissions from calcination.....	3
4.2.3 Combustion emissions.....	4
4.2.4 Emissions compared to other sectors.....	4
4.3 CO ₂ purification after capture.....	4
4.4 Abatement technologies in general.....	4
5 Overview of CO₂ capture technologies	5
5.1 Absorption with amines.....	5
5.2 Absorption with chilled ammonia.....	6
5.3 Sorbent-based adsorption technologies.....	6
5.4 Oxy-fuel combustion technology.....	7
5.5 Pressure swing adsorption separation technology.....	8
5.6 Separation with membranes.....	9
5.7 Direct separation.....	10
5.8 Calcium looping.....	11
6 Overview and assessment	13
6.1 Assessment factors of CO ₂ capture technologies.....	13
6.2 Case study of technological and economic evaluation of CO ₂ capture technologies.....	14
6.3 Ability to retrofit existing cement plants with CO ₂ capture technologies.....	15
7 Final considerations	15
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 265, *Carbon dioxide capture, transportation, and geological storage*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Concrete is the most-used manufactured substance on the planet in terms of volume. For example, it is used to build homes, schools, hospitals, workplaces, roads, railways and ports, and to create infrastructure to provide clean water, sanitation and energy. These are important for quality of life, public health, and social and economic well-being.

Raw materials for concrete are abundant and available in most parts of the world. Concrete is affordable, strong, durable and resilient to fire, floods and pests. It has the flexibility to produce complex and massive structures. There is currently no other material that is available in the quantities necessary to meet the demand for buildings and infrastructure.

Cement is used to manufacture concrete. It is described as the glue that binds the aggregates together. The demand for concrete, and therefore for cement, is expected to increase, by 12 % to 23 % by 2050 compared to 2014, as economies continue to grow, especially in Asia.

Increasing global population, urbanisation patterns and infrastructure development will increase global cement production. The use of concrete and cement is expected to become more efficient, and concrete pours at the application phase are expected to decrease. The cement sector faces the challenge of meeting an increasing demand for its product while cutting direct CO₂ emissions from its production [2]. The cement industry is a large emitter of CO₂ worldwide. The industry is committed to reduce their carbon footprint to meet the targets of the 'Paris Agreement' on climate change.

Process emissions arising from the production of cement clinker present a fundamental challenge to decarbonization of cement. In normal cement production processes, these process emissions are in the range of 500 kg CO₂/tonne clinker to 540 kg CO₂/tonne clinker[3], corresponding to 250 kg CO₂ to 500 kg CO₂ per tonne of cement depending on the type of cement. Replacement of limestone as raw materials with alternative raw materials with lower carbonate content can reduce these process emissions, but availability of these alternatives is limited, and the replacement potential is also limited (depending on required cement qualities).

Combustion emissions are another contributor to CO₂ emissions in addition to the process emissions. Replacement of carbon-based fuels by non-carbon-based energy sources and thermal energy from biomass sources (being considered as CO₂ neutral) will contribute to lowering the carbon intensity of the energy supply for the cement industry in the future.

One way to reduce CO₂ emissions is capturing CO₂ that is released in the production of cement (both direct emissions during the production process and emissions related to local energy production). CO₂ capture is an emerging approach for CO₂ abatement in the cement industry. It means that CO₂ arising from the combustion of fuels and from the treatment of raw materials could be captured and permanently stored or re-used. The integration of CO₂ capture equipment typically increases the specific energy intensity of cement manufacture, as additional energy is needed to operate the CO₂ capture plant, followed by drying, purification and compression of the captured CO₂ for transportation, (geological) storage and/or utilization[2]. CO₂ transportation, (geological) storage and utilization are beyond the scope of this document.

To date, no large-scale CO₂ capturing technologies have been installed in the cement industry. However, different technologies are under development to support the cement industry in achieving their objectives. Various cement companies participate in one or more research, development and/or demonstration projects in the field of CO₂ capture. These projects provide useful information about the application of the various technologies in the cement industry.

To facilitate the assessment and comparison of the different CO₂ capturing technologies, this document summarizes these technologies that are currently under development. This summary supplements and updates the information provided in ISO/TR 27912:2016, Clause 10 on capture from cement production processes. This document will inform the cement industry and their stakeholders on CO₂ capture technology options and other relevant aspects.

CO₂ capture will be an item of interest for all cement producers in the years to come^[5]. Currently, about 2 000 cement plants with relevant CO₂ emissions are operating worldwide^[14] with the majority of these plants being located in Asia. CO₂ capture implementation in the cement industry at global level would need a transport and storage infrastructure to facilitate the decarbonization of cement plants not located close to a geological storage facility or CO₂ use facility. Together with the investments in CO₂ capture facilities, this will be a major cost factor for the cement industry.

Currently in preview, click buy full version

Carbon dioxide capture — Overview of carbon dioxide capture technologies in the cement industry

1 Scope

This document provides an overview of technologies that are under development to capture carbon dioxide (CO₂) that is generated during cement manufacture.

This document is intended to inform users about the different technologies, including the characteristics, the maturity and the boundaries of these technologies.

This document is applicable to organizations involved in the cement industry and other stakeholders (e.g. policy makers).

This document addresses technologies for CO₂ capture that have potential applications in the cement industry. This document does not address CO₂ transport, CO₂ storage or CO₂ utilization.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 27917, *Carbon dioxide capture, transportation and geological storage — Vocabulary — Cross cutting terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 27917 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 CO₂ and the cement industry

4.1 Cement manufacture

Cement manufacture is a three-stage process: raw materials preparation, clinker production and clinker grinding with other components to produce cement. [Figure 1](#) illustrates the process of manufacturing cement. Different raw materials are mixed and milled into a homogeneous powder, from which clinker is produced in high-temperature kilns where direct emissions of CO₂ occur. Calcium oxide from the calcination of limestone is a precursor to the formation of calcium silicates that gives cement its strength^[2].