



BSI Standards Publication

Geosynthetics — Guidelines for the assessment of durability

National foreword

This Published Document is the UK implementation of ISO/TS 13434:2020. It supersedes DD ISO/TS 13434:2008, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/553, Geosynthetics.

A list of organizations represented on this committee can be obtained on request to its committee manager.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 539 04964 0

ICS 59.080.70

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 November 2020.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

TECHNICAL
SPECIFICATION

ISO/TS
13434

Second edition
2020-10-30

**Geosynthetics — Guidelines for the
assessment of durability**

Géosynthétiques — Lignes directrices concernant la durabilité



Reference number
ISO/TS 13434:2020(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020. Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	vi
1 Scope	1
2 Normative references	1
3 Terms, definitions, symbols and abbreviated terms	1
3.1 Terms and definitions.....	1
3.2 Symbols.....	1
3.3 Abbreviated items.....	2
4 Generalized procedure	3
4.1 General.....	3
4.2 Available and required properties.....	4
4.2.1 Condition of acceptability.....	4
4.2.2 Development of the required and available properties with time.....	4
4.3 Design life.....	6
4.4 Margin of safety.....	6
4.5 End of life (function).....	6
4.6 Durability study.....	7
5 Constituents of geosynthetics	7
5.1 Types of geosynthetic.....	7
5.1.1 Polymeric durability considerations.....	7
5.1.2 Geotextiles.....	8
5.1.3 Geosynthetic barriers or polymeric and bituminous geosynthetic barriers.....	8
5.1.4 GBR-C.....	8
5.1.5 Geoblankets (GBL).....	8
5.1.6 Geogrids.....	9
5.1.7 Geonets.....	9
5.1.8 Geocells.....	9
5.1.9 Geomats.....	9
5.1.10 Geocomposites.....	9
5.1.11 Geof foam.....	9
5.1.12 Geospacers.....	9
5.2 Individual polymer types.....	9
5.2.1 General.....	9
5.2.2 Polypropylene (PP).....	10
5.2.3 Flexible polypropylene (fPP).....	10
5.2.4 Polyethylene (PE).....	10
5.2.5 Polyesters (i.e. PET, PEN).....	10
5.2.6 Flexible polyvinyl chloride (PVC-P).....	10
5.2.7 Polyamides (PA).....	11
5.2.8 Ethylene propylene diene monomer (EPDM).....	11
5.2.9 Ethylene interpolymer alloy (EIA).....	11
5.2.10 Chlorinated polyethylene (CPE).....	11
5.2.11 Chlorosulfonated polyethylene (CSPE).....	11
5.2.12 Bitumen.....	11
5.2.13 Aramid.....	12
5.2.14 Polyvinyl alcohol (PVAL).....	12
5.2.15 Polystyrene (PS).....	12
5.2.16 Typical physical properties of polymeric geosynthetics.....	12
5.3 Manufacturing process.....	13
5.3.1 General.....	13
5.3.2 Geotextiles.....	13
5.3.3 Geosynthetic barriers.....	14
5.3.4 Geogrids.....	15
5.3.5 Geonets.....	15

5.3.6	Geocomposites	15
5.3.7	Geocells	15
5.3.8	GBR-C	15
5.4	Recycled and reworked materials	15
5.5	Additives, stabilizers, fillers and reinforcement scrims	16
5.5.1	General	16
5.5.2	Antioxidants	16
5.5.3	Acid scavengers	16
5.5.4	Metal ion deactivators	16
5.5.5	UV stabilizers	17
5.5.6	Plasticizers	17
5.5.7	Lubricants	17
5.5.8	Mineral fillers	17
5.5.9	Scrims	17
6	Environmental factors that may lead to degradation	17
6.1	The environment above ground	17
6.2	The environment below ground	18
6.3	Chemical and biological effects on a geosynthetic	19
6.3.1	General	19
6.3.2	Hydrolysis of PET and PA	20
6.3.3	Oxidation of PE and PP	20
6.3.4	Biochemical attack	20
6.3.5	Chemical effects on other geosynthetic barriers	20
6.4	Effects of load and mechanical damage	22
6.4.1	Tensile load: Creep and creep-rupture	22
6.4.2	Synergy of tensile load with environmental effects (environmental stress cracking)	22
6.4.3	Effect of mechanical load on weathering and oxidation	23
6.4.4	Loading during installation: Mechanical damage	23
6.4.5	Normal pressure: Compressive creep and penetration	23
6.4.6	Abrasion and dynamic loading	23
7	Evidence of the durability of geosynthetic	24
7.1	Historical development	24
7.2	Empirical evidence of durability from geosynthetics extracted from the soil	24
7.2.1	Geotextiles	24
7.2.2	Geosynthetic barriers	25
7.2.3	Geogrids	27
7.3	Summary	28
8	Procedure for assessment of durability	28
8.1	General	28
8.1.1	Need for testing	28
8.1.2	Testing concepts for lifetime index tests	28
8.1.3	Scope of durability assessment	29
8.2	Procedure	29
8.2.1	Material	29
8.2.2	Function and application	29
8.2.3	Environment	29
8.2.4	Mechanism of degradation	30
8.2.5	Design life	30
8.2.6	The “end-of-life” criterion	30
8.3	Degradation during storage and installation	30
8.3.1	Weathering	30
8.3.2	Mechanical damage	31
8.4	Short-, medium-, and long-term applications	31
8.5	Assessment of long-term durability	32
8.5.1	General	32
8.5.2	Evidence from service	32

	8.5.3	Accelerated testing.....	33
8.6		Prediction of durability.....	37
	8.6.1	Statement of the durability.....	37
	8.6.2	Level of confidence	37
8.7		Planning for future inspection.....	37
Bibliography.....			39

Currently in preview, click buy full version

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

ISO/TS 13434 was prepared by Technical Committee ISO/TC 221, *Geosynthetics*.

This first edition cancels and replaces ISO/TS 13434:2008, which has been technically revised. The main changes compared to the previous edition are as follows:

- standards and wording actualized;
- added product types in 5.1;
- updated subclauses 5.4, 8.4, 8.5 and Table 3.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Geosynthetics — Guidelines for the assessment of durability

1 Scope

This document provides guidelines for the assessment of the durability of geosynthetics, the object of which is to provide the design engineer with the necessary information, generally defined as changes in material properties or as partial safety factors, to ensure that the expected design life of a geosynthetic can be achieved with confidence.

This document is not applicable to products designed to survive for only a limited time, such as erosion-control fabric based on natural fibres.

This document is applicable to the durability of the geosynthetics and not to the durability of the geotechnical structure as a whole.

NOTE The calculation of reduction factors for soil reinforcement applications is described in ISO/TR 20432.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10318-1, *Geosynthetics — Part 1: Terms and definitions*

ISO 13431, *Geotextiles and geotextile-related products — Determination of tensile creep and creep rupture behaviour*

ISO 13438:2018, *Geosynthetics — Screening test method for determining the resistance of geotextiles and geotextile-related products to oxidation*

3 Terms, definitions, symbols and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 10318-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.2 Symbols

A	rate of degradation
A_0	constant in Arrhenius equation
d_{50}	50 % soil gradation
E	activation energy