



BSI Standards Publication

**Liquid chromatography at critical conditions (LCCC) — Chemical heterogeneity of polyethylene oxides**

---

## National foreword

This Published Document is the UK implementation of ISO/TS 23973:2020.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its committee manager.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020  
Published by BSI Standards Limited 2020

ISBN 978 0 539 05985 4

ICS 71.040.50

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 August 2020.

### Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

---

TECHNICAL  
SPECIFICATION

**ISO/TS**  
**23973**

First edition  
2020-08-17

---

---

**Liquid chromatography at critical  
conditions (LCCC) — Chemical  
heterogeneity of polyethylene oxides**

*Chromatographie liquide aux conditions critiques — Hétérogénéité  
chimique des oxydes de polyéthylène*



Reference number  
ISO/TS 23973:2020(E)

© ISO 2020



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020. Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>2</b>
5.1 General.....	2
5.2 Eluent supply.....	3
5.3 Pump.....	3
5.4 Injection system.....	4
5.5 Separation columns.....	4
5.6 Column temperature control.....	5
5.7 Detectors.....	5
5.8 Eluent.....	5
5.9 Data acquisition.....	5
<b>6 Sample preparation</b> .....	<b>5</b>
<b>7 Performance of the measurements</b> .....	<b>6</b>
7.1 Determination of the critical conditions.....	6
7.2 Analysis of the validation kit.....	7
<b>8 Test report</b> .....	<b>7</b>
<b>Annex A (informative) Error sources</b> .....	<b>9</b>
<b>Annex B (informative) Evaluation of the interlaboratory testing</b> .....	<b>10</b>
<b>Annex C (informative) Elugrams of the participants (excerpts)</b> .....	<b>17</b>
<b>Annex D (informative) Investigation of the long-term stability of the test mixture</b> .....	<b>41</b>
<b>Bibliography</b> .....	<b>47</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

Since the first description of liquid chromatography at critical conditions (LCCC) in 1986 (see Reference [1]), the method has been continuously refined and has proved itself to be indispensable for polymer characterisation. Separation is required not only for the quantitative analysis of the individual species. It also offers the preconditions for qualitative characterisation of the fractions by means of spectroscopic and spectrometric techniques. The key factor here is the reduction of the polydispersity/chemical heterogeneity within a fraction, which represents a large problem for mass-spectrometric investigations.

The method has been described extensively in professional circles over the last two decades for different polymer systems, see References [2] to [9].

Within the framework of the Technical Committee, the extent that the method supplies consistent results for a simple, chemically heterogeneous polymer mixture was clarified as part of interlaboratory testing.

At this time, necessary experience relating to the selection of the system (interaction between the polarities separation phase/eluent/sample) was not expected of any of the participating laboratories.

The interlaboratory testing has shown that, even with a well-characterized system and with specification of all pertinent system parameters, it has to date not been possible to classify the process as a routine method in laboratories with experience in polymer analytics.

The idea presents itself of offering a validation kit (polymer mixture with the expecting separation result).

# Liquid chromatography at critical conditions (LCCC) — Chemical heterogeneity of polyethylene oxides

## 1 Scope

This document establishes a valid method for separation of chemically heterogeneous polyethylene oxide (PEO) mixtures and for the determination the number and content of the chemically heterogeneous species in the overall sample.

The method presented in this document serves as a technical guideline and enables laboratories to learn the principle of “critical chromatography” on a validated system.

This method presented in this document with its stated system parameters is not applicable for other polymer classes, due to the diversity of the interactions between the polymer/mobile phase/stationary phase and the number of separation systems that are therefore available.

The evaluation of the interlaboratory testing has shown that many error sources relate to the technique of liquid chromatography in general. Possible error sources are described in [Annex A](#).

Details on the evaluation of the interlaboratory testing are given in [Annex B](#).

Elugrams of the participants (excerpts) are given in [Annex C](#).

Investigations of the long-term stability of the test mixture are given in [Annex D](#).

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

For the purposes of this document the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### liquid chromatography at critical conditions

##### LCCC

special term of liquid chromatography of polymers at the point of adsorption, where chemically and structurally identical polymers with a certain repeat unit elute independently of the molar mass at the same retention time

Note 1 to entry: The individual monomer units do not contribute to the retention. Under these determined system parameters (defined combination of separation column/eluent mixture/temperature), a separation of polymer mixtures of the same repeat unit takes place based on chemical heterogeneity. Chemical heterogeneities can take the form of different functional groups, end groups, differences in the microstructure (e.g. copolymers and their composition) as well as topological differences (e.g. branching).