



BSI Standards Publication

## Guidelines for specifying Charpy V-notch impact prescriptions in steel specifications

---

## National foreword

This Published Document is the UK implementation of ISO/TS 7705:2017.

The UK participation in its preparation was entrusted to Technical Committee ISE/100, Steel, General Issues.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017  
Published by BSI Standards Limited 2017

ISBN 978 0 580 93594 7

ICS 77.080.20

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 August 2017.

### Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

---

---

---

**Guidelines for specifying Charpy  
V-notch impact prescriptions in steel  
specifications**

*Lignes directrices pour la spécification des prescriptions d'énergie de rupture sur éprouvette Charpy à entaille en V dans les normes d'acier*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017. Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

## Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 General features of Charpy V-notch impact test</b> .....	<b>1</b>
4.1 Toughness testing methods in design codes and in steel specifications.....	1
4.2 Historical background to the Charpy V-notch impact test.....	1
4.3 The Charpy V-notch impact test in relation to other tests.....	2
4.4 Factors influencing impact properties.....	2
4.5 The Charpy V-notch impact test as a powerful tool for delivery control in steel specifications.....	3
<b>5 Information to be gained from the impact test</b> .....	<b>3</b>
<b>6 Subsize test pieces</b> .....	<b>6</b>
<b>7 Recommendations for specifying impact strength requirements in steel specifications</b> .....	<b>7</b>
7.1 Selection and preparation of samples and test pieces.....	7
7.1.1 Selection and preparation of samples.....	7
7.1.2 Cutting and machining.....	7
7.2 Number of test pieces to be taken per sample and specific requirements.....	7
7.3 Location of test pieces.....	7
7.4 Interpretation of test results.....	8
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 20, *General technical delivery conditions, sampling and mechanical testing methods*.

This first edition of ISO/TS 7705 cancels and replaces ISO/TR 7705:1991, which has been technically revised.

# Guidelines for specifying Charpy V-notch impact prescriptions in steel specifications

## 1 Scope

This document gives guidelines for specifying Charpy V-notch impact prescriptions in steel specifications.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 General features of Charpy V-notch impact test

### 4.1 Toughness testing methods in design codes and in steel specifications

Tests for evaluating the toughness of steel can be divided into two categories: notch toughness tests and fracture toughness tests based on fracture mechanics.

Notch toughness tests are used to measure the ability of a material to absorb energy and deform plastically in the presence of a mechanical notch. The Charpy V-notch impact test and the drop weight test are typical examples of small scale tests which are used for evaluations of notch toughness. They are often used to determine the ductile to brittle transition temperature of a material and to give a qualitative estimate of the material's toughness. Due to relatively good reproducibility and low cost these methods are highly suitable for use as delivery tests for steel consignments.

Fracture toughness tests such as the crack-tip opening displacement (CTOD) test (see ISO 12135) are fracture mechanics tests which are generally concerned with the determination of critical crack sizes which can appear without causing fracture in a material loaded to a specific stress level. Fracture mechanics tests are very complicated and expensive to carry out. They are primarily used to examine the behaviour of pressurized or structural components with respect to safety rules, etc. Therefore, fracture mechanics testing is primarily connected with design codes and not with steel specifications.

For these reasons, only notch toughness tests are dealt with in these guidelines for steel specifications.

### 4.2 Historical background to the Charpy V-notch impact test

When welded structures, especially heavy ones such as bridges and ships, were first developed on an industrial scale, and especially when the fabrication methods called for joining heavy segments by welding, problems with brittle fractures became more common. This was especially evident during the Second World War when the USA began to produce welded ships of the Liberty and Victory type, where a large number of failures occurred due to brittle fractures.