

## **Control of Electrochemical Corrosion of Underground Metallic Structures**



# Legal Notice for Standards

Canadian Standards Association (operating as “CSA Group”) develops standards through a consensus standards development process approved by the Standards Council of Canada. This process brings together volunteers representing varied viewpoints and interests to achieve consensus and develop a standard. Although CSA Group administers the process and establishes rules to promote fairness in achieving consensus, it does not independently test, evaluate, or verify the content of standards.

## Disclaimer and exclusion of liability

This document is provided without any representations, warranties, or conditions of any kind, express or implied, including, without limitation, implied warranties or conditions concerning this document’s fitness for a particular purpose or use, its merchantability, or its non-infringement of any third party’s intellectual property rights. CSA Group does not warrant the accuracy, completeness, or currency of any of the information published in this document. CSA Group makes no representations or warranties regarding this document’s compliance with any applicable statute, rule, or regulation.

IN NO EVENT SHALL CSA GROUP, ITS VOLUNTEERS, MEMBERS, SUBSIDIARIES, OR AFFILIATED COMPANIES, OR THEIR EMPLOYEES, DIRECTORS, OR OFFICERS, BE LIABLE FOR ANY DIRECT, INDIRECT, OR INCIDENTAL DAMAGES, INJURY, LOSS, COSTS, OR EXPENSES, HOWSOEVER CAUSED, INCLUDING BUT NOT LIMITED TO SPECIAL OR CONSEQUENTIAL DAMAGES, LOST REVENUE, BUSINESS INTERRUPTION, LOST OR DAMAGED DATA, OR ANY OTHER COMMERCIAL OR ECONOMIC LOSS, WHETHER BASED IN CONTRACT, TORT (INCLUDING NEGLIGENCE), OR ANY OTHER THEORY OF LIABILITY, ARISING OUT OF OR RESULTING FROM ACCESS TO OR POSSESSION OR USE OF THIS DOCUMENT, EVEN IF CSA GROUP HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES, INJURY, LOSS, COSTS, OR EXPENSES.

In publishing and making this document available, CSA Group is not undertaking to render professional or other services for or on behalf of any person or entity or to perform any duty owed by any person or entity to another person or entity. The information in this document is directed to those who have the appropriate degree of experience to use and apply its contents, and CSA Group accepts no responsibility whatsoever arising in any way from any and all use of or reliance on the information contained in this document.

CSA Group is a private not-for-profit company that publishes voluntary standards and related documents. CSA Group has no power, nor does it undertake, to enforce compliance with the contents of the standards or other documents it publishes.

## Intellectual property rights and ownership

As between CSA Group and the users of this document (whether it be in printed or electronic form), CSA Group is the owner, or the authorized licensee, of all works contained herein that are protected by copyright, all trade-marks (except as otherwise noted to the contrary), and all inventions and trade secrets that may be contained in this document, whether or not such inventions and trade secrets are protected by patents and applications for patents. Without limitation, the unauthorized use, modification, copying, or disclosure of this document may violate laws that protect CSA Group’s and/or others’ intellectual property and may give rise to a right in CSA Group and/or others to seek legal redress for such use, modification, copying, or disclosure. To the extent permitted by treaty or by law, CSA Group reserves all intellectual property rights in this document.

## Patent rights

Attention is drawn to the possibility that some of the elements of this standard may be the subject of patent rights. CSA Group shall not be held responsible for identifying any or all such patent rights. Users of this standard are expressly advised that determination of the validity of any such patent rights is entirely their own responsibility.

## Authorized use of this document

This document is being provided by CSA Group for informational and non-commercial use only. The user of this document is authorized to do only the following:

If this document is in electronic form:

- load this document onto a computer for the sole purpose of reviewing it;
- search and browse this document; and
- print this document if it is in PDF form.

Limited copies of this document in print or paper form may be distributed only to persons who are authorized by CSA Group to have such copies, and only if this Legal Notice appears on each such copy.

In addition, users may not and may not permit others to

- alter this document in any way, or remove this Legal Notice from the attached standard;
- sell this document without authorization from CSA Group; or
- make an electronic copy of this document.

If you do not agree with any of the terms and conditions contained in this Legal Notice, you may not load or use this document or make any copies of the contents hereof, and if you do make such copies, you are required to destroy them immediately. Use of this document constitutes your acceptance of the terms and conditions of this Legal Notice.



# ***Standards Update Service***

***C22.3 No. 4-1974***

***April 1974***

**Title:** *Control of Electrochemical Corrosion of Underground Metallic Structures*

To register for e-mail notification about any updates to this publication

- go to [store.csagroup.org](http://store.csagroup.org)
- click on **Product Updates**

The **List ID** that you will need to register for updates to this publication is **20015.2**

If you require assistance, please e-mail [techsupport@csagroup.org](mailto:techsupport@csagroup.org) or call 416-747-2233.

Visit CSA Group's policy on privacy at [www.csagroup.org/legal](http://www.csagroup.org/legal) to find out how we protect your personal information.

*C22.3 No. 4-1974*  
***Control of Electrochemical Corrosion  
of Underground Metallic Structures***



*®A trademark of the Canadian Standards Association, operating as "CSA Group"*

*Published in April 1974 by CSA Group  
A not-for-profit private sector organization  
178 Rexdale Boulevard, Toronto, Ontario, Canada M9W 1R3*

*To purchase standards and related publications, visit our Online Store at [store.csagroup.org](http://store.csagroup.org)  
or call toll-free 1-800-463-6727 or 416-747-4044.*

*ISSN 0317-8935*

*© 1974 Canadian Standards Association  
All rights reserved. No part of this publication may be reproduced in any form whatsoever  
without the prior permission of the publisher.*

# Contents

## COMMITTEE ON CANADIAN ELECTRICAL CODE, PART III

### SUBCOMMITTEE ON GROUND CURRENT COORDINATION

#### TASK GROUP ON ELECTROCHEMICAL CORROSION OF UNDERGROUND METALLIC STRUCTURES

#### PREFACE

#### 1. SCOPE

#### 2. SAFETY REQUIREMENT

#### 3. DEFINITIONS

#### 4. TYPES OF CORROSION

- 4.1 General.
- 4.2 Stray Current Corrosion
  - 4.2.1 Anodic Corrosion.
  - 4.2.2 Cathodic Corrosion (Corrosion by Cathodic Products).
- 4.3 Localized Corrosion
  - 4.3.1 General.
  - 4.3.2 Galvanic Corrosion.
  - 4.3.3 Local Action.
  - 4.3.4 Differential Aeration.
  - 4.3.5 Concentration Cell.
- 4.4 Chemical Attack.

#### 5. PRINCIPLES

- 5.1 General
- 5.2 Stray Current Corrosion
  - 5.2.1 Mitigation of Stray Current Corrosion
  - 5.2.2 Electrolysis Surveys.
  - 5.2.3 Maintenance of Protective System.
- 5.3 Non-Stray Current Corrosion
  - 5.3.1 Corrosion in Non-Stray Current Areas.
  - 5.3.2 Mitigation of Non-Stray Current Corrosion
  - 5.3.3 Surveys in Non-Stray Areas
- 5.4 Cooperative Arrangements.

#### 6. PRACTICES

- 6.1 General.
- 6.2 Limitation of Stray Currents.
- 6.3 Limitation of Stray Currents Discharged to Earth.
  - 6.3.1 Track Construction and Bonding
  - 6.3.2 Track Insulation
  - 6.3.3 Electrical Reinforcement of Tracks and Other Return Conductors
- 6.4 Limitations of Stray Currents Picked up from Earth
  - 6.4.1 General
  - 6.4.2 Location of Underground Structures with Respect to Tracks
  - 6.4.3 Avoidance of Contact Between Underground Structures.
  - 6.4.4 Conduit Construction
  - 6.4.5 Protective Coatings or Jackets on Pipes and Cables.
  - 6.4.6 Insulating Joints in Pipes and Cable Sheaths.
- 6.5 Drainage of Cable Sheaths and Pipes
  - 6.5.1 General.
  - 6.5.2 Application of Drainage.
  - 6.5.3 Location of Drainage Connections.
  - 6.5.4 Bonding of Cable Sheaths.
  - 6.5.5 Measurement of Drainage Currents.
  - 6.5.6 Reverse Current Blocking.
  - 6.5.7 Forced Drainage.
  - 6.5.8 Drainage of Pipes.

6.6 Protection Against Cathodic Corrosion (Corrosion by Cathodic Products)

6.6.1 General.

6.6.2 Restriction of Negative Potentials.

6.6.3 Flushing of Ducts.

6.7 Mitigative Measures Applicable in Non-Stray Areas

6.7.1 Cathodic Protection.

6.7.2 Current Required for Cathodic Protection.

6.7.3 Location of Current Supply Points.

6.7.4 Current Supply.

6.7.5 Type of Anodes.

6.7.6 Location of Anodes.

6.7.7 Joint Cathodic Protection.

**APPENDIX A VOLTAGE AND CURRENT DISTRIBUTION IN STRAY CURRENT AREAS**

**APPENDIX B DRAINAGE SYSTEMS**

### ***COMMITTEE ON CANADIAN ELECTRICAL CODE, PART III***

- J. E. GILLESPIE** (Chairman).....Hydro-Quebec, Montreal  
**N. J. DUNLOP** (Vice-Chairman)....British Columbia Telephone Company, Vancouver  
**(Representing Canadian Telecommunications Carriers Association)**  
**J. D. ADAM**.....Manitoba Telephone System, Winnipeg  
**N. J. DUNLOP**.....British Columbia Telephone Company, Vancouver  
**B. C. NOWLAN**.....Bell Canada, Montreal  
**J. F. NOYES**.....Newfoundland Telephone Co. Ltd., St. John's  
**(Representing Provincial Electrical Inspection Authorities)**  
**K. L. BELLAMY**.....Ontario Hydro, Toronto  
**(Representing Canadian Transport Commission)**  
**H. H. BLAKNEY**.....Canadian Transport Commission, Ottawa  
**(Representing Railways)**  
**R. T. BRADLEY**.....Canadian National Telecommunications, Toronto  
**B. T. POWER**.....Canadian Pacific Telecommunications, Montreal  
**(Representing Canadian Cable Television Association)**  
**K. J. EASTON**.....Cable Consultants, Clarkson  
**(Representing Canadian Electrical Association)**  
**M. FRALESSO**.....Ontario Hydro, Toronto  
**J. E. GILLESPIE**.....Hydro-Quebec, Montreal  
**W. G. MCMICHAEL**.....British Columbia Hydro and Power Authority, Vancouver  
**G. H. WELDON**.....Manitoba Hydro, Winnipeg  
**(Representing Association of Municipal Electrical Utilities)**  
**J. A. TORRANCE**.....Etobicoke Hydro-Electric Commission, Etobicoke  
**C. D. HOLMES**.....Roads and Transport Association of Canada, Ottawa  
**G. YORKE SLADER**.....The National Energy Board, Ottawa  
**H. M. ROBINSON** (Secretary non-voting).....Canadian Standards Association, Rexdale
- In addition to the members of the Committee, the following made valuable contribution to the development of this Standard in their capacities as noted:
- J. G. CASSAN** (Associate).....Ontario Hydro, Toronto  
**M. P. GUNNING** (Associate).....Hydro-Quebec, Montreal  
**W. J. MEESE** (Associate).....National Bureau of Standards, Washington D.C.  
**B. C. NOWLAN** (Associate).....Bell Canada, Montreal  
**C. POULIOT** (Alternate).....Hydro-Quebec, Montreal  
**R. E. TREEN** (Associate).....Ontario Hydro, Toronto

## ***SUBCOMMITTEE ON GROUND CURRENT COORDINATION***

- J. G. CASSAN** (Chairman).....Ontario Hydro, Toronto  
(Representing Canadian Electrical Association)
- M. E. CARLSON**.....TransCanada PipeLines Limited, Toronto  
(Representing Canadian Gas Association)
- C. DEGRANDMONT**.....Hydro Quebec, Montreal  
(Representing Canadian Electrical Association)
- W. J. HARDER**.....Saskatchewan Telecommunications, Regina  
(Representing Canadian Telecommunications Carriers Association)
- G. W. LAWSON**.....Department of Manpower and Labour, Edmonton  
(Representing Provincial Electrical Impaction Authorities)
- W. M. MCCOWAN**.....Toronto Hydro-Electric System, Toronto  
(Representing Association of Municipal Electrical Utilities)
- J. SOLINAS**.....Bell Canada, Montreal  
(Representing Canadian Telecommunications Carriers Association)
- T. R. THOMPSON**.....Ontario Hydro, Toronto  
(Representing Canadian Electrical Association)
- A. TILT**.....Public Utilities Commission, Scarborough  
(Representing American Water Works Association)
- R. TRUSSLER**.....City of Calgary Electric System, Calgary
- B. C. WATTSON**.....Canadian National Telecommunications, Toronto  
(Representing Canadian National Railways)
- H. A. WEBSTER**.....Corrosion Service Company Limited, Toronto

***TASK GROUP ON ELECTROCHEMICAL CORROSION OF UNDERGROUND METALLIC STRUCTURES***

- H. A. WEBSTER** (Chairman).....Corrosion Service Company Limited, Toronto  
**H. T. ANDERSEN**.....Canadian Western Natural Gas Company Limited, Calgary  
**R. T. CROTHERS**.....Bell Canada, Toronto  
(Representing Canadian Telecommunications Carriers Association)  
**R. C. JACOBSEN**.....Ontario Hydro, Toronto

Currently in preview, click buy full versi

## **PREFACE**

This is the third edition of C22.3 No. 4, it supersedes previous editions published in 1936 and 1958.

In the first edition, major emphasis was placed upon the corrosive effects of stray currents originating in direct-current electric railway systems. In fact, the title of the first edition was "Principles and Practices for Protecting Underground Structures from the Effects of Stray Currents Originating in Direct-Current Electric Railway Systems".

In preparing the second edition of C22.3 No. 4, the Committee recognized certain major changes that were occurring throughout the country. Many transportation systems had discontinued operation of electrically operated railways employing grounded rails, or were in the process of eliminating this type of system. For this reason, the stray current situation was undergoing a radical change, and often this change resulted in more severe corrosion problems than existed during the operation of the electric railway. For example, many street railways have in the past cooperated extensively with the owners of other subsurface structures by, designing their systems to limit stray currents and by permitting the installation of drainage bonds between the two systems at strategic locations. The net result of this cooperation has been a large measure of cathodic protection to the other system. With the elimination of the street railway, however, this protection has been withdrawn, and corrosion due to other causes has been permitted to take place.

It should be recognized that electrically operated railways employing grounded rail returns are not the only source of stray currents. Other types of systems utilizing grounded direct-current circuits often act as sources of stray currents in the earth. One such source that is becoming of major importance is the pipeline equipped with cathodic protection.

While the electric railway is becoming of decreasing importance as a source of stray currents, considerable experience in the mitigation of corrosion due to stray currents originating in such railways has accumulated over the years. For this reason some of the Rules contained in this Code apply specifically to railways. It should be realized, however, that these Rules apply in general to all systems which originate stray earth currents, and that railways are mentioned specifically merely for convenience.

The Committee charged with the preparation of the second edition foresaw the gradual abolition of electric railways and attempted to emphasize cathodic protection systems as a new and important source of stray dc current. In the interim between the publication of the second edition and the preparation of the third edition it is now apparent that electric traction systems may see increasing use in urban and inter-urban service. With the advent of high voltage direct current transmission for the long distance transportation of power and the almost universal use of cathodic protection on oil and gas piping systems the up-dating of this Standard is most timely.

This Standard was prepared by the Task Group on Electrochemical Corrosion of Underground Metallic Structures under the jurisdiction of the Subcommittee on Ground Current Coordination and the Committee on Canadian Electrical Code, Part III and was formally approved by these Committees.

REXDALE, APRIL, 1974

**NOTE:** In order to keep abreast of progress in the industries concerned, CSA Publications are subject to periodic review. Suggestions for improvement will be welcomed at all times. They will be recorded and in due course brought to the attention of the appropriate Committee for consideration.

Also, requests for interpretation will be accepted by the Committee. They should be worded in such a manner as to permit a simple "yes" or "no" answer based on the literal text of the requirements concerned.

All enquiries regarding this Standard should be addressed to Canadian Standards Association, 178 Rexdale Boulevard, Rexdale, Ontario M9W 1R3.

## 1. SCOPE

### 1.1

The provisions of this Standard, forming a part of the Canadian Electrical code, Part III, embody the applicable principles and general practices where underground metallic structures are subject to the risk of electro-chemical corrosion.

### 1.2

This Standard is issued for the guidance of all parties owning, controlling, or operating grounded electric systems and subsurface structures such as metallic pipes, metallic cable sheaths, or other structures with underground metallic components.

## 2. SAFETY REQUIREMENT

### 2.1

Where corrosion of underground systems or structures could result in a hazard to persons preventive measures shall be instituted. This demands the cooperation of all parties concerned.

**NOTE:** If any of the parties concerned are not sufficiently familiar with the engineering details involved in the mitigation of electrochemical corrosion as set forth in the principles and practices contained therein, such party should obtain technical advice from qualified experts. Information on the formation of Electrolysis Committees, as well as a directory of existing Committees, can be obtained from the National Association of Corrosion Engineers.

## 3. DEFINITIONS

### 3.1

The following definitions apply in this Standard:

**Anode** means an electrode through which current enters an electrolyte. In corrosion processes, the anode is the electrode that usually has the greater tendency to go into solution, or to corrode;

**Cathode** means an electrode through which current leaves an electrolyte. In corrosion processes, the cathode is usually the area that is not attacked;

**Cathodic corrosion (corrosion by cathodic products)** means corrosion occurring on the surface of a cathode due to the chemicals released there by electrolytic action, usually when the surrounding electrolyte is alkaline;

**Cathodic protection** means reduction or prevention of corrosion of a metal surface by making it all cathodic;

**Concentration cell** means an electrolytic cell, the emf of which is due to differences in strength or composition of the electrolyte at anode and cathode areas;

**Corrosion** means the deterioration of a substance, usually a metal, because of a reaction with its environment;

**Differential aeration cell** means an electrolytic cell, the emf of which is due to a difference in oxygen concentration at two otherwise similar electrodes;

**Drainage** means a technique whereby a metallic conductor is installed between structures to provide a preferential path for stray currents which would otherwise pass through the soil or other electrolyte;

**Electrolysis** means the production of chemical changes by the passage of current through an electrolyte. This term commonly refers to corrosion problems caused by stray currents;

**Electrolysis survey** means the operation of determining by means of measurements, relevant facts pertaining to electrolysis conditions. These measurements include determination of voltages, currents, voltage gradients, condition of the soil surrounding underground structures, the extent of corrosion that may have occurred, and other factors, so that the risk of corrosion may be assessed and suitable mitigative measures determined;

**Electrolyte** means a chemical substance, usually liquid containing ions which migrate in an electric field. For the purposes of this Standard electrolyte refers to the soil adjacent to and in contact with an underground metallic structure, including the moisture and other chemicals contained therein;

**Forced drainage** means the use of a rectifier or other dc source in a drainage bond to overcome an IR drop in the bond due to the passage of drainage current;

**Galvanic anode** means an anode constructed of a metal high in the galvanic series, usually magnesium, sometimes zinc. A galvanic anode is used to protect an underground structure of metal lower in the galvanic series. The galvanic