

FINAL VERSION

VERSION FINALE

**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving – Sheet 247:
Heatshrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and
medium wall**

**Gaines isolantes souples –
Partie 3: Spécifications pour types particuliers de gaines – Feuille 247: Gaines
thermorétractables en polyoléfine, à double paroi (épaisse et moyenne), non
retardées à la flamme**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Designation	7
4 Conditions of test.....	7
5 Requirements	7
6 Sleeving conformance.....	7
Annex A (informative) Guide to the available sizes and wall thicknesses	12
Table 1 – Property requirements	8
Table 2 – Requirements for breakdown voltage	11
Table 3 – Resistance to selected fluids.....	11
Table 4 – Additional property requirements.....	11
Table A.1 – Type A medium wall	12
Table A.2 – Type B thick wall	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and medium wall

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International governmental and non-governmental organizations liaising with the IEC also participate in this preparatory work. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters expressed, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

DISCLAIMER

This Consolidated version is not an official IEC Standard and has been prepared for user convenience. Only the current versions of the standard and its amendment(s) are to be considered the official documents.

This Consolidated version of IEC 60684-3-247 bears the edition number 1.1. It consists of the first edition (2011-06) [documents 15/625/FDIS and 15/637/RVD] and its amendment 1 (2016-12) [documents 15/754/CDV and 15/790/RVC]. The technical content is identical to the base edition and its amendment.

This Final version does not show where the technical content is modified by amendment 1. A separate Redline version with all changes highlighted is available in this publication.

International Standard IEC 60684-3-247 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60684 series, under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

- Part 1: Definitions and general requirements (IEC 60684-1)
- Part 2: Methods of test (IEC 60684-2)
- Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This standard gives one of the sheets comprising part 3 as follows:

Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and medium wall

Amendment 1 to IEC 60684-3-247 changes the requirements for peel strength. Major problems have been experienced with reliability and repeatability of results when selecting cable jackets of material types PE, PVC and EPR. The method requires conditioning at 50 °C, so careful selection of cable jackets that have a minimum rating exceeding this temperature is essential. Even when cables that exceed this temperature are selected, experience has shown reproducible adhesive peel forces are difficult to achieve. While it is appreciated that these cable jackets are used with this type of sleeveings as recovery of the sleeving is normally achieved by either flame or hot air devices. This means of recovery could be inserted into the method, but extensive testing has shown reproducibly of adhesive peel forces still to be a major problem. Due to these issues of lack of reliability and repeatability these substrates have been removed. Lead has also been removed due to health and safety reasons. Additional text has been included to aid clarification of the method that deviates from Clause 54 of IEC 60684-2:2011.

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and medium wall

1 Scope

This part of IEC 60684 gives the requirements for two types of heat-shrinkable, polyolefin, sleeving, dual wall, not flame retarded with a nominal shrink ratio of 3:1.

This sleeving has been found suitable for use at temperatures of up to 100 °C.

Type A : Medium wall, internal diameter up to 200,0 mm typically

Type B : Thick wall, internal diameter up to 200,0 mm typically

These sleeveings are normally supplied in colour black.

Since these types of sleeveings cover a significantly large range of sizes and wall thicknesses, Tables A.1 and A.2 provide a guide to the range of sizes available. The actual size shall be agreed between the user and supplier.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:2003, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

IEC 60502-1:2005, *Power cables with extruded insulation and their accessories for rated voltages from 0,6/1 kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV) – Part 1: Cables for rated voltages of 1 kV ($U_m = 1,2$ kV) and 3 kV ($U_m = 3,6$ kV)*

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:1997, *Flexible insulating sleeving – Part 2: Methods of test*
Amendment 2 (2005)

IEC 60757:1983, *Code for designation of colours*

ISO 846:1997, *Plastics – Evaluation of the action of micro-organisms*

ISO 868: 2003, *Plastics and ebonite – Determination of indentation hardness by means of a durometer (Shore hardness)*