

# FINAL VERSION

## VERSION FINALE

**Electric and optical fibre cables – Test methods for non-metallic materials –  
Part 202: General tests – Measurement of thickness of non-metallic sheath**

**Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux  
non-métalliques –**

**Partie 202: Essais généraux – Mesure de l'épaisseur des gaines non métalliques**

## CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references .....	6
3 Terms and definitions .....	6
4 Test method .....	6
4.1 General.....	6
4.2 Measuring equipment .....	6
4.3 Sample and test piece preparation .....	7
4.3.1 Sheaths applied over longitudinally regular surfaces .....	7
4.3.2 Sheaths applied over longitudinally irregular surfaces .....	7
4.3.3 Sheath applied over corrugated metallic sheaths .....	7
4.4 Measuring procedure.....	7
4.5 Evaluation of the measurement results .....	8
5 Test report.....	8
Bibliography.....	12
Figure 1 – Measurement of sheath thickness (circular inner profile).....	9
Figure 2 – Measurement of sheath thickness (irregular circular inner profile) .....	9
Figure 3 – Measurement of sheath thickness (non-circular inner profile) .....	10
Figure 4 – Measurement of sheath thickness (irregular outer surface) .....	10
Figure 5 – Measurement of sheath thickness (twin sheathed flat cable) .....	11
Figure 6 – Measurement of sheath thickness (flat cable with single cores).....	11

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**ELECTRIC AND OPTICAL FIBRE CABLES –  
TEST METHODS FOR NON-METALLIC MATERIALS –**

**Part 202: General tests –  
Measurement of thickness of non-metallic sheath**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

**DISCLAIMER**

**This Consolidated version is not an official IEC Standard and has been prepared for  
use for convenience. Only the current versions of the standard and its amendment(s)  
are to be considered the official documents.**

**This Consolidated version of IEC 60811-202 bears the edition number 1.1. It consists of  
the first edition (2012-03) [documents 20/1281/FDIS and 20/1330/RVD] and its  
amendment 1 (2017-07) [documents 20/1732/FDIS and 20/1743/RVD]. The technical  
content is identical to the base edition and its amendment.**

**This Final version does not show where the technical content is modified by  
amendment 1. A separate Redline version with all changes highlighted is available in  
this publication.**

International Standard IEC 60811-202 has been prepared by IEC technical committee 20: Electric cables.

There are no specific technical changes with respect to the previous edition, but see the Foreword to IEC 60811-100:2012.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This part of IEC 60811 shall be read in conjunction with IEC 60811-100.

A list of all the parts in the IEC 60811 series, published under the general title *Electric and optical fibre cables – Test methods for non-metallic materials*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## INTRODUCTION

The IEC 60811 series specifies the test methods to be used for testing non-metallic materials of all types of cables. These test methods are intended to be referenced in standards for cable construction and for cable materials.

NOTE 1 Non-metallic materials are typically used for insulating, sheathing, bedding, filling or taping within cables.

NOTE 2 These test methods are accepted as basic and fundamental and have been developed and used over many years principally for the materials in all energy cables. They have also been widely accepted and used for other cables, in particular optical fibre cables, communication and control cables and cables for ships and offshore applications.

Currently in preview, click buy full version

# ELECTRIC AND OPTICAL FIBRE CABLES – TEST METHODS FOR NON-METALLIC MATERIALS –

## Part 202: General tests – Measurement of thickness of non-metallic sheath

### 1 Scope

This Part 202 of IEC 60811 gives the methods for measuring thicknesses of non-metallic sheath which apply to the most common types of sheathing compounds (cross-linked PVC, PE, PP, etc.).

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60811-100:2012, *Electric and optical fibre cables – Test methods for non-metallic materials - Part 100: General*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60811-100 apply.

### 4 Test method

#### 4.1 General

This part of IEC 60811 shall be used in conjunction with IEC 60811-100.

The measurement of sheath thickness may be required as an individual test, or as a step in the procedure for carrying out other tests, such as the measurement of mechanical properties. The test method applies to the measurement of all sheaths for which thickness limits are specified, for example separation sheaths, as well as external sheaths.

In each case, the method of selecting samples shall be in accordance with the relevant cable standard.

#### 4.2 Measuring equipment

A measuring microscope or a profile projector of at least 10 x magnification or an optical digital image analyser shall be used. These types of equipment shall allow a reading of 0,01 mm and an estimated reading to three decimal places when measuring insulation with a specified thickness less than 0,5 mm.

For sheaths applied over longitudinally irregular surfaces such as corrugated metallic sheaths, a micrometer having a ball nose radius of 1 mm and allowing a reading of 0,01 mm may be used. This method is suitable only for corrugations having a radius greater than 1 mm.