

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Superconductivity –
Part 23: Residual resistance ratio measurement – Residual resistance ratio of
cavity-grade Nb superconductors**

**Supraconductivité –
Partie 23: Mesurage du rapport de résistance résiduelle – Rapport de résistance
résiduelle des supraconducteurs de Nb à cavités**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2024 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications provided, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications, symboles graphiques et le glossaire. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 500 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 25 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Superconductivity –

Part 23: Residual resistance ratio measurement – Residual resistance ratio of cavity-grade Nb superconductors

Supraconductivité –

Partie 23: Mesurage du rapport de résistance résiduelle – Rapport de résistance résiduelle des supraconducteurs de Nb à cavités

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 17.220, 29.050

ISBN 978-2-8322-8888-7

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Principle.....	8
5 Measurement apparatus	9
5.1 Mandrel or base plate	9
5.2 Cryostat and support of mandrel or base plate	9
6 Specimen preparation.....	10
7 Data acquisition and analysis	11
7.1 Data acquisition hardware.....	11
7.2 Resistance (R_1) at room temperature.....	11
7.3 Residual resistance (R_2) just above the superconducting transition.....	12
7.4 Validation of the residual resistance measurement.....	13
7.5 Residual resistance ratio.....	13
8 Uncertainty of the test method	13
9 Test report.....	14
9.1 General.....	14
9.2 Test information.....	14
9.3 Specimen information	14
9.4 Test conditions	14
9.5 RRR value	14
Annex A (informative) Additional information relating to the measurement of RRR.....	15
A.1 Considerations for specimens and apparatus.....	15
A.2 Considerations for specimen mounting orientation	16
A.3 Alternative methods for increasing temperature of specimen above superconducting transition temperature	16
A.3.1 General	16
A.3.2 Heater method.....	16
A.3.3 Controlled methods.....	16
A.4 Other test methods	16
A.4.1 General	16
A.4.2 Measurement of resistance versus time.....	17
A.4.3 Comparison of ice point and room temperature.....	17
A.4.4 Extrapolation of the resistance to 4,2 K	17
A.4.5 Use of magnetic field to suppress superconductivity at 4,2 K.....	18
A.4.6 AC techniques	18
Annex B (informative) Uncertainty considerations	19
B.1 Overview.....	19
B.2 Definitions.....	19
B.3 Consideration of the uncertainty concept	20
B.4 Uncertainty evaluation example for IEC TC 90 standards.....	22
Annex C (informative) Uncertainty evaluation for resistance ratio measurement of Nb superconductors	24

C.1	Evaluation of uncertainty.....	24
C.1.1	Room temperature measurement uncertainty.....	24
C.1.2	Cryogenic measurement uncertainty.....	25
C.1.3	Estimation of uncertainty for typical experimental conditions.....	27
C.2	Inter-laboratory comparison summary.....	28
	Bibliography.....	29
Figure 1	– Relationship between temperature and resistance near the superconducting transition.....	8
Figure A.1	– Determination of the value of R_2 from a resistance versus time plot.....	17
Figure C.1	– Graphical description of the uncertainty of regression related to the measurement of R_2	27
Table B.1	– Output signals from two nominally identical extensometers.....	20
Table B.2	– Mean values of two output signals.....	20
Table B.3	– Experimental standard deviations of two output signals.....	21
Table B.4	– Standard uncertainties of two output signals.....	21
Table B.5	– Coefficients of variation of two output signals.....	21
Table C.1	– Uncertainty of measured parameters.....	27
Table C.2	– RRR values obtained by inter-laboratory comparison using liquid helium.....	28

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –

**Part 23: Residual resistance ratio measurement –
Residual resistance ratio of cavity-grade Nb superconductors**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publications”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as far as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 61788-23 has been prepared by IEC technical committee 90: Superconductivity. It is an International Standard.

This third edition cancels and replaces the second edition published in 2021. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) The principle is changed to represent the present test method.

The text of this International Standard is based on the following documents:

Draft	Report on voting
90/515/FDIS	90/519/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The 'color inside' logo on the cover page of this publication indicates that it contains colors which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a color printer.

INTRODUCTION

High-purity niobium is the chief material used to make superconducting radio-frequency cavities. Similar grades of niobium can be used in the manufacture of superconducting wire. Procurement of raw materials and quality assurance of delivered products often use the residual resistance ratio (RRR) to specify or assess the purity of a metal. RRR is defined for non-superconducting metals as the ratio of electrical resistance measured at room temperature (293 K) to the resistance measured for the same specimen at low temperature (~4,2 K). The low-temperature value is often called the residual resistance. Higher purity is associated with higher values of RRR.

Niobium presents special problems due to its transformation to a superconducting state at 9 K, so DC electrical resistance is effectively zero below this temperature. The definition above would then yield an infinite value for RRR. This document describes a test method to determine the residual resistance value by using a plot of the resistance to temperature as the test specimen is gradually warmed through the superconducting transition in the absence of an applied magnetic field. This results in a determination of the residual resistance at just above superconducting transition, ~10 K, from which RRR is subsequently determined.

International Standards also exist to determine the RRR of superconducting wires. In contrast to superconducting wires, which are usually a composite of a superconducting material and a non-superconducting material and the RRR value is representative of only the non-superconducting component, here the entire specimen is composed of superconducting niobium. Frequently, niobium is procured as a sheet, bar or rod, and not as a wire. For such forms, test specimens will likely be a few millimetres in the dimensions transverse to electric current flow. This difference is significant when making electrical resistance measurements, since niobium samples will likely be much longer than that for the same length-to-diameter ratio as a wire, and higher electrical current can be required to produce sufficient voltage signals. Guidance for sample dimensions and electrical connections is provided in Annex A. Test apparatus should also take into consideration aspects such as the orientation of a test specimen relative to the liquid helium surface, accessibility through ports on common liquid helium dewars, design of current contacts, and minimization of thermal gradients over long specimen lengths. These aspects distinguish this document from similar wire standards.

Other test methods have been used to determine RRR. Some methods use a measurement at a temperature other than 293 K for the high resistance value. Some methods use extrapolations at 4,2 K in the absence of an applied magnetic field for the low resistance value. Other methods use an applied magnetic field to suppress superconductivity at 4,2 K. A comparison between this document and some other test methods is presented in Annex A. Note that systematic differences of up to 10 % are produced by these other methods, which is larger than the target uncertainty of this document. It is therefore important to apply this document or the appropriate corrections listed in Annex A according to the test method used.

Whenever possible, this test method should be transferred to vendors and collaborators who also perform RRR measurements. To promote consistency, the results of inter-laboratory comparisons are described in Clause C.2.

SUPERCONDUCTIVITY –

Part 23: Residual resistance ratio measurement – Residual resistance ratio of cavity-grade Nb superconductors

1 Scope

This part of IEC 61788 addresses a test method for the determination of the residual resistance ratio (RRR), r_{RRR} , of cavity-grade niobium. This method is intended for high-purity niobium grades with $150 < r_{RRR} < 600$. The test method is valid for specimens with rectangular or round cross-section, cross-sectional area greater than 1 mm² but less than 20 mm², and a length not less than 10 nor more than 25 times the width or diameter.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815, *International Electrotechnical Vocabulary – Part 815: Superconductivity* (available at: <https://www.electropedia.org/>)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-815 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1 residual resistance ratio RRR

r_{RRR}
ratio of resistance at room temperature to the resistance just above the superconducting transition

$$r_{RRR} = R_1 / R_2 \quad (1)$$

where

R_1 is the resistance at room temperature, 293 K;

R_2 is the resistance just above the superconducting transition, at ~10 K.