

INTERNATIONAL STANDARD

IEC
61788-3

Second edition
2006-04

Superconductivity –

Part 3:

Critical current measurement

DC critical current of Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors

© IEC 2006 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

T

For price, see current catalogue

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative reference.....	6
3 Terms and definitions.....	6
4 Principle.....	8
5 Requirements.....	8
6 Apparatus.....	8
7 Specimen preparation.....	9
8 Measurement procedure.....	10
9 Precision and accuracy of the test method.....	11
10 Calculation of results.....	12
11 Test report.....	13
Annex A (informative) Additional information relating to Clause 1 to 10.....	15
Annex B (informative) Magnetic hysteresis of the critical current of high-temperature oxide superconductors.....	21
Bibliography.....	23
Figure 1 – Intrinsic $U-I$ characteristic.....	14
Figure 2 – $U-I$ characteristic with a current transfer component.....	14
Figure A.1 – Illustration of a measurement configuration for a short specimen of a few hundred A class conductors.....	20
Figure A.2 – Illustration of superconductor simulator circuit.....	20
Table A.1 – Thermal expansion data of Bi-oxide superconductor and selected materials.....	19

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –

**Part 3: Critical current measurement –
DC critical current of Ag- and/or Ag alloy-sheathed
Bi-2212 and Bi-2223 oxide superconductors**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative References cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61788-3 has been prepared by IEC technical committee 90: Superconductivity.

This second edition cancels and replaces the first edition published in 2000. Modifications made to the second version mostly involve wording and essentially include no technical changes. Examples of technical changes introduced include the voltage lead diameter being smaller than 0,2 mm and the mode of expression for magnetic field accuracy being $\pm 1\%$ and $\pm 0,02\text{ T}$ instead of 1% . The expression for magnetic field precision has been changed in the same way.

The text of this standard is based on the following documents:

FDIS	Report on voting
90/184/FDIS	90/190/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 61788 consists of the following parts, under the general title *Superconductivity*:

- Part 1: Critical current measurement – DC critical current of Cu/Nb-Ti composite superconductors
- Part 2: Critical current measurement – DC critical current of Nb₃Sn composite superconductors
- Part 3: Critical current measurement – DC critical current of Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors
- Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti composite superconductors
- Part 5: Matrix to superconductor volume ratio measurement – Copper to superconductor volume ratio of Cu/Nb-Ti composite superconductors
- Part 6: Mechanical properties measurement – Room temperature tensile test of Cu/Nb-Ti composite superconductors
- Part 7: Electronic characteristic measurements – Surface resistance of superconductors at microwave frequencies
- Part 8: AC loss measurements – Total AC loss measurement of Cu/Nb-Ti composite superconducting wires exposed to a transverse alternating magnetic field by a pickup coil method
- Part 9: Measurements for bulk high temperature superconductors – Trapped flux density of large grain oxide superconductors
- Part 10: Critical temperature measurement – Critical temperature of Nb-Ti, Nb₃Sn, and Bi-system oxide composite superconductors by a resistance method
- Part 11: Residual resistance ratio measurement – Residual resistance ratio of Nb₃Sn composite superconductors
- Part 12: Matrix to superconductor volume ratio measurement – Copper to non-copper volume ratio of Nb₃Sn composite superconducting wires
- Part 13: AC loss measurements – Magnetometer methods for hysteresis loss in Cu/Nb-Ti multifilamentary composite

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

In 1986 J.G. Bednorz and K.A. Mueller discovered that some Perovskite type Cu-containing oxides show superconductivity at temperatures far above those which metallic superconductors have shown. Since then, extensive R & D work on high-temperature oxide superconductors has been and is being made worldwide, and its application to high-field magnet machines, low-loss power transmission, electronics and many other technologies is in progress [1].¹⁾

Fabrication technology is essential to the application of high-temperature oxide superconductors. Among high-temperature oxide superconductors developed so far, BiSrCaCu oxide (Bi-2212 and Bi-2223) superconductors have been the most successful at being fabricated into wires and tapes of practical length and superconducting properties. These conductors can be wound into a magnet to generate a magnetic field of several tesla [2]. It has also been shown that Bi-2212 and Bi-2223 conductors can substantially raise the limit of magnetic field generation by a superconducting magnet [3].

In summer 1993, VAMAS-TWA16 started working on the test methods of critical currents in Bi-oxide superconductors. In September 1997, the TWA16 worked out a guideline (VAMAS guideline) on the critical current measurement method for Ag-sheathed Bi-2212 and Bi-2223 oxide superconductors. This pre-standardization work of VAMAS was taken as the base for the IEC standard, described in the present document, on the dc critical current test method of Ag-sheathed Bi-2212 and Bi-2223 oxide superconductors.

The test method covered in this International Standard is intended to give an appropriate and agreeable technical base to those engineers working in the field of superconductivity technology.

The critical current of composite superconductors like Ag-sheathed Bi-oxide superconductors depends on many variables. These variables need to be considered in both the testing and the application of these materials. Test conditions such as magnetic field, temperature and relative orientation of the specimen and magnetic field are determined by the particular application. The test configuration may be determined by the particular conductor through certain tolerances. The specific critical current criterion may be determined by the particular application. It may be appropriate to measure a number of test specimens if there are irregularities in testing.

¹⁾ The numbers in brackets refer to the bibliography.

SUPERCONDUCTIVITY –

Part 3: Critical current measurement – DC critical current of Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors

1 Scope

This part of IEC 61788 covers a test method for the determination of the dc critical current of short and straight Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors that have a monolithic structure and a shape of round wire or flat or square tape containing mono- or multicores of oxides.

This method is intended for use with superconductors that have critical currents less than 500 A and n -values larger than 5. The test is carried out with and without an applying external magnetic field. For all tests in a magnetic field, the magnetic field is perpendicular to the length of the specimen. In the test of a tape specimen in a magnetic field, the magnetic field is parallel or perpendicular to the wider tape surface (or one surface if square). The test specimen is immersed either in a liquid helium bath or a liquid nitrogen bath during testing. Deviations from this test method that are allowed for routine tests and other specific restrictions are given in this standard.

2 Normative reference

The following referenced document is indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815:2000, *International Electrotechnical Vocabulary (IEV) – Part 815: Superconductivity*