

INTERNATIONAL STANDARD

IEC
61788-7

Second edition
2006-10

Superconductivity –

Part 7: Electronic characteristic measurements – Surface resistance of superconductors at microwave frequencies

© IEC 2006 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

V

For price, see current catalogue

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Requirements	7
5 Apparatus.....	8
5.1 Measurement system	8
5.2 Measurement apparatus for R_S	9
5.3 Dielectric rods	11
6 Measurement procedure.....	12
6.1 Specimen preparation	12
6.2 Set-up	12
6.3 Measurement of reference level	12
6.4 Measurement of the frequency response of resonators.....	13
6.5 Determination of surface resistance of the superconductor and ϵ' and $\tan \delta$ of the standard sapphire rods.....	15
7 Precision and accuracy of the test method.....	16
7.1 Surface resistance	16
7.2 Temperature.....	17
7.3 Specimen and holder support structure	17
7.4 Specimen protection.....	18
8 Test report.....	18
8.1 Identification of test specimen	18
8.2 Report of R_S values	18
8.3 Report of test condition	18
Annex A (informative) Additional information relating to Clauses 1 to 8.....	19
Bibliography.....	32
Figure 1 – Schematic diagram of measurement system for temperature dependence of R_S using a cryocooler	8
Figure 2 – Typical measurement apparatus for R_S	10
Figure 3 – Insertion attenuation IA , resonant frequency f_0 and half power bandwidth Δf , measured at T Kelvin	13
Figure 4 – Reflection scattering parameters (S_{11} and S_{22}).....	15
Figure 5 – Term definitions in Table 4.....	17
Figure A.1 – Schematic configuration of several measurement methods for the surface resistance.....	20
Figure A.2 – Configuration of a cylindrical dielectric rod resonator short-circuited at both ends by two parallel superconductor films deposited on dielectric substrates	22
Figure A.3 – Computed results of the u - v and W - v relations for TE_{01p} mode.....	23
Figure A.4 – Configuration of standard dielectric rods for measurement of R_S and $\tan \delta$	24

Figure A.5 – Three types of dielectric resonators	24
Figure A.6 – Mode chart to design TE_{011} resonator short-circuited at both ends by parallel superconductor films [11]	27
Figure A.7 – Mode chart to design TE_{013} resonator short-circuited at both ends by parallel superconductor films [11]	28
Figure A.8 – Mode chart for TE_{011} closed-type resonator.....	29
Figure A.9 – Mode chart for TE_{013} closed-type resonator.....	30
Table 1 – Typical dimensions of pairs of standard sapphire rods for 12 GHz, 18 GHz and 22 GHz	11
Table 2 – Dimensions of superconductor film for 12 GHz, 18 GHz, and 22 GHz.....	12
Table 3 – Specifications on vector network analyzer.....	16
Table 4 – Specifications on sapphire rods.....	16

Currently in preview, click buy full version.

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –

**Part 7: Electronic characteristic measurements –
Surface resistance of superconductors
at microwave frequencies**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61788-7 has been prepared by IEC technical committee 90: Superconductivity.

This second edition cancels and replaces the first edition, published in 2002, of which it constitutes a technical revision. Examples of technical changes made are: 1) closed type resonators are recommended from the viewpoint of the stable measurements, 2) uniaxial-anisotropic characteristics of sapphire rods are taken into consideration for designing the size of the sapphire rods, and 3) recommended measurement frequency of 18 GHz and 22 GHz are added to 12 GHz described in the first edition.

The text of this standard is based on the following documents:

FDIS	Report on voting
90/193/FDIS	90/198/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 61788 consists of the following parts, under the general title *Superconductivity*:

- Part 1: Critical current measurement – DC critical current of Cu/Nb-Ti composite superconductors
- Part 2: Critical current measurement – DC critical current of Nb₃Sn composite superconductors
- Part 3: Critical current measurement – DC critical current of Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors
- Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti composite superconductors
- Part 5: Matrix to superconductor volume ratio measurement – Copper to superconductor volume ratio of Cu/Nb-Ti composite superconductors
- Part 6: Mechanical properties measurement – Room temperature tensile tests of Cu/Nb-Ti composite superconductors
- Part 7: Electronic characteristic measurements – Surface resistance of superconductors at microwave frequencies
- Part 8: AC loss measurements – Total AC loss measurement of Cu/Nb-Ti composite superconducting wires exposed to a transverse alternating magnetic field by a pickup coil method
- Part 9: Measurements for bulk high temperature superconductors – Trapped flux density of large grain oxide superconductors
- Part 10: Critical temperature measurement – Critical temperature of Nb-Ti, Nb₃Sn, and Bi-system oxide composite superconductors by a resistance method
- Part 11: Residual resistance ratio measurement – Residual resistance ratio of Nb₃Sn composite superconductors
- Part 12: Matrix to superconductor volume ratio measurement – Copper to non-copper volume ratio of Nb₃Sn composite superconducting wires
- Part 13: AC loss measurements – Magnetometer methods for hysteresis loss in Cu/Nb-Ti multifilamentary composites

The committee has decided that the contents of this publication will remain unchanged until the maintenance release date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

Since the discovery of some Perovskite-type Cu-containing oxides, extensive research and development (R & D) work on high-temperature oxide superconductors has been, and is being, made worldwide, and its application to high-field magnet machines, low-loss power transmission, electronics and many other technologies is in progress.

In various fields of electronics, especially in telecommunication fields, microwave passive devices such as filters using oxide superconductors are being developed and are undergoing on-site testing [1,2]¹⁾.

Superconductor materials for microwave resonators, filters, antenna and delay lines have the advantage of very low loss characteristics. Knowledge of this parameter is of primary importance for the development of new materials on the supplier side and for the design of superconductor microwave components on the customer side. The parameters of superconductor materials needed for the design of microwave low loss components are the surface resistance R_s and the temperature dependence of the surface resistance.

Recent advances in high T_c superconductor (HTS) thin films with R_s several orders of magnitude lower than that of normal metals have increased the need for a reliable characterization technique to measure this property [3,4]. Traditionally, the R_s of Nb or any other low temperature superconducting material was measured by first fabricating an entire three dimensional resonant cavity and then measuring its Q value. The R_s could be calculated by solving the EM field distribution inside the cavity. Another technique involves placing a small sample inside a larger cavity. This technique has many forms but usually involves the uncertainty introduced by extracting the loss contribution due to the HTS films from the experimentally measured total loss of the cavity.

The best HTS samples are epitaxial films grown on flat crystalline substrates and no high quality films have been grown on any curved surface so far. What is needed is a technique that: can use these small flat samples; requires no sample preparation; does not damage or change the film; is highly repeatable; has great sensitivity (down to 1/1 000th the R_s of copper); has great dynamic range (up to the R_s of copper); can reach high internal powers with only modest input powers; and has broad temperature coverage (4,2 K to 150 K).

The dielectric resonator method is selected among several methods [5,6,7] to determine the surface resistance at microwave frequencies because it is considered to be the most popular and practical at present. Especially, the sapphire resonator is an excellent tool for measuring the R_s of HTS materials [8,9].

The test method given in this standard can be also applied to other superconductor bulk plates including low T_c material.

This standard is intended to provide an appropriate and agreeable technical base for the time being to engineers working in the fields of electronics and superconductivity technology.

The test method covered in this standard is based on the VAMAS (Versailles Project on Advanced Materials and Standards) pre-standardization work on the thin film properties of superconductors.

1) Figures in square brackets refer to the Bibliography.

SUPERCONDUCTIVITY –

Part 7: Electronic characteristic measurements – Surface resistance of superconductors at microwave frequencies

1 Scope

This part of IEC 61788 describes measurement of the surface resistance of superconductors at microwave frequencies by the standard two-resonator method. The object of measurement is the temperature dependence of R_s at the resonant frequency.

The applicable measurement range of surface resistances for this method is as follows:

- Frequency: 8 GHz < f < 30 GHz
- Measurement resolution: 0,01 m Ω at 10 GHz

The surface resistance data at the measured frequency, and that scaled to 10 GHz, assuming the f^2 rule for comparison, are reported.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815, *International Electrotechnical Vocabulary (IEV) – Part 815: Superconductivity*