

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Dielectric and resistive properties of solid insulating materials –
Part 2-1: Relative permittivity and dissipation factor – Technical frequencies
(0,1 Hz to 10 MHz) – AC methods**

**Propriétés diélectriques et résistives des matériaux isolants solides –
Partie 2-1: Permittivité relative et facteur de dissipation – Fréquences techniques
(0,1 Hz à 10 MHz) – Méthodes en courant alternatif**



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient 21 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Dielectric and resistive properties of solid insulating materials –
Part 2-1: Relative permittivity and dissipation factor – Technical frequencies
(0,1 Hz to 10 MHz) – AC methods**

**Propriétés diélectriques et résistives des matériaux isolants solides –
Partie 2-1: Permittivité relative et facteur de dissipation – Fréquences techniques
(0,1 Hz à 10 MHz) – Méthodes en courant alternatif**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 17.220.99; 29.035.01

ISBN 978-2-8322-5414-1

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Method of test	7
4.1 General theory.....	7
4.2 Power supply (voltage)	10
4.3 Equipment	10
4.3.1 Accuracy	10
4.3.2 Choice of measuring methods.....	10
4.3.3 Measurement setup with applied electrodes to the material	11
4.4 Calibration	14
4.5 Test specimen	14
4.5.1 General	14
4.5.2 Recommended dimensions of test specimen and electrode arrangements	15
4.5.3 Manufacturing of test specimen	15
4.5.4 Number of test specimen	15
4.5.5 Conditioning and pre-treatment of test specimen	16
4.6 Procedures for specific materials	16
5 Test procedure	16
5.1 General.....	16
5.2 Calculation of permittivity and relative permittivity.....	16
5.2.1 Relative permittivity	16
5.2.2 The dielectric dissipation factor $\tan \delta$	16
6 Report	16
7 Repeatability and reproducibility	17
Annex A (informative) Basic fundamentals	18
A.1 Error for the effective area in guard ring electrodes – Examples with $d_1 = 25$ mm, 50 mm or 100 mm and $w = 1$ mm	18
A.2 Computation of edge correction of effective area	19
A.3 Determining A and calculating B	20
Bibliography.....	21
Figure 1 – Dielectric dissipation factor	8
Figure 2 – Equivalent circuit diagrams	9
Figure 3 – Cylindrical electrode with guard ring for plate designed specimen	12
Figure 4 – Specimen with liquid electrodes	13
Figure A.1 – Area error of h in $e\%$ with $\epsilon_r = 1$	18
Figure A.2 – Area error of h in $e\%$ with $\epsilon_r = \infty$	18
Figure A.3 – Error calculation for different ϵ_r and d_1	18
Figure A.4 – Flow chart for the computation of edge correction of effective area	19
Figure A.5 – Factor H versus gap and height	20
Table 1 – Test specimen.....	15

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**DIELECTRIC AND RESISTIVE PROPERTIES
OF SOLID INSULATING MATERIALS –****Part 2-1: Relative permittivity and dissipation factor –
Technical frequencies (0,1 Hz to 10 MHz) – AC methods**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization, comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with the conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, issue to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International standard IEC 62631-2-1 has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems.

This first edition cancels and replaces the first edition IEC 60250, published in 1969. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) technical frequencies confined to AC methods;
- b) update on measurements on solid dielectric materials.

The text of this standard is based on the following documents:

FDIS	Report on voting
112/412/FDIS	112/417/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62631 series, published under the general title *Dielectric and resistive properties of solid insulating materials*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Tan δ , also called loss tangent, or dissipation factor is a basic parameter for the quality of insulating materials. The measurement of capacitance and loss angle is a classical method well established in the industry over 100 years.

The dissipation factor (tan δ) is dependent on several parameters, such as electrode design, material characteristics, environmental issues, moisture, temperature, voltage applied, and highly dependent on frequencies, the accuracy of measuring apparatus and other parameters applied to the measured specimen.

The frequency range is limited, depending on the test cell and electrode design, the dimension of the samples and connection leads. In this standard the parameters for the frequencies applied are therefore limited in the range of very low frequency (VLF) from less than 1 Hz and up to 10 MHz. However, measuring instruments can provide a broader frequency range, whereby the usable and suitable frequency range is limited by the whole test setup.

DIELECTRIC AND RESISTIVE PROPERTIES OF SOLID INSULATING MATERIALS –

Part 2-1: Relative permittivity and dissipation factor – Technical frequencies (0,1 Hz to 10 MHz) – AC methods

1 Scope

This part of IEC 62631 describes test methods for the determination of permittivity and dissipation factor properties of solid insulating materials (AC methods from 0,1 Hz up to 10 MHz).

NOTE This part of the standard mainly considers measuring setups with guard-electrodes.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60212, *Standard conditions for use prior to and during the testing of solid electrical insulating materials*

ISO 4593, *Plastics – Film and sheeting – Determination of thickness by mechanical scanning*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

electrical insulating material

solid with negligibly low electric conductivity, used to separate conducting parts at different electrical potentials

Note for entry: The term "electrical insulating material" is sometimes used in a broader sense to designate also insulating liquids and gases. Insulating liquids are covered by IEC 60247.

3.2

dielectric properties

comprehensive behaviour of an insulating material measured with AC comprising the capacitance, absolute permittivity, relative permittivity, relative complex permittivity, dielectric dissipation factor

3.3

absolute permittivity

electric flux density divided by the electric field strength