

IPC-1601 **2010**

Printed Board Handling and Storage Guidelines

August 2010

A standard developed by IPC

Association Connecting Electronics Industries



The Principles of Standardization

In May 1995 the IPC's Technical Activities Executive Committee (TAEC) adopted Principles of Standardization as a guiding principle of IPC's standardization efforts.

Standards Should:

- Show relationship to Design for Manufacturability (DFM) and Design for the Environment (DFE)
- Minimize time to market
- Contain simple (simplified) language
- Just include spec information
- Focus on end product performance
- Include a feedback system on use and problems for future improvement

Standards Should Not:

- Inhibit innovation
- Increase time-to-market
- Keep people out
- Increase cycle time
- Tell you how to make something
- Contain anything that cannot be defended with data

Notice

IPC Standards and Publications are designed to serve the public interest through eliminating misunderstandings between manufacturers and purchasers, facilitating interchangeability and improvement of products, and assisting the purchaser in selecting and obtaining with minimum delay the proper product for his particular need. Existence of such Standards and Publications shall not in any respect preclude any member or nonmember of IPC from manufacturing or selling products not conforming to such Standards and Publication, nor shall the existence of such Standards and Publications preclude their voluntary use by those other than IPC members, whether the standard is to be used either domestically or internationally.

Recommended Standards and Publications are adopted by IPC without regard to whether their adoption may involve patents on articles, materials, or processes. By such adoption, IPC does not assume any liability to any patent owner, nor do they assume any obligation whatever to parties adopting the Recommended Standard or Publication. Users are also wholly responsible for protecting themselves against all claims of liabilities for patent infringement.

IPC Position Statement on Specification Revision Change

It is the position of IPC's Technical Activities Executive Committee that the use and implementation of IPC publications is voluntary and is part of a relationship entered into by customer and supplier. When an IPC publication is updated and a new revision is published, it is the opinion of the TAEC that the use of the new revision as part of an existing relationship is not automatic unless required by the contract. The TAEC recommends the use of the latest revision. Adopted October 6, 1998

Why is there a charge for this document?

Your purchase of this document contributes to the ongoing development of new and updated industry standards and publications. Standards allow manufacturers, customers, and suppliers to understand one another better. Standards allow manufacturers greater efficiencies when they can set up their processes to meet industry standards, allowing them to offer their customers lower costs.

IPC spends hundreds of thousands of dollars annually to support IPC's volunteers in the standards and publications development process. There are many rounds of drafts sent out for review and the committees spend hundreds of hours in review and development. IPC's staff attends and participates in committee activities, typesets and circulates document drafts, and follows all necessary procedures to qualify for ANSI approval.

IPC membership dues have been kept low to allow as many companies as possible to participate. Therefore, the standards and publications revenue is necessary to complement dues revenue. The price schedule offers a 50% discount to IPC members. If your company buys IPC standards and publications, why not take advantage of this and the many other benefits of IPC membership as well? For more information on membership in IPC, please visit www.ipc.org or call 847/597-2872.

Thank you for your continued support.



IPC-1601

Printed Board Handling and Storage Guidelines

Developed by the Board Storage and Handling Subcommittee (D-35)
within the Rigid Printed Board Committee (D-30) of IPC

Users of this publication are encouraged to participate in the
development of future revisions.

Contact:

IPC
3000 Lakeside Drive, Suite 309S
Bannockburn, Illinois
60015-1249
Tel 847615.7100
Fax 847615.7105

This Page Intentionally Left Blank

Currently in preview, click buy full version

2

Acknowledgment

Any document involving a complex technology draws material from a vast number of sources. While the principal members of the Board Storage and Handling Subcommittee (D-35) of the Rigid Printed Board Committee (D-30) are shown below, it is not possible to include all of those who assisted in the evolution of this standard. To each of them, the members of the IPC extend their gratitude.

Rigid Printed Board Committee

Chair
Vicka White
Honeywell Inc. Air Transport Systems

Vice-Chair
Debra Obitz
Trace Laboratories - East

Board Storage and Handling Subcommittee

Chair
Tom Kemp
Rockwell Collins

Vice-Chair
C. Don Dupriest
Lockheed Martin Missiles
and Fire Control

Technical Liaisons of the IPC Board of Directors

Peter Bigelow
IMI Inc.

Sammy Yi
Flextronics International

Board Storage and Handling Subcommittee

Mumtaz Y. Bora, Peregrine Semiconductor	Christopher Hunt, National Physical Laboratory	Robert Roessler, Lineage Power Corp.
Beverly Christian, Research In Motion Limited	Joseph E. Kane, BAE Systems Platform Solutions	Karl Sauter, Oracle America, Inc.
Ashley Collier, Celestica	Harold Kleinfeldt, RadiSys Corporation	Douglas Schueller, AbelConn, LLC
Glenn Dody, Dody Consulting	Robert L. Lazzara, Circuit Connect Inc.	Joseph Smetana, Alcatel-Lucent
Harold Ellison, Quantum Corporation	Michael G. Luke, Raytheon Company	Bhanu Sood, University of Maryland
Gary M. Ferrari, FTG Circuits	Clifford M. Hoot, Boeing Company	Richard Stadem, General Dynamics Information Systems, Inc.
Lionel Fullwood, WKK Distribution Ltd.	Brian W. Jensen, Continental AG	Jeff Taylor, IBM Corporation
Michael J. Gay, Isola Group	Chris Mananna, Robisan Laboratory Inc.	Sam Theabo, Plexus Corp.- Training Center
Chris Goodall, Celestica	Kenneth Manning, Raytheon Company	Bill Vuono, Raytheon Company
Michael Green, Lockheed Martin Space Systems Company	Matthew McQueen, NSW Crane	Vicka White, Honeywell Inc. Air Transport Systems
Ben Gumpert, Lockheed Martin Missile & Fire Control	Steven M. Nolan, Lockheed Martin Maritime Systems & Sensors	Dewey Whittaker, Honeywell Inc. Air Transport Systems
Philip Henault, Raytheon Company	Gerard O'Brien, Solderability Testing & Solutions, Inc.	
David D. Hillman, Rockwell Collins	Michael Paddack, Boeing Company	

Table of Contents

1 INTRODUCTION	1	4.1.3	Effects on Final Finish Solderability	7
1.1 Background	1	4.1.4	Storage and Packaging Environment	9
1.2 Scope	1	4.1.5	ESD Concerns	9
1.3 Application	1	4.2	Packaging Materials	9
1.4 Terms and Definitions	1	4.2.1	Water Vapor Transmission Rate (WVTR)	9
1.4.1 Humidity Indicator Card (HIC)	1	4.2.2	Typical Packaging Material Types	9
1.4.2 Moisture Barrier Bag (MBB)	1	4.2.3	Desiccant	9
1.4.3 Subcomposite	1	4.2.4	Humidity Indicator Card (HIC)	9
1.4.4 Water Vapor Transmission Rate (WVTR)	1	4.2.5	Laminate Witness Coupons	9
1.4.5 Sulfur Free	1	4.3	Packaging Methods	10
1.4.6 Dry Packaging	1	4.3.1	Internal (Dry Packaging)	10
2 APPLICABLE DOCUMENTS	1	4.3.2	External Packaging	10
2.1 IPC	1	4.4	Marking	10
2.2 Joint Industry Standards	2	4.4.1	Lead-Free/ RoHS compliance	10
2.3 Electrostatic Discharge Association (ESD)	2	4.4.2	ESD	11
2.4 Europa	2	4.4.3	Moisture	11
2.5 International Aerospace Quality Group	2	4.4.4	Other Markings	11
2.6 International Organization for Standardization	2	5 PRINTED BOARD RECEIVING, STORAGE AND ASSEMBLY	11	
3 PRINTED BOARD FABRICATION AND PACKAGING (HANDLING)	2	5.1	Before Opening	11
3.1 Printed Board Materials	2	5.2	Storage Location (Stock Room)	11
3.1.1 Bonding Materials, Prepreg and Resin Coated Foils	3	5.3	Shop Opening A Moisture Barrier Bag	11
3.1.2 Copper Clad Laminates	3	5.4	Production Environment (Temperature, Humidity, and Atmosphere)	12
3.2 Inner Layer Production	3	5.5	Storage Containers (Shop Floor)	12
3.2.1 Phototooling	3	5.6	Soldering Operations	12
3.2.2 Process Equipment	3	5.7	Maximum Acceptable Moisture Content (MAMC)	12
3.2.3 Moisture Concerns for Etched Cores and Subcomposites	3	5.8	Evaluating Moisture Content	13
3.3 Manufacture of the Laminated Panels/Printed Boards	4			
3.3.1 Processing Validation and Control	4			
3.3.2 Handling and Transport of Product	4			
3.3.3 Environment	5			
3.3.4 Test	5			
3.3.5 Inspection	5			
3.3.6 Recommended Moisture Levels Prior to Packaging	5			
3.4 Baking for Moisture Removal	6			
3.4.1 Problems Caused by Baking	6			
3.4.2 Baking Environment	6			
3.4.3 Baking Considerations	6			
3.4.4 Establishing Baking Profiles	7			
4 PACKAGING, STORAGE, AND SHIPMENT	7			
4.1 Packaging Evaluation	7			
4.1.1 Moisture Absorption	7			
4.1.2 Physical Attributes	7			

Figures

Figure 4-1	EOS/ESD S8.1 Protective Symbol	10
Figure 4-2	Moisture Sensitivity Caution Symbol	11

Table

Table 3-1	Recommendations for Printed Board Baking Profiles	7
-----------	---	---

PRINTED BOARD HANDLING AND STORAGE GUIDELINES

1 INTRODUCTION

1.1 Background Historically, the printed board industry has relied on military specifications and guidelines to define packaging methods to preserve the quality and reliability of printed boards during shipment and storage. However, many of these documents are obsolete, incomplete, do not address lead-free assembly processes, or do not cover newer laminates or final finishes. Additionally, the proliferation of alternative final finishes has produced concerns and requirements for printed board packaging and handling to preserve the finish and assure good solderability.

1.2 Scope This document provides suggestions for proper handling, packaging materials and methods, environmental conditions, and storage for printed boards. These guidelines are intended to protect printed boards from contamination, physical damage, solderability degradation, electrostatic discharge (ESD) (when necessary), and moisture uptake. Moisture absorbed in printed board laminates expands at soldering temperatures, and in some cases, the resulting vapor pressure can cause internal delamination or excessive strain on plated-hole walls and other structures. This is especially challenging with the higher temperatures used for lead-free soldering.

This document covers all phases from the manufacture of the bare printed board, through delivery, receiving, stocking, assembly, and soldering. As a guideline, this information is to be used with, and is secondary to, the established requirements in such documents as the IPC-4550 series for alternate final finishes.

1.3 Application The target audience includes those involved in all phases of printed board design, manufacture, assembly, shipping, storage, and possible warranty activities. Information herein has been supplied by all of these functions, as well as the material and equipment suppliers.

1.4 Terms and Definitions The definition of all terms used herein shall be as specified in IPC-T-50 and as defined in 1.4.1 through 1.4.6.

1.4.1 Humidity Indicator Card (HIC) A card on which a moisture sensitive chemical is applied such that it will make a significant, perceptible change in color (hue), typically from blue (dry) to pink (wet) when the indicated relative humidity is exceeded. The HIC is packed inside the moisture-barrier bag (MBB), along with a desiccant, to aid in determining the level of moisture to which the moisture-sensitive devices or printed boards have been subjected.

1.4.2 Moisture Barrier Bag (MBB) A bag designed to restrict the transmission of water vapor and used to pack moisture sensitive devices. An MBB is made of material with a low WVTR (see 4.2.1).

1.4.3 Subcomposite In sequential lamination, a structure composed of more than two layers that have been laminated together, and which will subsequently be laminated with other layers into a complete printed board.

1.4.4 Water Vapor Transmission Rate (WVTR) A measure of the permeability of plastic film or metallized plastic film material to moisture, an important rating for moisture barrier bags (MBBs).

1.4.5 Sulfur Free Chemicals that are unlikely to express corrosive sulfur compounds like H₂S or SO₂.

1.4.6 Dry Packaging Packaging that consists of desiccant material and a Humidity Indicator Card (HIC) sealed with the printed boards inside a Moisture Barrier Bag (MBB) (See 4.3.1).

2 APPLICABLE DOCUMENTS

2.1 IFC

IPC-6013-001 Handbook and Guide to Supplement J-STD-001

IPC-T-50 Terms and Definitions for Interconnecting and Packaging Electronic Circuits

IPC-A-311 Process Controls for Phototool Generation and Use

IPC-TR-585 Time, Temperature and Humidity Stress of Final Board Finish Solderability