

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS A 1404 : 2015

Method of test for waterproof agent
of cement for concrete construction

ICS 91.100.10

Reference number : JIS A 1404 : 2015 (E)

A 1404 : 2015

Date of Establishment: 1960-03-01

Date of Revision: 2015-02-20

Date of Public Notice in Official Gazette: 2015-02-20

Investigated by: Japanese Industrial Standards Committee
Standards Board for ISO area
Technical Committee on Architecture

JIS A 1404:2015, First English edition published in 2015-12

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

KK/AT

PROTECTED BY COPYRIGHT

Contents

	Page
Introduction.....	1
1 Scope.....	1
2 Normative references.....	1
3 Testing apparatus.....	2
4 Sample.....	2
5 Material to be used.....	2
6 Specimen.....	2
6.1 Dimensions of specimen.....	2
6.2 Number of specimens.....	3
6.3 Mixing of mortar.....	3
6.4 Mixing method.....	3
6.5 Moulding.....	3
6.6 Removal of formwork, curing and drying.....	4
7 Test procedures.....	4
7.1 General.....	4
7.2 Setting time test.....	4
7.3 Soundness test.....	4
7.4 Strength test.....	4
7.5 Water absorption test.....	4
7.6 Water permeability test.....	5
8 Calculation.....	7
8.1 Strength ratio.....	7
8.2 Water absorption ratio.....	7
8.3 Water permeability ratio.....	8
9 Test report.....	8
Annex A (informative) Comparison table between previous and current editions of this Standard on technically significant revisions.....	9

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law. Consequently **JIS A 1404:2013** is replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Method of test for waterproof agent of cement for concrete construction

Introduction

This Japanese Industrial Standard was established in 1960 and has gone through four revisions up to the present. The last revision was made in 2013, and the revision at this time is to correspond to the actual situation in Japan.

No corresponding International Standard has been established at this point. The comparison table between previous and current editions of this Standard on technically significant revisions is given in Annex A.

1 Scope

This Standard specifies the test method for the waterproof agent of cement (hereafter referred to as “waterproof agent”) used by mixing it into mortar or concrete for construction.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS R 5201 *Physical testing methods for cement*

JIS R 5210 *Portland cement*

JIS Z 8801-1 *Test sieves—Part 1: Test sieves of metal wire cloth*

3 Testing apparatus

3.1 Balance The weighing capacity shall be 2 kg or more and the graduation shall be 0.1 g or smaller.

3.2 Compacting bar

3.2.1 Compacting bar for strength test and water absorption test The compacting bar used for moulding specimens for strength test and specimens for water absorption test shall be as specified in **JIS R 5201**.

3.2.2 Compacting bar for water permeability test For the compacting bar used for moulding specimens for water permeability test, the thrust portion shall be a cube of which the size of all the sides is $35 \text{ mm} \pm 1 \text{ mm}$ and the mass shall be $1\,000 \text{ g} \pm 5 \text{ g}$.

3.3 Drier The drier shall have an exhaust port and shall be capable of keeping the inside temperature of tank at $80 \text{ }^\circ\text{C}$.

3.4 Container for water absorption test The container used for water absorption test shall be watertight, and the depth shall be about 5 cm.