

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS A 5523 : 2021

(JISF)

Weldable hot rolled steel sheet piles

ICS 25.160.20 ; 77.140.70;91.100.15

Reference number : JIS A 5523 : 2021 (E)

Date of Establishment: 2000-11-20

Date of Revision: 2021-02-22

Date of Public Notice in Official Gazette: 2021-02-22

Investigated by: Japanese Industrial Standards Committee

Standards Board for ISO area

Technical Committee on Metal and Inorganic Materials

JIS A 5523 : 2021, First English edition published in 2021-09

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2021

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

HN

Contents

		Page
1	Scope	1
2	Normative references	1
3	Term and definition	1
4	Symbols of grade	2
5	Chemical compositions	2
6	Carbon equivalent	2
7	Mechanical properties	3
7.1	Yield point or proof stress, tensile strength and elongation	3
7.2	Coupling tensile strength of steel sheet piles having straight line shape	3
7.3	Charpy absorbed energy	4
8	Shapes, dimensional tolerances and unit mass	4
9	Appearance	7
10	Tests	7
10.1	Chemical analysis	7
10.2	Mechanical tests	7
10.3	Coupling tensile test on steel sheet piles having straight line shape	9
11	Inspection	10
12	Re-inspection	11
13	Marking	11
14	Report	11
	Annex A (normative) Steel — nitride type nitrogen determination method	12

Foreword

This Japanese Industrial Standard has been revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by The Japan Iron and Steel Federation (JISF) with a draft being attached, based on the provision of Article 12, paragraph (1) of the Industrial Standardization Act applied mutatis mutandis pursuant to the provision of Article 16 of the said Act. This edition replaces the previous edition (**JIS A 5523:2012**), which has been technically revised.

However, **JIS A 5523: 2012** may be applied in the **JIS** mark certification based on the relevant provisions of Article 30, paragraph (1), etc. of the Industrial Standardization Act until 21 February 2022.

This **JIS** document is protected by the Copyright Act.

It should be noted that being in conformance with this Standard may come under the use of the patent rights and other rights held by the following:

— Name: Nippon Steel Corporation Address: 2-6-1, Marunouchi, Chiyoda-ku, Tokyo

The holder/holders of this/these patent right/rights and other rights has/have indicated an intention of granting license to anyone under the nondiscriminatory and reasonable conditions, except to the other relevant holders of the patent rights and other rights related to this Standard who will not grant their license under the same conditions.

It should be noted that following this Standard does not always refer to granting a free license.

Some parts of this Standard may conflict with patent rights and other rights other than mentioned above. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights and other rights.

The “patent rights and other rights” as mentioned here include patent right, published patent application or utility model right.

Weldable hot rolled steel sheet piles

1 Scope

This Japanese Industrial Standard specifies the requirements¹⁾ for hot rolled steel sheet piles (hereafter referred to as steel sheet piles) especially excellent in weldability which are used for sheathing, coffering, structural foundations and other similar applications.

Note¹⁾ This Standard also specifies the determination methods of carbon equivalent, free nitrogen and Charpy absorbed energy, which are not described in **JIS A 5528**.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS G 0320 *Standard test method for heat analysis of steel products*

JIS G 0321 *Product analysis and its tolerance for wrought steel*

JIS G 0404 *Steel and steel products — General technical delivery requirements*

JIS G 0415 *Steel and steel products — Inspection documents*

JIS G 1201 *Iron and steel — General rules for analytical methods*

JIS G 1228 *Iron and steel — Methods for determination of nitrogen content*

JIS G 3192 *Dimensions, mass and permissible variations of hot rolled steel sections*

JIS R 6010 *Coated abrasive grain sizes*

JIS Z 2241 *Metallic materials — Tensile testing — Method of test at room temperature*

JIS Z 2242 *Method for Charpy pendulum impact test of metallic materials*

3 Term and definition

For the purpose of this Standard, the following term and definition apply.

3.1

free nitrogen

nitrogen dissolved in steel other than nitrogen in nitride (nitride type nitrogen) which is chemically combined with alloy elements having high affinity with nitrogen (aluminium, titanium, vanadium, etc.) and precipitated in steel

However, nitrogen contained in silicon nitride is to be included in free nitrogen.