

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS G 0802 : 2016

(JSSA/JSA)

**Ultrasonic testing of stainless steel
plates**

ICS 77.040.20;77.140.20

Reference number : **JIS G 0802 : 2016 (E)**

Date of Establishment: 1998-07-20

Date of Revision: 2016-11-21

Date of Public Notice in Official Gazette: 2016-11-21

Investigated by: Japanese Industrial Standards Committee

Standards Board for ISO area

Technical Committee on Metal and Inorganic

Materials

JIS G 0802:2016, First English edition published in 2017-03

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2017

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

DH/AT

Contents

	Page
Introduction.....	1
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
3A General matters.....	2
4 Testing method.....	2
5 Inspection engineer.....	2
6 Testing apparatus.....	3
6.1 Composition of testing apparatus.....	3
6.2 Flaw detector.....	3
6.3 Probe.....	4
6.4 Scanning and indexing apparatus, manipulator, automatic alarm, and marking or recording equipment.....	5
6.5 Test blocks.....	5
7 Test procedure.....	6
7.1 Type of flaw detection.....	6
7.2 Time of flaw detection.....	6
7.3 Test surface.....	6
7.4 Coupling medium.....	6
7.5 Scanning procedure.....	6
7.6 Flaw detection area (scanning area and range).....	7
8 Application and setting of working sensitivity and setting of reference lines.....	10
8.1 General matters.....	10
8.2 Application of working sensitivity.....	10
8.3 Evaluation method using distance-amplitude characteristic curve.....	10
8.4 Setting of working sensitivity.....	10
8.5 Setting of reference lines.....	11
9 Classification of flaws.....	12
9.1 Classification of flaws and identification symbols.....	12
9.2 Flaw dimensions and ultrasonic flaw length.....	13
9.3 Recording of flaws.....	14
10 Evaluation of flaws.....	14
10.1 Flaws subject to evaluation.....	14

10.2	Conversion for evaluation	14
10.3	Number of major flaws (× flaws)	15
10.4	Maximum ultrasonic flaw length of a single flaw	15
10.5	Flaw density	15
11	Criteria for flaw evaluation	15
12	Test report	16
Annex JA (normative)	Type E reference block for double crystal probe (RB-E-S)	17
Annex JB (normative)	Sensitivity-correcting reference block (RB-S)	18
Annex JC (normative)	Performance of double crystal probe	20
Annex JD (normative)	Preparation of distance-amplitude characteristic curve and method for echo height division	22
Annex JE (informative)	Comparison table between JIS and corresponding International Standard	25

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of the proposal for revision of Japanese Industrial Standard submitted by Japan Stainless Steel Association (JSSA)/ Japanese Standards Association (JSA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14.

Consequently **JIS G 0802:1998** is replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Ultrasonic testing of stainless steel plates

Introduction

This Japanese Industrial Standard has been prepared based on the second edition of **ISO 17577**, published in 2016, with some modifications of the technical contents.

The vertical lines on both sides and dotted underlines indicate addition to the corresponding International Standard. A list of modifications with the explanations is given in Annex JE.

1 Scope

This Standard specifies the ultrasonic testing of stainless steel plates of 6 mm or over up to and including 200 mm in thickness.

This ultrasonic testing also applies to nickel plates, nickel alloy plates and superalloy plates. (Stainless steel plates, nickel plates, nickel alloy plates and superalloy plates will hereinafter be collectively referred to as flat products.)

Additionally, this Standard may be applied to products less than 6 mm or over 200 mm in thickness by agreement between the purchaser and the manufacturer.

NOTE : The International Standard corresponding to this Standard and the symbol of degree of correspondence are as follows:

ISO 17577:2016 *Steel—Ultrasonic testing of steel flat products of thickness equal to or greater than 6 mm (MOD)*

In addition, symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are **IDT** (identical), **MOD** (modification), and **NEQ** (not equivalent) according to **ISO/IEC Guide 21-1**.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS B 0601 *Geometrical Product Specifications (GPS)—Surface texture: Profile method—Terms, definitions and surface texture parameters*

JIS B 8236 *Alternative standard for construction of pressure vessels*

JIS G 0431 *Steel products—Employer's qualification system for non-destructive testing (NDT) personnel*

JIS G 4304 *Hot-rolled stainless steel plate, sheet and strip*

JIS G 4305 *Cold-rolled stainless steel plate, sheet and strip*

JIS Z 2300 *Terms and definitions of nondestructive testing*

JIS Z 2305 *Non-destructive testing—Qualification and certification of NDT personnel*