

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS G 1258-1 : 2014

(JISF)

Iron and steel—ICP atomic
emission spectrometric method—
Part 1: Determination of various
elements—Decomposition with
acids and fusion with potassium
disulfate

ICS 77.080.10;77.080.20

Reference number : JIS G 1258-1 : 2014 (E)

Date of Establishment: 2007-07-20

Date of Revision: 2014-02-20

Date of Public Notice in Official Gazette: 2014-02-20

Investigated by: Japanese Industrial Standards Committee
Standards Board
Technical Committee on Iron and Steel

JIS G 1258-1:2014, First English edition published in 2015-11

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

NH/AT

Contents

	Page
Introduction.....	1
1 Scope.....	1
2 Normative references.....	2
3 General rules.....	2
4 Summary.....	2
5 Reagents.....	3
6 ICP atomic emission spectrometer.....	8
6.1 Performance reference.....	8
6.2 Examination frequency of performance criteria.....	10
7 Weighing of sample.....	10
8 Operation.....	11
8.1 Cleaning of apparatus.....	11
8.2 Preparation of sample solution.....	11
8.3 Emission intensity measurement.....	12
9 Blank test.....	12
10 Spectrum overlap factor of coexisting component.....	12
11 Preparation of calibration curve.....	13
12 Calibration of calibration curve.....	14
13 Calculation.....	14
14 Precision.....	15

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry, through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by The Japan Iron and Steel Federation (JISF) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14.

Consequently, **JIS G 1258-1:2007** is replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

JIS G 1258 series consists of the following 8 parts under the general title “*Iron and steel—ICP atomic emission spectrometric method*”:

Part 0: General rules

Part 1: Determination of various elements—Decomposition with acids and fusion with potassium disulfate

Part 2: Determination of various elements—Decomposition with phosphoric and sulfuric acids

Part 3: Determination of various elements—Decomposition with acids and fusion with sodium carbonate

Part 4: Determination of nickel content—Dissolution in phosphoric and sulfuric acids or Dissolution in acids and fusion with potassium disulfate

Part 5: Determination of boron content—Dissolution in phosphoric and sulfuric acids

Part 6: Determination of boron content—Dissolution in acids and fusion with sodium carbonate

Part 7: Determination of boron content—Distillation as trimethyl borate

Iron and steel—ICP atomic emission spectrometric method—Part 1: Determination of various elements— Decomposition with acids and fusion with potassium disulfate

Introduction

This Japanese Industrial Standard has been established in 2007, and the revision at this time is to respond to the recent expansion of applicable elements.

No corresponding International Standard has been established at this point.

1 Scope

This Standard specifies ICP atomic emission spectrometric method using decomposition in acids and fusion with potassium disulfate to determine the content rate of 16 components specified in table 1 in steel. This method applies to the determination of each component within the range specified in table 1, however it is not applicable to steels in which the iron content (mass fraction) is less than 92 %, steels which contain one or more components of content rate over the maximum limit of determination specified in table 1, or steels which contain components not specified in table 1 (e.g. carbon) by mass fraction 1.0 % or more (for tungsten, mass fraction 0.1 % or more).

Table 1 Applicable element and determination range

Applicable element	Determination range [mass fraction (%)]
Silicon	≥ 0.01 ≤ 0.60
Manganese	≥ 0.01 ≤ 2.00
Phosphorus	≥ 0.003 ≤ 0.10
Nickel	≥ 0.01 ≤ 4.00
Chromium	≥ 0.01 ≤ 3.00
Molybdenum	≥ 0.01 ≤ 1.20
Copper	≥ 0.01 ≤ 0.50
Vanadium	≥ 0.002 ≤ 0.50
Cobalt	≥ 0.003 ≤ 0.20
Titanium	≥ 0.001 ≤ 0.30
Aluminium	≥ 0.004 ≤ 0.10
Calcium	≥ 0.000 5 ≤ 0.005
Magnesium	≥ 0.000 5 ≤ 0.011
Arsenic	≥ 0.001 ≤ 0.012
Zirconium	≥ 0.010 ≤ 0.060
Zinc	≥ 0.001 ≤ 0.005