

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS G 3478 : 2015

(JISF)

**Carbon steel tubes for general machine
structural purposes**

ICS 77.140.10 ; 77.140.75

Reference number : JIS G 3478 : 2015 (E)

G 3478 : 2015

Date of Establishment: 2015-05-20

Date of Public Notice in Official Gazette: 2015-05-20

Investigated by: Japanese Industrial Standards Committee

Standards Board for ISO area

Technical Committee on Metal and Inorganic Materials

JIS G 3478 : 2015, First English edition published in 2015-08

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

HN

Contents

	Page
Introduction	1
1 Scope	1
2 Normative references	1
3 Designation of grade	1
4 Manufacturing method	1
5 Chemical composition	2
6 Flattening resistance	3
7 Dimensions and dimensional tolerances	3
7.1 Dimensions	3
7.2 Dimensional tolerances	4
8 Appearance	4
9 Tests	5
9.1 Chemical analysis	5
9.2 Flattening test	5
10 Inspection and re-inspection	7
10.1 Inspection	7
10.2 Re-inspection	7
11 Marking	7
12 Report	8
Annex A (informative) Examples of test to be applied by the agreement between the purchaser and the manufacturer	9

Foreword

This translation has been made based on the original Japanese Industrial Standard established by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee according to the proposal for establishment of Japanese Industrial Standard submitted by The Japan Iron and Steel Federation (JISF) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Carbon steel tubes for general machine structural purposes

Introduction

The increasing demand for steel tubes made of steels specified in JIS G 4051 led to the need for establishment of Japanese Industrial Standard exclusively intended for steel tubes. In order to respond to such market needs, this Standard has been established based on the chemical composition specified in JIS G 4051.

In addition to the specification items in the main body, the examples of test to be applied by the agreement between the purchaser and the manufacturer are given in Annex A.

1 Scope

This Standard specifies the carbon steel tubes mainly used for machine parts (hereafter referred to as “tubes”).

2 Normative references

The following standards contain provisions which through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS G 0320 *Standard test method for heat analysis of steel products*

JIS G 0321 *Product analysis and its tolerance for wrought steel*

JIS G 0404 *Steel and steel products — General technical delivery requirements*

JIS G 0415 *Steel and steel products — Inspection documents*

JIS Z 8401 *Guide to the rounding of numbers*

3 Designation of grade

The tubes shall be classified into 23 grades, and the designation of grade and symbol of manufacturing method thereof shall be as given in Table 1.

NOTE : Designation of grade in Table 1 is expressed by suffixing TK to the designation of grade given in JIS G 4051.

4 Manufacturing method

The manufacturing method shall be as follows.

- a) The tubes shall be manufactured by combination of the tube manufacturing method and the finishing method which are indicated in Table 1. If required, the appropriate heat treatment may be designated on tubes.
- b) If required, the purchaser may designate the heat treatment.
- c) The shape of end of tube shall be plain-ended, unless otherwise specified.