

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS K 7351 : 2018

**Sensitive measurement method of
peroxide in plastics by detecting
ultra-weak photon emission**

ICS 83.080.01

Reference number : JIS K 7351 : 2018 (E)

K 7351 : 2018

Date of Establishment: 2018-01-22

Date of Public Notice in Official Gazette: 2018-01-22

Investigated by: Japanese Industrial Standards Committee
Standards Board for ISO area

Technical Committee on Chemical Products and
Analytical Methods

JIS K 7351:2018, First English edition published in 2018-11

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2018

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

KK/AT

Contents

		Page
1	Scope	1
2	Terms and definitions	1
3	Measurement principle	1
4	Sample	2
5	Chemiluminescence measuring apparatus	2
5.1	Composition of apparatus body	2
5.2	Composition of sample chamber	3
5.3	Installation environment for apparatus	4
6	Measurement method	4
6.1	Apparatus preparation	4
6.2	Confirmation of normal operation of apparatus	4
6.3	Measurement procedure	4
7	Display of measurement results	6
7.1	General requirements	6
7.2	Measurement in inert gas atmosphere	7
7.3	Measurement in oxidation accelerating atmosphere	8
8	Record of measurement results	9
Annex A (informative)	Detection of oxidation deterioration by chemiluminescence measurement	10
Annex B (informative)	Measurement of oxidation deterioration degree of the mainly-oxidized polyethylene (PE)	13
Annex C (informative)	Measurement of equilibrium chemiluminescence intensity and evaluation of antioxidant capacity	14
Annex D (informative)	Measurement of oxidation deterioration degree of various plastics with different number of times of extrusion	16
Annex E (informative)	Evaluation of oxidation induction time (OIT)	18
Annex F (informative)	Life estimation by oxidation induction time (OIT) measurement	19
Annex G (informative)	Reference case of measurement of oxidation deterioration degree of substances other than plastics	21
	Bibliography	23

Foreword

This Japanese Industrial Standard has been established by the Minister of Economy, Trade and Industry, through deliberations at the Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Sensitive measurement method of peroxide in plastics by detecting ultra-weak photon emission

1 Scope

This Japanese Industrial Standard specifies the measurement method for detecting ultra-weak photon emission highly sensitively from the peroxide produced by oxidation reaction of plastics in order to evaluate the deterioration degree of a substance due to the oxidation.

The measurement method in this Standard can also be applied to the measurement of the peroxide contained in organic materials other than plastics. The organic materials refer to, for example, food, oil and medicine as well as polymer materials such as rubber and elastomer.

2 Terms and definitions

For the purpose of this Standard, the following terms and definitions apply.

2.1

chemiluminescence (CL)

phenomenon of light emission observed when electrons are excited to at least one-level higher energy level due to the energy produced by chemical reaction and then are deactivated from the energy levels to the ground state

2.2

dark current value

numeric data measured in a state where the detection element is not irradiated with light

2.3

background

numeric data measured in a state where samples are not placed in a sample container

2.4

oxidation induction time (OIT)

time when the emission intensity rapidly increases due to the disturbance of the equilibrium between the generation rate and the disappearance rate of the peroxide produced in plastics

NOTE The oxidation induction time varies according to the type of antioxidant, additive amount, measurement temperature, etc.

3 Measurement principle

The ultra-weak chemiluminescence (CL) generated when the peroxide with two or more oxygen atoms is decomposed by heat is measured with an apparatus using highly sensitive photodetection elements (e.g. photomultiplier and CCD camera). The temporal