

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS R 3223 : 2017

(FGMAJ/JSA)

Tempered fire resistance glass

ICS 81.040.20;81.040.30

Reference number : **JIS R 3223 : 2017 (E)**

Date of Establishment: 2017-03-21

Date of Public Notice in Official Gazette: 2017-03-21

Investigated by: Japanese Industrial Standards Committee
Standards Board for ISO area
Technical Committee on Architecture

JIS R 3223:2017, First English edition published in 2017-10

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2017

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

HT/AT

Contents

		Page
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Classification and symbols	2
5	Quality	3
5.1	Appearance	3
5.2	Warp	3
5.3	Edge strength of tempered fire resistance glass	3
5.4	Solar reflective tempered fire resistance glass	5
6	Dimensions and tolerances	5
6.1	Unit of side length	5
6.2	Thickness and tolerances thereon	5
6.3	Tolerance on side length	5
7	Base material plate glass	6
8	Fireproof performance	6
9	Testing methods	7
9.1	Appearance test	7
9.2	Thickness measurement	7
9.3	Side length measurement	7
9.4	Warp measurement	7
9.5	Edge strength test	8
9.6	Measurement of surface compressive stress	10
9.7	Quality tests of solar reflective tempered fire resistance glass	11
9.8	Fireproof performance test	11
10	Inspection	15
11	Packaging	15
12	Edge protection	15
13	Marking	15
13.1	Marking on product	15
13.2	Marking of performance	15

Foreword

This translation has been made based on the original Japanese Industrial Standard established by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee according to the proposal for establishment of Japanese Industrial Standard submitted by Flat Glass Manufacturers Association of Japan (FGMAJ)/Japanese Standards Association (JSA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Tempered fire resistance glass

1 Scope

This Japanese Industrial Standard specifies the tempered fire resistance glass which is rectangular or square in shape and used for fire protection equipment in buildings. The tempered fire resistance glass constituting sealed insulating glass, laminated glass and laminated sealed insulating glass is also within the scope of this Standard.

NOTE : The tempered fire resistance glass is a glass manufactured to be suitable for fire protective purposes by the following process: The soda lime glass used as a base material, is cut to the specified dimensions, given a special polishing around the edge, and then given a controlled thermal treatment to induce compressive stress on the glass surface, and the edge strength is increased so that its heat crack resistance is enhanced.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

- JIS A 1304 *Method of fire resistance test for structural parts of buildings*
- JIS A 5430 *Fibre reinforced cement boards*
- JIS B 7502 *Micrometers*
- JIS B 7512 *Steel tape measures*
- JIS B 7516 *Metal rules*
- JIS C 1605 *Mineral insulated thermocouples*
- JIS R 3106 *Testing method on transmittance, reflectance and emittance of flat glasses and evaluation of solar heat gain coefficient*
- JIS R 3202 *Float glass and polished plate glass*
- JIS R 3203 *Patterned glass*
- JIS R 3208 *Heat absorbing glass*
- JIS R 3209 *Sealed insulating glass*
- JIS R 3211 *Solar reflective glass*
- JIS R 3222 *Heat-strengthened glass*

3 Terms and definitions

For the purposes of this Standard, the following terms and definitions apply.

3.1 float tempered fire resistance glass

tempered fire resistance glass manufactured with float plate glass, polished plate glass, heat absorbing float plate glass or heat absorbing polished plate glass