

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS Z 3147 : 2017

High-speed rotating bar bending
fatigue testing of aluminium alloys
and magnesium alloys

ICS 77.120.10;77.120.20

Reference number : JIS Z 3147 : 2017 (E)

Z 3147 : 2017

Date of Establishment: 2017-12-20

Date of Public Notice in Official Gazette: 2017-12-20

Investigated by: Japanese Industrial Standards Committee

Standards Board for ISO area

Technical Committee on Metal and Inorganic

Materials

JIS Z 3147:2017, First English edition published in 2018-07

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2018

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

KK/AT

PROTECTED BY COPYRIGHT

Contents

		Page
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Grade of test	2
5	Test material and test piece	3
5.1	General requirements	3
5.2	Shape and dimensions of test piece	3
5.3	Preparation of test piece	3
6	High-speed test	4
6.1	Fatigue testing machine	4
6.2	Method of high-speed test	4
7	Temperature measurement	6
7.1	General requirements	6
7.2	Temperature measuring device	6
7.3	Installation of thermocouple	7
8	Drawing <i>S-N</i> diagram	7
9	Report of test results	8

Foreword

This Japanese Industrial Standard has been established by the Minister of Economy, Trade and Industry, through deliberations at the Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law.

This **JIS** document is protected by the Copyright Law.

It should be noted that being in conformance with this Standard may come under the use of the patent rights held by the following:

- Title of invention: Fatigue testing device
- Patent application number: 2016-033359
- Name: Yamamoto Metal Technos Co., Ltd.
- Address: 2-4-7, Setoguchi, Hirano-ku, Osaka-shi, Osaka, Japan

The relevant holders of the above-mentioned patent rights have indicated an intention of granting license to anyone under the nondiscriminatory and reasonable conditions, except to the other relevant holders of the patent rights related to this Standard who will not grant their licenses under the same conditions.

It should be noted that following this Standard does not always refer to granting a free license.

There is the possibility that some parts of this Standard may conflict with patent rights other than mentioned above. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights.

The “patent rights” as mentioned here include patent right, application for a patent after opening to the public or utility model right.

High-speed rotating bar bending fatigue testing of aluminium alloys and magnesium alloys

1 Scope

This Japanese Industrial Standard specifies the method of high-speed rotating bar bending fatigue testing at room temperature and at a frequency of over 5 000 cycles/min up to and including 8 000 cycles/min (hereafter referred to as high-speed test) for obtaining the fatigue life in the high cycle range, in which the number of cycles is over 10^7 up to and including 10^9 , for the base material and junction of structural aluminium alloys and structural magnesium alloys used for rolling stock, marine vessels, automobiles, etc.

The high-speed test method specified in this Standard is applicable to the tests in which the number of cycles is 10^7 or under.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. For standards with the year indication, only the editions of the indicated year shall be applied and the revisions (including amendments) made thereafter shall not be applied. For those without the indication of the year, the most recent edition (including amendments) shall be applied.

JIS H 4000 *Aluminium and aluminium alloy sheets, strips and plates*

JIS H 4100 *Aluminium and aluminium alloy extruded profiles*

JIS H 4140 *Aluminium and aluminium alloy forgings*

JIS H 4201 *Magnesium alloy sheets, plates and strips*

JIS H 4204 *Magnesium alloy extruded shapes*

JIS H 4205 *Magnesium alloy forgings*

JIS H 5202 *Aluminium alloy castings*

JIS H 5203 *Magnesium alloy castings*

JIS H 5302 *Aluminium alloy die castings*

JIS H 5303 *Magnesium alloy die castings*

JIS R C 310 *Coated abrasive grain sizes*

JIS Z 2273:1978 *General rules for fatigue testing of metals*

JIS Z 2274:1978 *Method of rotating bending fatigue testing of metals*

3 Terms and definitions

For the purpose of this Standard, the terms and definitions given in **JIS Z 2273:1978**, and the following apply.

3.1 standard test piece

test piece for the high-speed test classified as Class I