



**American Welding Society**  
Gateway to the world of Welding



Revised 2016-07-06  
Approved 2003-07

**NACE Standard NACE NO.12/AWS C2.23M/SSPC CS-23 STANDARD PRACTICE  
Item No. 21100**

# Specification for the Application of Thermal Spray Coatings (Metallizing) of Aluminum, Zinc, and Their Alloys and Composites for the Corrosion Protection of Steel

This NACE International (NACE)/American Welding Society (AWS)/SSPC: The Society for Protective Coatings standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard practice. Nothing contained in this NACE/AWS/SSPC standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials not discussed herein. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE, AWS and, SSPC and assume no responsibility for the interpretation or use of this standard by other parties, and accept responsibility for only those official NACE, AWS and, SSPC interpretations issued by NACE, AWS and, SSPC in accordance with their governing procedures and policies, which preclude the issuance of interpretations by individual volunteers.

Users of this NACE/AWS/SSPC standard are responsible for reviewing appropriate health, safety, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE/AWS/SSPC standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE/AWS/SSPC standard also are responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

**CAUTIONARY NOTICE:** NACE/AWS/SSPC joint surface preparation standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE/AWS/SSPC technical committee procedures. NACE, AWS, and SSPC require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication, and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE/AWS/SSPC standards may receive current information on all standards and other NACE/AWS/SSPC joint publications by contacting the organizations at the addresses below:

## ABSTRACT

*Revised in 2016. This revised NACE/AWS/SSPC joint standard contains requirements for the application of zinc and aluminum alloys to steel substrates using thermal spray, often referred to as "metallizing." The metal coatings are referred to as metallized or "thermal spray coatings" (TSCs). The standard includes requirements for surface preparation, coating application, repairing coating defects, measurement of coating thickness, adhesion testing of the applied coating, and application of sealers and topcoats over the thermally sprayed metal coating. This standard is intended for use by facility owners and specifiers who develop project specifications for the application of thermally sprayed coatings for the preservation and maintenance of steel structures and components. The standard also may be used by thermal spray coating inspectors to assess the quality of surface preparation and coating application, and by thermal spray contractors to develop project work plans.*

## KEYWORDS

*bend test, coatings, corrosion resistant coatings, cut test, erosion resistant coatings, job control record, JCR, job reference standard, JRS, metallizing, protective coating, steels, TG 146, thermal spray, thermal spray equipment, TSC feedstock material, TSC inspectors, TSCs*

NACE International  
15835 Park Ten Place  
Houston, Texas 77084-5145  
+1 281-228-6200

American Welding Society (AWS)  
8669 N.W. 36th Street #130  
Miami, FL 33166  
+1 305-443-9353

SSPC: The Society for Protective Coatings (SSPC)  
800 Trumbull Drive  
Pittsburgh PA 15205  
+1 412-281-2331

©2016, NACE International

©2016, AWS

©2016, SSPC

**ISBN 0-87171-713-15**  
**NACE No. 12/AWS C2.23M/SSPC CS-23**

## Foreword

*In NACE/AWS/SSPC standards, the terms shall, must, should, and may are used in accordance with Paragraph 2.2.1.8 of the Agreement between NACE International and SSPC: The Society for Protective Coatings. The terms shall and must are used to state mandatory requirements. The term should is used to state something considered good and is recommended but is not mandatory. The term may is used to state something considered optional.*

This NACE/AWS/SSPC joint standard contains requirements for the application of zinc and aluminum alloys to steel substrates by melting feedstock with heat from combustion or electric arc and propelling the molten metal particles onto the substrates using compressed air or another gas. This process is called thermal spray, often referred to as "metalizing," and the metal coatings are referred to as metalized or "thermal spray coatings" (TSCs).

This standard is intended for use by facility owners and specifier who develop project specifications for the application of thermally sprayed coatings for the preservation and maintenance of steel structures and components. It also may be used by thermal spray coating inspectors to assess the quality of surface preparation and coating application, and by thermal spray contractors to develop project work plans.

This joint standard was originally published in 2000 by SSPC<sup>(1)</sup> committee C.1.14 (formerly C.1.2.B), AWS<sup>(2)</sup> C2 Committee and NACE<sup>(3)</sup> Task Group (TG) 146. It was revised in 2016 by SSPC C.1.14, "Committee on Thermal Spray Coatings"; AWS C2 Committee on Thermal Spraying; and NACE TG 146, "Coating Thermal Spray," and administered by NACE Specific Technology Group (STG) 02, "Protective Coatings and Linings—Atmospheric"; and sponsored by NACE STG 09, "Process Industry—Materials Applications." It is published by NACE International under the auspices of STG 02.

<sup>(1)</sup> SSPC: The Society for Protective Coatings, 800 Trumbull Drive, Pittsburgh, PA 15205.

<sup>(2)</sup> American Welding Society (AWS), 8669 NW 36 St., #130, Miami, FL 33166.

<sup>(3)</sup> NACE International, 15835 Park Ten Place, Houston, TX 77084-5145.

# Specification for the Application of Thermal Spray Coatings (Metallizing) of Aluminum, Zinc, and Their Alloys and Composites for the Corrosion Protection of Steel

1.	Introduction .....	4
2.	Definitions .....	5
3.	Summary of Practice.....	6
4.	TSC Feedstock Requirements .....	7
5.	Surface Preparation Requirements.....	8
6.	Thermal Spray Equipment Setup.....	8
7.	Job Reference Standard (JRS) .....	9
8.	TSC Application Procedure.....	9
9.	Inspection of Applied TSC.....	10
10.	Application of Optional Sealers and Topic.....	11
11.	Records.....	12
12.	Debris Containment and Control.....	12
13.	Work Procedures and Safety .....	13
14.	Application Procedure.....	13
	References.....	13
	Bibliography .....	15
	Appendix A.....	16
	Appendix B.....	17
	Appendix C.....	19
	Appendix D.....	21

**Figures**

Figure 1	Job Reference Standard Illustration .....	5
Table 1	Minimum TSC System Requirements and Acceptance Tests.....	7
Table 2	Minimum Tensile Adhesion Requirements.....	11
Figure A3.1	TSC Bend Test: Passing and Failing Sample .....	16
Table A.1	Maximum Bend Test Mandrel Diameter for Relative TSC Thickness .....	17
Figure B3.1	Tools for Cut Test .....	17
Figure B4.1	Performing the Cut Test .....	18
Figure B4.2	Completed Cut Test .....	18
Figure B5.1	Passing the Cut Test.....	18
Figure B5.2	Failing the Cut Test.....	19
Table C.3	Blasting Media and Mesh Size Found Suitable for TSCs on Steel Substrates .....	20

## Section 1: General

- 1.1 General:** This joint standard is a procedure for the application of metallic thermal spray coating (TSCs) of aluminum, zinc, and their alloys and composites for the corrosion protection of steel. Required equipment, application procedures, and in-process quality control (QC) checkpoints are specified. Other thermal spray corrosion and erosion resistant coatings such as carbides, cobalt, nickel, and other alloys are not included in this standard. The powder thermal spray and cold spray processes are not included in this standard.
- 1.2 Scope:** Included are requirements for surface preparation, coating application, repair of coating defects, measurement of coating thickness, adhesion testing of the applied coating, and application of sealers and topcoats over the thermally sprayed metal coating. Not included in this standard are requirements for design and fabrication, thermal spray equipment qualification, coating selection, and operator and inspector certification. For successful thermal spray application, the steel structure and components should be designed and fabricated in accordance with NACE SP0178.<sup>1</sup> Additional consideration should be given to weldments and components, or structures with thermal cut edges, whose hardness may preclude adequate profile depth.
- 1.3 Safety:** The basic precautions for thermal spraying are essentially the same as for welding and cutting. Information on safety can be found in ANSI<sup>(4)</sup> Z49.1, Safety in Welding, Cutting, and Allied Processes;<sup>2</sup> and NFPA<sup>(5)</sup> 58, Standard for the Storage and Handling of Liquefied Petroleum Gases.<sup>3</sup> Read and follow safety precautions in the manufacturer's equipment technical instructions and manuals and the feedstock safety data sheet (SDS). See U.S. Code of Federal Regulations (CFR)<sup>(6)</sup> Title 29 CFR 1910.94(c)(6)(i), "Ventilation,"<sup>4</sup> for Occupational Safety & Health Administration (OSHA)<sup>(7)</sup> ventilation requirements for spray booths.

**1.3.1** This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety issues associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations before use.

**1.3.2** Potential thermal spraying hazards include exposure to vapors, dust, fumes, gases, noise (from the spray gun), and arc ultraviolet (UV) radiation. Additionally, improperly used thermal spray equipment can create potential fire and explosion hazards from oxygen, fuel, and compressed gases and a potential electrical shock hazard from the electrical and electronic equipment and charged wire spools. To minimize hazards, proper safety precautions shall be followed. Operators shall comply with the procedures in the safety references, the manufacturer's technical manuals, and the safety data sheets (SDS).

**1.3.3** All TSC equipment operators shall be qualified to a prequalified procedure before production application of the coating. Procedure and TSC equipment operator qualifications shall be retained by the contractor and made available to the end user upon request.

<sup>(1)</sup> SSPC: The Society for Protective Coatings, 800 Trumbull Drive, Pittsburgh, PA 15205.

<sup>(2)</sup> American Welding Society (AWS), 8669 NW 36 St., #130, Miami, FL 33166.

<sup>(3)</sup> NACE International, 15835 Park Ten Place, Houston, TX 77084-5145.

<sup>(4)</sup> American National Standards Institute (ANSI), 1819 L Street NW, Suite 600, Washington, DC, 20036.

<sup>(5)</sup> National Fire Protection Association (NFPA), 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101.

<sup>(6)</sup> U.S. Code of Federal Regulations (CFR), U.S. Government Printing Office (GPO), 732 N. Capitol Street NW, Washington, DC 20401.

<sup>(7)</sup> Occupational Safety & Health Administration (OSHA), U.S. Dept. of Labor, 200 Constitution Ave NW, Washington, DC 20210.