

Standard Practice

Control of External Corrosion on Underground or Submerged Metallic Piping Systems

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International FirstService Department, 1440 South Creek Drive, Houston, Texas 77084-4906 (telephone +1 [281] 228-6200).

Reaffirmed 2007-03-15
Reaffirmed 2002-04-11
Reaffirmed 1996-09-13
Revised April 1992
Revised January 1983
Revised September 1976
Revised January 1972
Approved April 1969
NACE International
1440 South Creek Drive
Houston, Texas 77084-4906
+1 281/228-6200
ISBN 1-57590-035-1
©2007, NACE International

Foreword

This standard practice presents procedures and practices for achieving effective control of external corrosion on buried or submerged metallic piping systems. These recommendations are also applicable to many other buried or submerged metallic structures. It is intended for use by corrosion control personnel concerned with the corrosion of buried or submerged piping systems, including oil, gas, water, and similar structures. This standard describes the use of electrically insulating coatings, electrical isolation, and cathodic protection (CP) as external corrosion control methods. It contains specific provisions for the application of CP to existing bare, existing coated, and new piping systems. Also included are procedures for control of interference currents on pipelines.

This standard should be used in conjunction with the practices described in the following NACE standards and publications, when appropriate (use latest revisions):

SP0572¹ RP0177² RP0285³ SP0186⁴ SP0187⁵ SP0387⁶ SP0188⁷
 TPC 11⁸ TM0497⁹

For accurate and correct application of this standard, the standard must be used in its entirety. Using or citing only specific paragraphs or sections can lead to misinterpretation and misapplication of the recommendations and practices contained in this standard.

This standard does not designate practices for every specific situation because of the complexity of conditions to which buried or submerged piping systems are exposed.

This standard was originally published in 1969, and was revised by NACE Task Group (TG) T-10-1 in 1972, 1976, 1983, and 1992. It was reaffirmed in 1996 by NACE Unit Committee T-10A on Cathodic Protection, and in 2002 and 2007 by Specific Technology Group (STG) 35 on Pipelines, Tanks, and Well Casings. This standard is issued by NACE International under the auspices of STG 35, which is composed of corrosion control personnel from oil and gas transmission companies, gas distribution companies, power companies, corrosion consultants, and others concerned with external corrosion control of buried or submerged metallic piping systems.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the NACE Publications Style Manual, 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. The term *should* is used to state something considered good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

**NACE International
Standard Practice**

**Control of External Corrosion on Underground or Submerged
Metallic Piping Systems**

Contents

1. General	1
2. Definitions	1
3. Determination of Need for External Corrosion Control	3
4. Piping Systems Design	4
5. External Coatings	6
6. Criteria and Other Considerations for CP	12
7. Design of Cathodic protection Systems	17
8. Installation of CP Systems	20
9. Control of Interference Currents	22
10. Operation and Maintenance of CP Systems	24
11. External Corrosion Control Records	25
References	26
Table 1	8
Table 2	8
Table 3	9
Table 4	10
Table 5	11
Bibliography for Section 6	14
Bibliography for Section 7	20
Appendix A	28
Appendix B	28
Appendix C	28
Appendix D	29

Section 1: General

1.1 This standard presents acknowledged practices for the control of external corrosion on buried or submerged steel, cast iron, ductile iron, copper, and aluminum piping systems.

1.2 This standard is intended to serve as a guide for establishing minimum requirements for control of external corrosion on the following systems:

1.2.1 New piping systems: Corrosion control by a coating supplemented with CP, or by some other proven method, should be provided in the initial design and maintained during the service life of the piping system, unless investigations indicate that corrosion control is not required. Consideration should be given to the construction of pipelines in a manner that facilitates the use of in-line inspection tools.

1.2.2 Existing coated piping systems: CP should be provided and maintained, unless investigations indicate that CP is not required.

1.2.3 Existing bare piping systems: Studies should be made to determine the extent and rate of corrosion on existing bare piping systems. When these studies indicate that corrosion will affect the safe or economic operation of the system, adequate corrosion control measures shall be taken.

1.3 The provisions of this standard should be applied under the direction of competent persons who, by reason of knowledge of the physical sciences and the principles of engineering and mathematics, acquired by education and related practical experience, are qualified to engage in the practice of corrosion control on buried or submerged metallic piping systems. Such persons may be registered professional engineers or persons recognized as corrosion specialists or CP specialists by NACE if their professional activities include suitable experience in external corrosion control of buried or submerged metallic piping systems.

1.4 Special conditions in which CP is ineffective or only partially effective sometimes exist. Such conditions may include elevated temperatures, disbonded coatings, thermal insulating coatings, shielding by soil attack, and unusual contaminants in the electrolyte. Deviation from this standard may be warranted in specific situations provided that corrosion control personnel in responsible charge are able to demonstrate that the objectives expressed in this standard have been achieved.

1.5 This standard does not include corrosion control methods based on chemical control of the environment, on the use of electrically conductive coatings, or on control of internal corrosion.

Section 2: Definitions ⁽¹⁾

Amphoteric Metal: A metal that is susceptible to corrosion in both acid and alkaline environments.

Anode: The electrode of an electrochemical cell at which oxidation occurs. Electrons flow away from the anode in the external circuit. Corrosion usually occurs and metal ions enter solution at the anode.

Anodic Polarization: The change of the electrode potential in the noble (positive) direction caused by current across the electrode/electrolyte interface. (See *Polarization*.)

Backfill: Material placed in a hole to fill the space around the anodes, wet pipe, and buried components of a cathodic protection system.

Beta Curve: A plot of dynamic (fluctuating) interference current or related proportional voltage (ordinate) versus the corresponding structure-to-electrolyte potentials at a selected location on the affected structure (abscissa) (see Appendix A [nonmandatory]).

Cable: One conductor or multiple conductors insulated from one another.

Cathode: The electrode of an electrochemical cell at which reduction is the principal reaction. Electrons flow toward the cathode in the external circuit.

Cathodic Disbondment: The destruction of adhesion between a coating and the coated surface caused by products of a cathodic reaction.

⁽¹⁾ Definitions in this section reflect common usage among practicing corrosion control personnel and apply specifically to how the terms are used in this standard. In many cases, in the interests of brevity and practical usefulness, the scientific definitions are abbreviated or paraphrased.