

Standard Practice

Pipeline External Corrosion Confirmatory Direct Assessment

This NACE International (NACE) standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE international standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE international standards may receive current information on all standards and other NACE international publications by contacting the NACE International *FirstService* Department, 1440 South Creek Dr., Houston, Texas 77084-4907 (telephone +1 281-228-6200).

Approved 2010-10-22
NACE International
1440 South Creek Dr.
Houston, Texas 77084-4906
+1 281-228-6200

ISBN 1-57590-240-0
© 2010, NACE International

Foreword

This standard covers the NACE external corrosion confirmatory direct assessment (ECCDA) process for buried onshore ferrous piping systems. This standard is intended to serve as a guide for applying the NACE ECCDA process on previously assessed typical pipeline systems.

ECCDA as described in this standard practice is specifically intended to address buried onshore pipelines constructed from ferrous materials. Users of this standard must be familiar with all applicable pipeline safety regulations for the jurisdiction in which the pipeline operates. This includes all regulations requiring specific pipeline integrity assessment practices and programs. This standard is intended for use by pipeline operators and others who must manage pipeline integrity.

This standard was prepared by Task Group (TG) 377, "Pipeline External Corrosion Confirmatory Direct Assessment." TG 377 is administered by Specific Technology Group (STG) 35, "Pipelines, Tanks, and Well Completions." This standard is issued by NACE International under the auspices of STG 35.

| |
|---|
| <p>In NACE standards, the terms <i>shall</i>, <i>must</i>, <i>should</i>, and <i>may</i> are used in accordance with the definitions of these terms in the <i>NACE Publications Style Manual</i>. The terms <i>shall</i> and <i>must</i> are used to state a requirement, and are considered mandatory. The term <i>should</i> is used to state something good and is recommended, but is not considered mandatory. The term <i>may</i> is used to state something considered optional.</p> |
|---|

**NACE International
Standard Practice**

Pipeline External Corrosion Confirmatory Direct Assessment

Contents

| | |
|--|----|
| 1. General..... | 1 |
| 2. Definitions..... | 6 |
| 3. Preassessment..... | 9 |
| 4. Indirect Inspection..... | 20 |
| 5. Direct Examination..... | 25 |
| 6. Post Assessment..... | 32 |
| 7. ECDA Records..... | 35 |
| References..... | 37 |
| FIGURES | |
| Figure 1(a): External Corrosion Confirmatory Direct Assessment Flowchart—Part 1..... | 3 |
| Figure 1(b): External Corrosion Confirmatory Direct Assessment Flowchart—Part 2..... | 4 |
| Figure 1(c): External Corrosion Confirmatory Direct Assessment Flowchart—Part 3..... | 5 |
| Figure 2—Preassessment Step..... | 10 |
| Figure 3—Example Selection of Indirect Inspection Tools..... | 18 |
| Figure 4—Example Definitions of ECDA Regions..... | 19 |
| Figure 5—Indirect Inspection Step..... | 21 |
| Figure 6—Direct Examination Step..... | 26 |
| Figure 7—Adjustment/Confirmation of Assumed Corrosion Rate..... | 34 |
| TABLES | |
| Table 1—ECDA Data Elements..... | 11 |
| Table 2—ECDA Tool Selection Matrix..... | 17 |
| Table 3—Example Severity Classification Criteria..... | 24 |
| Table 4—Example Prioritization Criteria for Indirect Inspection Indications..... | 28 |

Section 1: General

1.1 Introduction

1.1.1 This standard covers the NACE external corrosion confirmatory direct assessment (ECCDA) process for buried onshore ferrous piping systems. This standard is intended to serve as a guide for applying the NACE ECCDA process on typical pipeline systems.

1.1.2 This standard was written to provide flexibility for an operator to tailor the process to specific pipeline situations.

1.1.3 ECCDA is a continuous improvement process. Through successive applications, ECCDA should confirm conclusions drawn from previous assessments and identify and address locations at which corrosion activity has occurred, is occurring, or may occur.

1.1.3.1 ECCDA provides the advantage and benefit of locating areas where corrosion is likely to occur in the future rather than only areas where corrosion has already occurred.

1.1.3.2 Comparing the results of successive ECCDA applications is one method of evaluating the effectiveness of the ECCDA process, as well as the external corrosion direct assessment (ECDA) process, and demonstrating that confidence in the integrity of the pipeline is continuously improving.

1.1.4 ECCDA was developed as a process for improving pipeline safety. If external corrosion is a threat to be evaluated, ECCDA can be used to validate previous assessment conclusions or determine whether the reassessment interval is still appropriate.

1.1.5 ECCDA applications can include but are not limited to assessments of external corrosion on pipeline segments that:

1.1.5.1 Can be inspected using other common inspection methods (such as in-line inspection [ILI] or pressure testing).

1.1.5.2 Have been inspected using other inspection technologies as a method of managing future corrosion.

1.1.5.3 Have been inspected with another inspection technology as a method of establishing a reassessment interval.

1.1.6 ECCDA may detect other pipeline integrity threats such as mechanical damage, stress corrosion cracking (SCC), and microbiologically influenced corrosion (MIC). When such threats are detected, additional assessments or inspections must be performed. The pipeline operator should use appropriate methods such as ASME⁽¹⁾ B31.4,¹ ASME B31.8,² ASME B31.8S,³ and API⁽²⁾ 1160⁴ to address risks other than external corrosion.

1.1.7 The ECCDA process has limitations, but many pipelines can be successfully assessed with ECCDA. Precautions should be taken when these techniques are applied, just as with other assessment methods.

1.1.7.1 This standard may be applied to poorly coated or bare pipelines in accordance with the methods and procedures included in NACE SP0502,⁵ NACE SP0207,⁶ and NACE Standard TM0109.⁷ Poorly coated pipelines are usually treated as essentially bare if the cathodic current requirements to achieve protection are substantially the same as those for bare pipe.

⁽¹⁾ ASME International (ASME), Three Park Ave., New York, NY 10016-5990.

⁽²⁾ American Petroleum Institute (API), 1220 L St. NW, Washington, DC 20005-4070.