

Handling and Proper Usage of Inhibited Oilfield Acids

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International FirstService Department, 15835 Park Ten Place, Houston, Texas 77084 (telephone +1 281/228-6200).

ABSTRACT

Outlines methods and procedures for the handling and use of inhibited hydrochloric acid for oilfield applications. Includes general considerations when using inhibited acid in wells, such as material and equipment checks, acid solution preparation, acid solution pumping and injection, and return fluids handling; field testing of 15% or less hydrochloric acid solution for presence or absence of corrosion inhibitors; and dispersibility tests for corrosion inhibitors in oilfield acids.

KEYWORDS

corrosion inhibitors, inhibited acids, wells.

In NACE standards, the terms shall, must, should, and may are used in accordance with the definitions of these terms in the NACE Publications Style Manual, 4th ed., Paragraph 7.4.1.9. Shall and must are used to state mandatory requirements. The term should is used to state something considered good and is recommended but is not mandatory. The term may is used to state something considered optional.

Foreword

This standard practice outlines methods and procedures for handling and using inhibited stimulation acid in oilfield applications. It is intended for individuals who wish to supplement their understanding of oilfield acidizing processes or who handle or use inhibited acids in oilfield operations.

Acids are used to improve the fluid production from or injection into, subterranean formations. Hydrochloric acid is the most commonly used acid, yet these solutions are safety hazards and corrosive to metals. This standard practice outlines methods and procedures for the handling and use of inhibited stimulation acid for oilfield applications. It is intended for individuals who wish to supplement their understanding of oilfield acidizing processes or who handle or use inhibited acids in oilfield operations. This standard practice also outlines field tests for corrosion inhibitor presence and its dispersibility/solubility using a 15% (or less) HCl solution.

This standard was originally prepared in 1973 by the API⁽¹⁾/NACE Subcommittee on Oilfield Acid Corrosion Inhibitor Evaluation and jointly issued as API Bulletin D-15 (now withdrawn) and NACE Standard RP0273-73. This standard was revised in 1995 by NACE Task Group T-1D-37, a component of Unit Committee T-1D on Corrosion Monitoring and Control of Corrosive Environments in Petroleum Production Operations. It was reaffirmed in 2001 and 2007 by Specific Technology Group (STG) 31 on Oil and Gas Production—Corrosion and Scale Inhibition. It was revised in 2015 by TG 496—Review and Revise as Necessary RP0273-2007. It is issued by NACE International under the auspices of STG 31.

⁽¹⁾ American Petroleum Institute (API), 1220 L Street NW, Washington, DC 20005.

Handling and Proper Usage of Inhibited Oilfield Acids

1. General	4
2. General Guidelines for Using Inhibited Acid in Wells	4
3. Field Test of Oilfield Acids for Presence or Absence of Corrosion Inhibitors.....	7
4. Laboratory Test for Solubility-Dispersibility of Corrosion Inhibitors in Oilfield Acids..	9
References.....	10

Figures

Figure 1: Preloaded test ampoule	8
--	---

Section 1: General

- 1.1 This standard presents guidelines for minimizing acid corrosion in oilfield environments. Corrosion mechanisms include general corrosion, pitting, and stress corrosion cracking (SCC). Topics covered include well preparation, acid solution preparation, pumping, and injection, and return fluids handling.
- 1.2 This standard presents a field test of oilfield acid with HCl concentrations of 15% or less in the presence or absence of corrosion inhibitors.
- 1.3 This standard presents a laboratory test for corrosion inhibitor solubility and dispersibility in oilfield acids.

Section 2: General Guidelines for Using Inhibited Acid in Wells

- 2.1 This section provides guidelines to minimize acid-associated general corrosion, pitting, and SCC. Guidelines pertaining to well preparation, acid preparation, acid injection, and subsequent well cleanup are presented. These guidelines may not be applicable for all acid treatment, and the merits of each shall be evaluated carefully. The user shall document their decisions taken in following these guidelines.

2.2 Well Preparation Guidelines

2.2.1 Pipe Conditions: The well-pipe should be examined for evidence of corrosion or scale deposition. Leaks may result from the removal of scale or corrosion products and not directly from acid attack on the pipe material. Acid effects on nonmetallic materials (e.g., plastic-coated or cement-lined tubular goods) shall also be considered.

2.2.2 Nonmetallic Material Precautions: Acid inhibitors do not protect certain metals from corrosion by acid solutions. These metals may include aluminum, magnesium, chrome-plated metals, and galvanized metals. Consideration shall be given to removing these metals prior to treatment. In addition, stainless steel may be susceptible to SCC and other corrosion mechanisms. Lastly, acetic acid can be inhibited for use with chrome-plated metal, stainless steels, and aluminum, but cannot be adequately inhibited for use with magnesium or galvanized metal.

2.2.3 Leak Check: Precautions shall be taken to ensure that the tubing string and the packer do not leak. Pressure tests should be performed with water or brine to ensure the absence of leaks in pressure piping, tubing, and packer. If acid solution becomes trapped in the annular space, it can cause damage even if the acid was properly inhibited. Severe damage resulting from trapped acid cannot be attributed to lack of inhibitor or inhibitor failure.

2.2.4 Hydrogen Sulfide (H₂S) Precautions: Inorganic inhibitors can be precipitated by H₂S. Thus, the presence of H₂S in the acid may contribute to increasing corrosion and SCC. Hydrogen sulfide can also be produced if the acid dissolves FeS solids on the pipe surface, therefore, sour fluids should be displaced to prevent H₂S from contaminating the acid. Organic inhibitors are preferred for H₂S service although they too can be adversely affected by H₂S.

2.2.5 Well Cooling Considerations: Consideration should be given to cooling a very hot well by injecting oil or water ahead of the acid solution. However,