

External Corrosion Control of Underground Storage Tank Systems by Cathodic Protection

©2021 Association for Materials Protection and Performance (AMPP). All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means (electronic, mechanical, photocopying, recording, or otherwise) without the prior written permission of AMPP.

External Corrosion Control of Underground Storage Tank Systems by Cathodic Protection

This AMPP standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformity with this standard. Nothing contained in this AMPP standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. AMPP assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official AMPP interpretations issued by AMPP in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this AMPP standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This AMPP standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within the standard. Users of this AMPP standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities, if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: AMPP standards are subject to periodic review and may be revised or withdrawn at any time in accordance with AMPP technical committee procedures. AMPP requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of AMPP standards may receive current information on all standards and other AMPP/NACE/SSPC publications by contacting the AMPP Customer Support Department, 15835 Park Ten Place, Houston, Texas 77084-5145 (Tel: +1 281-228-6200, email: customersupport@ampp.org).

Document History

- 2021-09-21: Reaffirmed by AMPP SC 15, Pipelines and Tanks
- 2019-06-13: Revised as SP0285 by NACE TG 011, Underground Storage Tank Systems: Corrosion Control by Cathodic Protection
- 2002-04-06: Revised by NACE TG 011, Underground Storage Tank Systems: Corrosion Control by Cathodic Protection
- 1997-February: Revised by NACE T-10A-14, Corrosion Control of Underground Storage Tank System.
- 1987-March: Approved as RP0285 by NACE T-10A-14, Corrosion Control of Underground Storage Tank System.

AMPP values your input. To provide feedback on this standard, please contact: standards@ampp.org

NACE SP0285-2021

©2021 Association for Materials Protection and Performance (AMPP). All rights reserved.

External Corrosion Control of Underground Storage Tank Systems by Cathodic Protection

Foreword	5
Section 1 General	5
Section 2 Definitions	6
Section 3 Cathodic Protection of New Underground Storage Tank Systems.....	8
3.1 General	8
3.2 Factory-Fabricated Cathodic Protection Systems.....	8
3.3 Piping for New Underground Storage Tank Systems.....	9
3.4 Coatings	10
3.5 Electrical Isolation	10
3.6 Backfill.....	10
3.7 Miscellaneous	11
Section 4 Cathodic Protection of Existing Underground Storage Tank Systems	11
4.1 General	11
4.2 Physical Description.....	11
4.3 Operating History.....	12
4.4 On-site Testing.....	12
4.5 Laboratory Testing.....	14
4.6 Data Analysis	14
Section 5 Criteria for Cathodic Protection.....	15
5.1 General.....	15
5.2 Criteria for Steel Structures	15
5.3 Alternative Reference Electrodes.....	16
5.4 Special Considerations	16
Section 6 Coating Application	16
6.1 General.....	16
6.2 Galvanic Anode Systems.....	16
6.3 Impressed Current Systems.....	18
6.4 Test Stations.....	19
6.5 Wire and Connections.....	20
6.6 Miscellaneous.....	20
Section 7 Installation of Cathodic Protection Systems.....	20
7.1 General.....	20
7.2 Site Conditions	21

	7.3 Installation Procedures.....	21
	7.4 Cathodic Protection System Commissioning	22
	7.5 Records.....	23
Section 8	Operation and Maintenance.....	24
	8.1 General	24
	8.2 Maintenance Surveys	24
	8.3 Visual Inspection	25
	8.4 Remedial Measures	25
	8.5 Records	25
References	26
Tables		
Table 1	Conversion of Other Potential Measurements to CSE Equivalents	16

Foreword

This standard presents standard practices for effective control of external corrosion of underground storage tank (UST) systems by cathodic protection (CP). It is intended to be used by corrosion professionals as a guideline to establish minimum requirements for using CP to control external corrosion of metallic UST systems, including those used to contain oil, gas, and water. Specifically addressed is CP of:

- (a) Existing bare and externally coated steel USTs;
- (b) New externally coated steel USTs;
- (c) Metallic piping and flexible connectors; and
- (d) Other metallic components.

For further information on testing CP systems for UST systems, refer to NACE Standard TM0101.¹

In AMPP standards, the terms *shall* and *must* are used to state requirements and are considered mandatory. The term *should* is used to state something that is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

Section 1: General

1.1 Introduction

- 1.1.1 This standard presents standard practices for effective control of external corrosion of UST systems by CP. It is intended to serve as a guideline to establish minimum requirements for using CP to control external corrosion of metallic UST systems, including those used to contain oil, gas, and water, and that are buried, partially buried, or in contact with the soil.
- 1.1.2 When designing the CP system, the designer shall provide the owner with the design life and the assumptions used to develop the CP system design. If conditions change at the UST site, the original CP system design life may also change. Some examples of UST system changes include fluctuation in soil resistivity, UST system coating failure, adding/removing components of the UST system or site, and electrical shorting or isolation of UST components. This information should be kept as part of the permanent UST system records.
- 1.1.3 This standard does not designate specific practices for every situation because the complexity of some environmental conditions in which UST systems are buried precludes standardization of corrosion control practices.
- 1.1.4 This standard does not include corrosion control methods based on chemical control of the environment, internal linings, or the use of UST construction materials other than steel.
- 1.1.5 This standard does not override applicable safety codes and should not be used to infringe on the primary requirement of protecting personnel, the environment, and equipment. In any situation, the CP system design for UST systems should incorporate all requirements of any applicable codes, standards, and regulations as determined by authorities having jurisdiction.
- 1.1.6 The provisions of this standard shall be applied under the responsible direction of competent individuals. Such individuals must either be registered professional engineers, NACE International certified Corrosion Specialists or CP Specialists, or individuals qualified by professional education