

# Detection, Repair, and Mitigation of Cracking in Refinery Equipment in Wet H<sub>2</sub>S Environments

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

**CAUTIONARY NOTICE** NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International *FirstService* Department, 15835 Park Ten Place, Houston, Texas 77084-5145 (telephone +1 281-228-6200).

## **ABSTRACT**

*Intended to be a primary source of information on cracking in wet H<sub>2</sub>S petroleum refinery environments. Provides guidelines on detection, repair, and mitigation of cracking of existing carbon steel refinery pressure vessels, including columns, heat exchangers, drums, reboilers, separators, and more. In this standard, "wet H<sub>2</sub>S service" is defined as refinery process environments in which the concentration of H<sub>2</sub>S is 50 ppmw or greater in the aqueous phase. Thirteen tables show the frequency and severity of cracking as reported in a survey conducted on the topic. Examples of cracking are shown in photographs.*

## **KEYWORDS**

*carbon steels, cracking, hydrogen embrittlement, hydrogen sulfide, metals, refinery equipment, sour environments, steels, sulfide stress cracking, vessels.*

## Foreword

*In NACE standards, the terms shall, must, should, and may are used in accordance with the definitions of these terms in the NACE Publications Style Manual, 4th ed., Paragraph 7.4.1.9. Shall and must are used to state mandatory requirements. The term should is used to state something considered good and is recommended but is not mandatory. The term may is used to state something considered optional.*

NACE International Task Group (TG) T-8-16, "Cracking in Wet H<sub>2</sub>S Environments," was formed in 1988 to conduct an organized study on the incidence and mechanisms of cracking in pressure vessels operating in refinery wet hydrogen sulfide (H<sub>2</sub>S) environments. Specific objectives were to (a) define the nature and extent of the problem by means of an industry survey; (b) define mechanisms for the type of cracking found, to be accomplished primarily through a literature survey; (c) establish inspection guidelines for existing vessels; and (d) develop repair and mitigation guidelines for cracked vessels. Four work groups were formed to address these tasks. In 1990, a fifth work group was formed with a fifth objective, (e) to investigate material specifications and fabrication practices for new pressure vessels.

This standard practice summarizes objectives (a), (c), and (d) listed above. A technical committee report (NACE Publication 8X294)<sup>1</sup> was issued to address objective (b). Finally, objective (e) was handled by another technical committee report (NACE Publication 8X194).<sup>2</sup>

This standard is intended for use primarily by refinery corrosion and materials engineers and inspection, operations, and maintenance personnel. Information and guidance presented in this standard reflect the work of many individuals representing numerous companies worldwide.

The titles and source information of the codes, specifications, and standards referred to or discussed in this standard are provided in Appendix A (nonmandatory) rather than listed in footnotes throughout the standard. Confining this information to one appendix should help readers who have any interest in further research. This standard was originally prepared in 1996 by former TG T-8-16, "Cracking in Wet H<sub>2</sub>S Environments." It was reaffirmed in 2000 by Group Committee T-8, revised in 2004. TG 268 revised this standard in 2010 to address a number of items raised by Specific Technology Group (STG) 34 members as well as to respond to revisions in other applicable NACE standards, such as SP0472.<sup>3</sup> The original emphasis of this standard was on pressure vessels, and this emphasis remains; however, with this revision, some limited information on piping has been included at the request of TG 268 members and other members of STG 34. It was reaffirmed in 2016 by TG 268, "Wet H<sub>2</sub>S Cracking in Petroleum Refinery Pressure Vessels." TG 268 is administered by STG 34, "Petroleum Refining and Gas Processing." This standard is issued by NACE International under the auspices of STG 34.

# Detection, Repair, and Mitigation of Cracking in Refinery Equipment in Wet H<sub>2</sub>S Environments

1. General .....	4
2. Mechanisms of Cracking .....	5
3. Inspection for Cracking .....	8
4. Repair of Cracked or Blistered Equipment.....	16
5. Mitigation Considerations for Operation.....	19
References.....	20
Bibliography .....	22
Appendix A Cited Codes, Specifications, and Standards(Nonmandatory).....	23
Appendix B Nature and Extent of Problem—Results from 1990 T-8-16a Survey(Nonmandatory) .....	24
Appendix C Typical Cracks Found in Wet H <sub>2</sub> S Environments (Nonmandatory) .....	24

## Figures

Table B1: Overall Summary .....	24
Table B2: Cracking Reported by Company .....	24
Table B3: Cracking by Process Unit.....	25
Table B4: Cracking vs. Operating Temperature .....	25
Table B5: Cracking vs. H <sub>2</sub> S Concentration.....	26
Table B6: Cracking vs. Steel Specification.....	26
Table B7: Cracking vs. Steel Grade.....	26
Table B8: Cracking vs. PWHT.....	27
Table B9: Cracking vs. Blistering History .....	27
Table B10: Cracking vs. Weld Repairs .....	27
Table B11: Depth of Cracking .....	27
Table B12: Crack Penetration .....	28
Table B13: Disposition of Cracked Pressure Vessels .....	28
Figure C1: SSC in HAZ of head-to-shell weld of FCCU absorber tower .....	29
Figure C2: Hydrogen blister in ASTM A 516-70 amine contactor/water wash tower .....	30
Figure C3a: Hydrogen blisters on ID surface of amine contactor/water wash tower .....	31
Figure C3b: Cross-section of plate shown in upper photo illustrating "stepwise" cracking).....	31
Figure C4: SOHIC in soft base metal extending from the tip of SSC in a hard HAZ of a repair weld in the shell of a primary absorber (deethanizer) column in an FCCU gas plant.....	32
Figure C5: ASCC (carbonate cracking) of non-PWHT ASTM A 285-C steel shell of FCCU main fractionator overhead accumulator.....	33

## Section 1: General

**1.1** This standard is intended to be a primary source of information on cracking in wet H<sub>2</sub>S petroleum refinery environments and provides guidelines on the detection, repair, and mitigation of cracking of existing carbon steel refinery equipment in wet H<sub>2</sub>S environments.

**1.1.1** For the purposes of this standard, the term equipment refers to pressure vessels and piping made of carbon steel plate material. Refinery pressure vessels include items such as, but not limited to, columns or towers, heat exchangers, drums, reboilers, and separators.

**1.1.2** Limited cracking has been noted in seamless piping; therefore, the information in this standard concentrates on longitudinally seam-welded pipe fabricated from plate.

**1.1.3** Information on fabrication and inspection practices for new pressure vessels (never in service) is in NACE Publication 8X10.

**1.2** For the purposes of this standard, the term wet H<sub>2</sub>S environments includes, but is not limited to, refinery process environments known to cause wet H<sub>2</sub>S cracking resulting from hydrogen entry into the steel, as defined in NACE Standard MR0103.<sup>4</sup> Some environmental conditions known to cause wet H<sub>2</sub>S cracking are those containing an aqueous phase and:

- (a) > 50 ppmw total sulfide content in the aqueous phase; or
- (b) ≥ 1 ppmw total sulfide content in the aqueous phase and pH < 4; or
- (c) ≥ 1 ppmw total sulfide content and ≥ 20 ppmw free cyanide in the aqueous phase and pH < 7.6; or
- (d) > 0.3 kPa absolute (0.05 psia) partial pressure H<sub>2</sub>S in the gas phase associated with the aqueous phase of a process.

However, the threshold total sulfide content in the aqueous phase required for cracking to occur has not been clearly established. Therefore, selective application of this standard may be appropriate when experience has indicated the presence of cracking or blistering in comparable service, regardless of total sulfide content.

Alkaline environments such as alkanolamine solutions that contain sulfides and carbonate-containing sour waters also are included in the term wet H<sub>2</sub>S environments and thus are within the scope of this standard. Two forms of alkaline stress corrosion cracking (ASCC) are commonly found in these alkaline wet H<sub>2</sub>S environments. Amine stress corrosion cracking (commonly referred to as amine cracking) can occur in amine service under certain conditions, which are discussed in API<sup>(1)</sup> RP 945.<sup>5</sup> Alkaline carbonate stress corrosion cracking (commonly referred to as carbonate cracking) can occur in alkaline carbonate-containing sour waters under certain conditions. NACE Publication 34108<sup>6</sup> describes where carbonate cracking has occurred in process equipment in petroleum refining service, the refining community's current theory(ies) on the conditions and mitigation techniques that may have an impact on this type of cracking, and analytical and inspection techniques that have been used to address the issue.

**1.3** Increased industry attention to the potential for cracking of carbon steel pressure vessels began in 1984 with the rupture of a monoethanolamine (MEA) absorber tower at a Lemont, Illinois refinery. The ensuing explosion and fire resulted in fatalities and extensive damage to the facility.<sup>7</sup> In response to this incident, NACE Task Group T-8-14, "Stress Corrosion Cracking of Carbon Steel in Amine Solutions," was formed in the fall of 1984. An industry survey to determine the nature

<sup>(1)</sup>American Petroleum Institute (API), 1220 L St. NW, Washington, DC 20005-4070.