

Standard Test Method

Test Method for Measurement of Gouge Resistance of Coating Systems

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letter patent, or as indemnifying or protecting anyone against liability for infringement of letter patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and/or determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve conformance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE FirstService Department, 15835 Park Ten Place, Houston, TX 77084-5145 (telephone +1 281-228-6200).

Approved 2015-06-25
NACE International
15835 Park Ten Place
Houston, Texas 77084-5145
+1 281-228-6200

ISBN 1-57590-316-2
©2015, NACE International

Currently in preview, click buy full version

Foreword

Organic coatings are the most frequently used materials to protect buried ferrous metal pipelines from corrosion and mechanical damage. During storage, transport, and installation, pipes are exposed to severe mechanical stress that can lead to damage of the protective coating layer.

Therefore, it is important to use coatings with high-mechanical strength and toughness. Impact resistance, wear resistance, hardness, and resistance to shear scratch/indentation are good indicators of the coating's mechanical strength and toughness.

This NACE standard test method describes a reliable measuring methodology for determining the gouge resistance to shear scratch/indentation of coating systems.

The purpose of this standard is to provide a test method for determining the gouge resistance of coating systems used on buried ferrous metal pipelines.

There have been several efforts in the past to develop a reliable test method for determining the gouge resistance of coating systems, but they failed because different kinds of test equipment and test conditions have led to scattered data. This tighter test method could lead to more consistent test data.

This latest effort to develop a test method was driven by the joint efforts of representatives of coating manufacturers, coating applicators, equipment suppliers, corrosion specialists, and other personnel concerned with the construction of underground pipeline facilities.

It is intended to be used by pipeline operating companies, pipeline owners, pipeline contractors, pipeline inspection services, and pipeline coating mills.

This test method was prepared in 2015 by Task Group (TG) 034, "Pipeline Coatings, External—Gouge Test." It is administered by Specific Technology Group (STG) 03, "Coatings and Linings, Protective—Immersion and Buried Service." It is sponsored by STG 35, "Pipelines, Tanks, and Well Casings." This standard is issued by NACE under the auspices of STG 03.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

**NACE International
Standard Test Method**

**Test Method for Measurement of Gouge
Resistance of Coating Systems**

Contents

1. General	1
2. Equipment.....	1
3. Test Samples.....	3
4. Conditioning of Test Samples.....	3
5. Test Procedures	4
6. Report.....	5
7. References	6
FIGURES	
Figure 1: Schematic of Gouge Test.....	1
Figure 2: Example of a Gouge.....	1
Figure 3a: SL1 Smooth Carbide Bit	2
Figure 3b: SL1 Single Flute Burr	2
Figure 3c: SL1 Hard Metal Burr	2
Figure 4: Example of a Gouge Depth Gauge	3
Figure 5: Test Sample with Gouges and Straight Lines Drawn Through Middle Points.....	5

Section 1: General

1.1 This standard describes the design and operation of an apparatus to determine the gouge resistance of pipe coatings.

1.2 This test method is used for organic coatings that are used on buried ferrous metal pipelines. The primary application is for testing thermosetting coatings (e.g., fusion-bonded epoxy [FBE], liquid epoxy). Polyolefins (polyethylene [PE] and polypropylene [PP]) may also use this test method.

Section 2: Equipment

2.1 Gouge Test Apparatus

2.1.1 A shear gouge test apparatus consisting of a gouge tool (see Paragraph 2.1.2), an adjustable load system (see Paragraph 2.1.3), and other accessories necessary for repeatable test results shall be used (see Figures 1 and 2).




Figure 1: Schematic of a Gouge Test Apparatus



Figure 2: Example of a Gouge Tester